

Bimetallic Nanocrystals

Subjects: Nanoscience & Nanotechnology

Submitted by:  Gaojie Li

Definition

Bimetallic nanocrystals are nanoscale crystals composed of two different metal elements. Bimetallic nanocrystals are expected to exhibit improved physical and chemical properties due to the synergistic effect between the two metals, not just a combination of two monometallic properties, which have important applications in the field of catalysis, energy conversion, gas sensing and bio-detection applications.

1. Definition

Bimetallic nanocrystals are nanoscale crystals composed of two different metal elements, which include noble metal and noble metal, noble metal and non-noble metal, non-noble metal and non-noble metal.

2. Structure

Despite only two elements, the architecture of bimetallic nanocrystals are complicated and multiform. According to the atomic ordering and configuration of two different metals, bimetallic nanostructures can be classified into three main types: alloyed structures (intermetallic and solid solution) and core-shell and heterostructure, as displayed in Figure 1.




Figure 1. Bimetallic nanostructures: (a) intermetallic alloy, (b) solid solution alloy, (c) core-shell, and (d) heterostructure.

3. synthetic method

3.1. Co-Reduction

The co-reduction method entails that the precursors of two metal ions can be reduced simultaneously under certain reaction conditions, and then nucleate and grow into nanocrystals. The method is considered to be the most simple and straightforward strategy to prepare the bimetal with alloyed or intermetallic nanostructures (Figure 2)^[1]. However, core-shell and heterostructure also can be obtained by this method under certain condition.




Figure 2. Schematic diagram of synthesis process by co-reduction method.

3.2. Seed-Mediated Growth

Seed-mediated growth is an effective synthesis strategy to generate the bimetallic nanocrystals with well-defined structures that are difficult to obtain by other methods^{[2][3]}. The conceptual diagram of these two structures obtained by the seed growth method is shown in Figure 3. In this process, one metal is

firstly synthesized as a seed, and then the other metals are uniformly deposited on the seeds surface and form a shell layer, resulting in a bimetallic nanocrystal with a core-shell structure; And if the second metal is only deposited and grown in the special sites of seed crystals, the bimetallic nanocrystal with a heterogeneous structure will be obtained.




Figure 3. Schematic diagram of synthesis process by seed-mediated growth method.

3.3. Thermal Decomposition

3.4. Galvanic Replacement Reaction

As a good way to produce bimetals with special structure, the galvanic replacement reaction is an electrochemical process, in which one metal is replaced by another metal ion due to their different reduction potential in the reaction system. In essence, the reaction is also an oxidation-reduction process. Metal (C) with high potential can be easily oxidized. Metal ions (D^{+x}) with low reduction potential are difficult to reduce by chemical reduction method, but can be reduced by metal C. Therefore, the method is usually suitable for preparing the inactive metal nanocrystals using active metal as template.^{[4][5]}




Figure 4. Schematic diagram of the experimental procedure that prepared hollow Au nanocrystals by using Ag nanocrystals with various morphologies as templates.^[4]

3.5. Other Methods

Thanks to the nanoengineering technique, the morphology and microstructure of the nanoparticles can be precisely controlled. In addition to the four methods we mentioned above, there are some other synthetic protocols to prepare bimetals with well-defined shapes, such as hard or soft template methods, combustion synthesis, hydrothermal treatment, the combination of the two approaches and so on. These methods have their own advantages and disadvantages in preparing bimetallic nanocrystals with different special structures.

4. Applications

Bimetallic nanocrystals have been widely used in many important fields from science to technology. In comparison to single metal nanocrystals, bimetallic nanocrystals possess many unique properties due to the adjustable composition, controllable morphology and variable electronic structure, so they also have many practical and potential applications including catalysis, sensing, biodetection, biomedicine, and so on.

4.1. Catalytic Applications

Bimetallic nanocatalysts have been widely used in solution electrocatalytic reactions, such as methanol electrooxidation, hydrogen electrooxidation, and oxygen reduction reaction and so on. At the

same time, they are often used to catalyze heterogeneous reactions, such as CO oxidation, NO_x reduction, and petroleum reforming and so on. The applications of bimetallic nanocrystals in heterogeneous catalytic reactions such as anode and cathode of fuel cells are briefly introduced.

4.1.1 Electrocatalysis

1. **Oxygen Reduction Reaction (ORR)**
2. **Methanol Oxidation Reaction (MOR)**
3. **Oxygen Evolution Reaction (OER)**

4.1.2 Heterogeneous Catalysis

4.2. Energy Conversion Applications

The research on conversion of CO₂ to other high value-added carbon containing small molecular compounds, such as hydrogenation to alkanes, olefins and other fuels, or to medium acid, ethanol and other chemical products, has not been extended to large-scale applications. The application of this process mainly depends on the development of high catalytic performance and low-cost catalysts. The preparation of CO, HCOOH, CH₃OH, CH₄, C₂H₆ and other organic hydrocarbon small molecular compounds by the electrochemical catalysis of CO₂ have attracted the attention of researchers as a promising method for large-scale energy storage (power storage) of solar energy and wind energy due to its relatively mild conditions, strong controllability and high yield per unit area (compared with a direct photocatalytic method).

Compared with the alloy materials with noble metal components, the bimetallic materials formed by two kinds of non-noble metal can also obtain high catalytic activity and selectivity if the size, shapes and compositions could be reasonably designed.^{[6][7]}

4.3. Sensing Applications

A sensor is a detection device, which can selectively recognize the target information and transform the information into electrical signal or other measurable signal according to certain rules. Under normal conditions, bimetallic NPs can be designed and obtained to express their unique properties of each metal. The modification and doping of bimetallic nanocrystals especially noble metals (Pd, Pt, Au, Rh, and Ag) have been proved to be among the most effective ways to reduce the operating temperature of sensors, enhance the response of target gases and improve the selectivity of sensors.^{[8][9]}

4.3.1. Metal Oxide Semiconducting (MOS) Sensors

4.3.2. Electrochemical Sensors

4.3.3. Catalytic Combustion Gas Sensor

References

1. Kyle D. Gilroy; Aleksey Ruditskiy; Hsin-Chieh Peng; Dong Qin; Younan Xia; Bimetallic Nanocrystals: Syntheses, Properties, and Applications. *Chemical Reviews* **2016**, *116*, 10414-10472, [10.1021/acs.chemrev.6b00211](https://doi.org/10.1021/acs.chemrev.6b00211).
2. Chun-Lun Lu; Kariate Sudhakara Prasad; Hsin-Lun Wu; Ja-An Annie Ho; Michael H. Huang; Au Nanocube-Directed Fabrication of Au–Pd Core–Shell Nanocrystals with Tetrahedral, Concave Octahedral, and Octahedral Structures and Their Electrocatalytic Activity. *Journal of the American Chemical Society* **2010**, *132*, 14546-14553, [10.1021/ja105401p](https://doi.org/10.1021/ja105401p).
3. Xue Wang; Madeline Vara; Ming Luo; Hongwen Huang; Aleksey Ruditskiy; Jinho Park; Shixiong Bao; Jingyue Liu; Jane Howe; Miaofang Chi; et al. Zhaoxiong Xie Younan Xia Pd@Pt Core–Shell Concave Decahedra: A Class of Catalysts for the Oxygen Reduction Reaction with Enhanced Activity and Durability. *Journal of the American Chemical Society* **2015**, *137*, 15036-15042, [10.1021/jacs.5b10059](https://doi.org/10.1021/jacs.5b10059).
4. Yugang Sun; And Brian T. Mayers; Younan Xia; Template-Engaged Replacement Reaction: A One-Step Approach to the Large-Scale Synthesis of Metal Nanostructures with Hollow Interiors. *Nano Letters* **2002**, *2*, 481-485, [10.1021/nl025531v](https://doi.org/10.1021/nl025531v).

5. Yugang Sun; Benjamin Wiley; ‡ And Zhi-Yuan Li; † Younan Xia; Synthesis and Optical Properties of Nanorattles and Multiple-Walled Nanoshells/Nanotubes Made of Metal Alloys. *Journal of the American Chemical Society* **2004**, *126*, 9399-9406, [10.1021/ja048789r](https://doi.org/10.1021/ja048789r).
6. Abdesslem Jedidi; Shahid Rasul; Dilshad Masih; Luigi Cavallo; Kazuhiro Takanabe; Generation of Cu-In alloy surfaces from CuInO₂ as selective catalytic sites for CO₂ electroreduction. *Journal of Materials Chemistry A* **2015**, *3*, 19085-19092, [10.1039/c5ta05669a](https://doi.org/10.1039/c5ta05669a).
7. Toshihiro Takashima; Tomohiro Suzuki; Hiroshi Irie; Electrochemical Reduction of Carbon Dioxide to Formate on Palladium-Copper Alloy Nanoparticulate Electrode. *Electrochemistry* **2019**, *87*, 134-138, [10.5796/electrochemistry.18-00086](https://doi.org/10.5796/electrochemistry.18-00086).
8. Gaojie Li; Zhixuan Cheng; Qun Xiang; Liuming Yan; Xiaohong Wang; Jiaqiang Xu; Bimetal PdAu decorated SnO₂ nanosheets based gas sensor with temperature-dependent dual selectivity for detecting formaldehyde and acetone. *Sensors and Actuators B: Chemical* **2018**, *283*, 590-601, [10.1016/j.snb.2018.09.117](https://doi.org/10.1016/j.snb.2018.09.117).
9. Gaojie Li; Xiaohong Wang; Liuming Yan; Yan Wang; Zhanying Zhang; Jiaqiang Xu; PdPt Bimetal-Functionalized SnO₂ Nanosheets: Controllable Synthesis and its Dual Selectivity for Detection of Carbon Monoxide and Methane. *ACS Applied Materials & Interfaces* **2019**, *11*, 26116-26126, [10.1021/acsami.9b08408](https://doi.org/10.1021/acsami.9b08408).

Keywords

bimetallic nanocrystals; controllable synthesis; catalytic applications; gas sensing application; Bio-detection applications

Retrieved from <https://encyclopedia.pub/15524>