Conversion of 5-hydroxymethylfurfural to 2,5dimethylfuran

Subjects: Chemistry, Applied Contributor: Nor Azam Endot

Many researchers have extensively explored selective hydrogenation of 5-hydroxymethylfurfural (HMF) to 2,5dimethylfuran (DMF), and some of them were able to achieve high conversion and a high yield of DMF under certain reaction conditions. However, the main challenge is to reduce the operational cost using cost-effective catalysts as an alternative to the expensive noble metals. Overall, the approach of using bifunctional catalysts is an important direction for catalysis in general and particularly for reactions that require significantly different types of elementary steps as part of an overall reaction. For this reason, efforts to use the rational design of interfaces will become important for supplementing the promising initial work in demonstrating bifunctional catalysis for catalytic transformations of biomass-derived 5-hydroxymethylfurfural to a potential liquid fuel, 2,5-dimethylfuran. Apart from the different types of metal and support, it was also observed that reaction conditions, namely the type of solvent, H_2 donor, reaction temperature, reaction time, and H_2 .

hydroxymethylfurfural

dimethylfuran hydrodeoxygenation

Catalysts

1. Introduction

Among the works on 5-hydroxymethylfurfural (HMF) hydrogenation reported in the literature, it can be seen that most of the catalysts used consist of a noble metal, such as Pd, Ru or Pt, apart from transition metal catalysts based on Cu, Ni and Co supported on metal oxides and carbon. The addition of a secondary metal from a transitional metal to a noble metal has also been used by many researchers. Apart from the different types of metal, it was also observed that reaction conditions, namely the type of solvent, H₂ donor, reaction temperature, reaction time and H₂ pressure, play an important role in influencing the HMF conversion and 2,5-dimethylfuran (DMF) yield.

Dumesic et al. were able to produce a reasonable DMF yield using CuCrO₄ and CuRu/C catalysts under a batch condition in 1-butanol at 220 °C and 6.8 bar H₂ in 10 h (entry 2). It was observed that the addition of Ru to Cu supported on carbon increased the DMF yield from 61% to 71% under the same reaction condition. Although the Ru/Co_3O_4 (entry 13)-catalysed reaction achieved a high DMF yield (93%) at relatively low pressure and temperature, a high catalyst loading (40 wt% to HMF) and long reaction time (24 h) are needed. Pd/C in supercritical carbon dioxide leads to a 100% yield of DMF in 2 h; however, the reaction requires a specific combination of water and supercritical CO₂ [entry 12].

DMF production by catalytic transfer hydrogenation has also been investigated using formic acid (FA) ^{[1][2]}, methanol ^[3] and isopropyl alcohol (IPA) ^{[4][5]}. Thananatthanachon et al. demonstrated the conversion of HMF to DMF using Pd/C/H₂SO₄ (2 mmol HMF in THF, 0.4 g of catalyst) with 95% yield of DMF in 15 h at 120 °C ^[6]. However, this requires the addition of H₂SO₄. Dutta et al. performed the same reaction using Ru/C; however, a lower DMF yield was obtained (30%) ^[7].

2. Hydrogenation with Noble Metal Catalysts

Typical processes to acquire upgraded biofuels or chemical platforms require the use of homogeneous, heterogeneous or biological (enzymes, microorganisms and yeasts) catalysts ^[8]. This process normally involves acid-catalysed reactions. As the conversion of HMF to DMF is a hydrogenation/hydrogenolysis process, catalysts used for this reaction are hydrogenation catalysts, commonly noble metals such as Pd ^[9], Ru ^{[1][10][11]}, Pt ^[12] and others, which are generally supported on carbon in some form. This combination provides high reactivity and good dispersion on sustainable and tuneable supports with a high surface area and easy-to-modify porosity and surface properties.

However, noble metals may be deactivated in water, which is commonly used in these hydrogenation reactions. Moreover, their price is high and unsustainable. Only in the case of low concentrations and high catalyst lifetime can these catalysts be considered as those of the future for biomass transformations. However, they possess high reactivity even at low hydrogen pressures, and it was shown that it is possible to obtain 100% HMF conversion and 98% DMF yield after 2 h at 180 °C and 10 bar H₂ over Pt-Co in hollow carbon nanospheres ^[12]. In another study, Ru/Co₃O₄ catalyst exhibited 93.4% DMF yield at 130 °C and 7 bar H₂ ^[11]. Further still, transfer hydrogenation with 2-propanol as a hydrogen donor was carried out by Jae and co-workers, who used Ru/C and achieved 100% HMF conversion and 81% DMF selectivity after 6 h at 190 °C under 20 bar N₂ ^[4]. With the same catalyst, Ru/C, in the presence of THF as the solvent yielded 94.7% DMF at 200 °C under 20 bar H₂ for 2 h ^[2].

3. Hydrogenation Reactions with a Transitional Metal Catalyst

To date, most of the catalysts being used in the transformation of HMF into DMF involved precious metals such as Ru, Pt and Pd ^[13]. Thus an alternative catalytic system based on non-precious metals (Co, Ni, Cu and Fe) is crucial from the economic point of view since they are cheaper.

Ni and Co are typically active metals for hydrogenation processes since both metals can hydrogenate C=C and C=O bonds ^{[14][15]}. Raney nickel catalyst, for example, has been used in a wide range of hydrogenation reactions, such as in the hydrogenation of nitro compounds, alkenes, carbonyl compounds, nitriles, alkynes and aromatic compounds ^[16]. Recently, Iriondo et al. demonstrated that Cu catalyst supported on ZrO_2 has the best selectivity towards DMF among other compared metals such as Pt and Ru ^[17]. Ni supported on Co_3O_4 also shows good activity as an additive to Co_3O_4 in converting HMF to DMF, since both of the elements have a good ability to break

C–O bonds ^[18]. A 76% yield of DMF was achieved under relatively mild reaction conditions (130 °C, 10 bar H₂, 24 h). Kong et al. showed that Ni supported on Al_2O_3 is promising for HMF hydrogenation, with a high yield of DMF, DMTHF and DHMTHF ^[14]. The modulation of the surface metal–acid bifunctional site via calcination temperatures and control reaction conditions resulted in a high yield of DMF (91.5%), DMTHF (97.4%) and DHMTHF (96.2%).

Catalysts based on Ni and Co were also used in the chemoselective hydrogenation of furfural. Furfural hydrogenation is quite similar to HMF hydrogenation, apart from having less methyl and a hydroxyl group ^[17]. Ni/SiO₂ was reported to have better reactivity than Rh/SiO₂ for the hydrogenation of furfural and selectivity to furfuryl alcohol ^[19]. **Figure 1** shows the schemes proposed by Nakagawa et al. for the hydrogenation mechanism of furfural and furfural alcohol over Ni/SiO₂ catalyst. Based on the kinetic analysis, they reported that adsorption of furfural on Ni/SiO₂ catalyst is much stronger than that of furfural alcohol (FOL) under hydrogenation conditions, suggesting that furfural is adsorbed at the C=O group ^[20].



Figure 1. Proposed mechanisms for the hydrogenation of (A) furfural and (B) FOL over Ni/SiO₂^[19].

The use of new and cheap metals for the hydrogenation of HMF to DMF should be explored more since this could be beneficial as an alternative for the precious metal. Apart from the transition metal being used as a monometallic catalyst for hydrogenation, the combination of these metals with other transition metals or noble metals is also getting more attention ^[13].

4. Hydrogenation Reactions with Bimetallic Catalysts

Bimetallic catalysts have been receiving a lot of attention in selective oxidation ^[21], Fischer–Tropsch ^[22] and hydrogenation catalytic ^[23] reactions. This is due to positive synergistic effects emerging upon alloying that result in structures and properties that are distinct from those of the pure element. The chemical and physical properties may be tuned by varying the composition and atomic ordering as well as the size of the clusters. In fact, bimetallic

metal nanoparticles may display not only magic sizes but also magic compositions at which the alloy presents special stability that may determine the chemical reactivity, especially catalytic activity ^[24]. For instance, in benzene hydrogenation, Yoon et al. ^[25] synthesised a bimetallic catalyst of Pd-Rh/CNT via a microemulsion method, and it was found that this combination exhibits the highest TOF compared to its monometallic analogues. Another example was shown by Zhu et al., who showed that Ru-Ni/C (0.024 wt% Ru, 1.00 wt% Ni) shows the highest TOF for hydrogenation of benzene compared to monometallic Ni/C and Ru/C ^[23]. The authors suggested that this is due to the efficient synergistic effect between Ru, Ni and NiO sites, stemming from the nanostructure of Ru on Ni/NiO nanoparticles. It is also speculated that the additional metals can improve the size and morphology of active particles as well as the catalysts' selectivity ^[26].

In the hydrogenation of glucose to sorbitol, the addition of metalloids (elements that have properties of both metals and non-metals, such as boron, B) as the promoter to Ni demonstrated an improvement in activity. The authors found that the higher activity of this alloy catalyst is due to the combination of the structural features and the surface electronic state ^[27]. Extended X-ray absorption fine structure (EXAFS) analyses of the samples revealed that the amorphous catalyst has a lower Ni coordination number and a shorter Ni–Ni bond distance compared to a crystalline catalyst that has been calcined. This was considered to be responsible for the active catalyst, which is beneficial for hydrogenation reactions. Furthermore, the addition of B to Ni makes it electron-rich, and as a consequence, the glucose adsorption through the C=O group is weakened. This means that more H_2 could be adsorbed on the Ni-B catalyst, and hence a higher hydrogenation activity is observed ^[27].

Besides improving the reactivity of the reaction, the bimetallic system also can help in reducing the dependence on noble metals by incorporating some non-noble metals, such as Ni and Co. Not only they are cheaper, but in certain molar ratios, they could result in better reactivity than the noble metals themselves ^[28].

As for the hydrogenation of bio-derived furan derivatives such as furfural and HMF, many Ni-, Co- or Cu-based bimetallic catalysts have been used ^[29]. Recently. Chen et al. demonstrated that carbon-coated Cu-Co bimetallic nanoparticles show excellent performance in selective hydrogenolysis of HMF to DMF, with 99.4% yield of DMF at 180 °C and 50 bar H₂ in 8 h ^[30]. X-ray photoelectron spectroscopy (XPS) analysis revealed the coexistence of cobalt oxide species that are responsible for the synergistic effect between cobalt species and copper, while Luo et al. reported that (10 wt%) Pt-Ni alloyed nano-crystals supported on carbon with a ratio of 3:1 exhibit a high yield of DMF compared to other compositions and its monometallic catalysts ^[31]. Ni-Fe/CNT (10 wt%) also displayed high selectivity towards DMF and DHMF, depending on the temperature. This was attributed to the formation of Ni-Fe alloys species that is beneficial to the C–O bond cleavage ^[32]. The bimetallic non-noble metals were also demonstrated by Giovanni et al. A high yield of the mixture of both DMF and DMTHF was obtained when Cu-Zn nanoalloy was used in HMF hydrogenation ^[33]. The authors proposed that the synergistic effect between active CuO sites with Lewis acidic ZnO sites is responsible for the high reactivity based on a previous study ^[34].

Figure 2 illustrates the adsorption structure of furfural on the catalyst surface, as proposed by Nakagawa et al. ^[35]. It was believed that the addition of Ir may promote the adsorption of the C=O site on furfural and weaken the adsorption on the furan ring in the case of Pd-Ir/SiO₂ catalyst. This was demonstrated by comparing the selectivity

of furfural and furfuryl alcohol on Pd-Ir alloy to monometallic Pd and Ir. The high reactivity of furan ring hydrogenation was observed on monometallic Pd. In the presence of furfural, the hydrogenation of furfuryl alcohol over Ir was suppressed, suggesting the strong adsorption of C=O on the surface of Ir.



Figure 2. The proposed adsorption structure of furfural on the catalyst surface. Adapted from [35].

The property of the adsorption of the substrate on the catalyst can be changed by the addition of a secondary metal, particularly an oxophilic metal (electropositive element) such as Sn. Vetere et al. ^[19] studied the chemoselective hydrogenation of furaldehyde using monometallic Pt, Ni or Rh and a bimetallic catalyst with Sn supported on SiO₂. They found that the addition of Sn shows significant conversion for Pt and an increase in selectivity towards furfuryl alcohol with Ni. **Figure 3** shows the promotion effect of an oxophilic metal on substrate adsorption at the C=O bond ^{[36][37][38]}. The presence of an oxophilic metal or cation on the noble metal surface induces the hydrogen species formed on the noble metal to be transferred to the C=O bond to achieve selective hydrogenation.



Figure 3. The proposed adsorption structure of furfural on the catalyst surface.

After the recent increased interest in biomass-related transformations, the challenges for the catalysis chemist reside in the complex structure and functionalities of biomass. The challenge in designing catalysts to facilitate the new transformations is to prepare catalysts that can selectively remove functional groups and break specific chemical bonds in the biomass-derived feedstock. Thus, bimetallic catalyst systems seem to be promising due to the synergistic effects between two combination metals.

This synergistic phenomenon can be explained by recent studies by Luo et al. ^{[31][39]} and Chen et al. ^[30]. The monolayer oxide present on the surface interacted weakly with the furan ring to prevent the hydrogenation of the ring and the ring-opening of DMF. At the same time, it acted as an active site for the hydrogenolysis process. The proposed successive hydrogenolysis mechanism of DHMF on Pt-Co alloy is depicted in **Figure 4**. DHMF undergoes C–O bond cleavage on a honeycomb edge site consisting of two Co atoms, forming a loosely bound radical and an OH group. Next, an H atom transfers from the OH group to the radical, yielding MFA and a chemisorbed oxygen atom. The second hydroxymethyl group undergoes similar C–O scission, forming DMF as the final product.



Figure 4. Reaction mechanism of DHMF hydrodeoxygenation to MFA on the $Co_3O_2/Pt(111)$ surface based on DFT calculation. Reproduced from ^[39] by permission of American Chemical Society.

5. The Role of a Support

Catalyst support also plays an important role in the selectivity of hydrogenation reactions. The supports are usually metal oxides or carbon with the goal of maximising the specific surface area, thus giving better dispersion of the active phase. The most common support includes various types of silica, alumina and carbon. However, the use of

microporous support typically involves mass transfer issues due to diffusion limitation. In porous catalyst particles, the reacting molecules diffuse first through the fluid film surrounding the particle surface and then into the pores of the catalyst to the active sites. Similarly, the reaction products diffuse out of the catalyst grains. As an outcome of the pore diffusion in the most common reaction kinetics, the reaction rates inside the pore are lower than with the concentration level of the main bulk.

Carbon materials have been one of the most widely studied supports for catalyst preparation owing to their advantages ^[40]. Other than being low in cost, carbon also gives better dispersion due to a high surface area compared to other supports, such as Al_2O_3 and SiO_2 . Moreover, the carbon surface is relatively inert, preventing any unwanted reactions catalysed by the support surface or the reaction of the support with the active phase. Most importantly, carbon can minimise poisoning issues due to its hydrophobic nature. For example, it leads to a weaker interaction between the catalyst and the solvent. However, the chemical nature of their surface can be modified chemically to decrease the hydrophobic character by oxidising treatment ^[40]. For example, treatment with hydrogen peroxide and nitric acid introduces oxygen surface groups, which are responsible for the improvement of the hydrophilic character of the carbon surface.

Priecel et al. demonstrated that CNTs as support of Ru improve DMF yield and shorten the reaction time from 3 h to 1 h compared to carbon as support. This owing to the superior accessibility of pores in carbon nanotubes, together with an electronic promotional effect in the carbon nanotubes, appears to be responsible for the superior activity of the catalysts supported on carbon nanotubes [41].

Ricardo et al. reported that Ru supported on materials with a high isoelectric point (basic), such as ceria, magnesia-zirconia and x-alumina, results in a high yield of DHMTHF as compared to a low-isoelectric-point (acidic) support, such as SiO_2 , for selective hydrogenation of HMF ^[42]. This demonstrates that the basicity of the catalyst support favours the formation of ring hydrogenation of DHMF to DHMTHF. In contrast, the acidic support favours the formation of ring products, such as 1,2,5-hexanetriol.

The effect of different supports on a palladium catalyst for the hydrogenation of HMF was studied by Cai et al. ^[43]. Acidic Pd/x-Al₂O₃ and Pd/SiO₂ show a similar activity as that of Pd/C, apart from the selectivity towards DHMTF, which is higher than that of Pd/C, suggesting that the acidity of the support influences the product's selectivity. When the reaction is prolonged to 3 h, the final product is mainly DHMTHF due to the saturation of the C=C bond in DHMF (<u>Scheme 2</u>). As for Pd/TiO₂, DHMF is the main product even when the reaction time is prolonged. It is speculated that by dispersing the metal on the reductive support (TiO₂), the metal catalyst demonstrates the potential for selectively hydrogenating the carbonyl group without affecting the C=C bond 89]. In the case of Pd/HT catalyst, the basic HT support is found to restrain the dehydration reaction and inhibits the hydrogenation activity of Pd. It is also reported that HT could induce ring-opening, C–O dissociation and other side reactions ^[44]. An extensive review on the effect of the support used and the kinetic modelling of HMF transformation into DMF has been performed by Maki et al. ^[45] and Esteves et al. ^[46].

6. The Role of Solvents

The medium of reaction also plays an important role in determining the reactivity or the product yield in a chemical reaction, especially the hydrogenation of HMF ^[47]. Usually, a solvent like water is preferable since it is a green solvent and no extra precaution is needed to handle it as a waste. However, not all reactions are suitable with water as the solvent. In general, a solvent can be divided into three different categories: polar protic, polar aprotic and non-polar. Polar protic solvents often display hydrogen bonding and have acidic hydrogen. These solvents have a high dielectric constant and polarity for instant water, formic acid, methanol, butanol and propanol. These types of solvents are most likely to participate in the reaction. Polar aprotic solvents lack hydrogen bonds and have moderate-to-high dielectric constants. They do not participate in the reaction, as they are relatively free in solution, making them more reactive. Common examples of such solvents are acetone, acetonitrile, THF and DMSO. Nonpolar solvents are solvents such as hexane, benzene and toluene that have low dielectric constants and are not good solvents for a charged species.

A recent study by Chatterjee et al. ^[48] showed that a solvent with negative delta (δ) values that is capable of accepting electrons shows higher conversion of HMF. However, as the δ value increased, the conversion of HMF decreased. The authors suggested that solvent adsorption leads to the partial blocking of metal active sites. In addition, a neutral medium was preferred over a basic or an acidic medium. Water was also found to be superior to other organic solvents used for the conversion of HMF and the production of DHMF ^[44].

The study of the effect of solution-phase acidity on the selectivity for the hydrogenation of HMF was performed by Alamillo et al. ^[42]. Treatment of the HMF feed with resin led to an increase of over 20% in the selectivity of DHMTHF using Ru catalyst. The treatment with resin resulted in an increase in pH, and the increment in pH suggested that the minor impurities of acid mixed with HMF decrease the selectivity to DHMTHF. The influence of the addition of specific types of acid on the hydrogenation of HMF was also studied ^[42]. Levulinic acid and H₂SO₄ were added to the reaction mixture, and the addition of levulinic acid led to a decrease in DHMTHF yield, while H₂SO₄ resulted in a significant decline in DHMTHF selectivity from 76% to 9%. It was suggested that HMF and DHMF undergo acid-catalysed degradation, thus leading to low selectivity ^[42].

The study of the hydrogenation of HMF using different solvents was also carried out by Alamillo et al. using a water-1-butanol biphasic system, water, a mixture of THF and water and THF-alcohol ^[42]. It was found that HMF and DHMF are completely converted in each of the reactions. The selectivity of DHMTHF decreased when pure water was used, indicating the presence of additional degradation pathways in the presence of water. Detailed reviews on the effect of solvents were discussed by Wang et al. ^[49].

7. Conclusions

Selective hydrogenation of HMF to DMF has been extensively explored by many researchers, and some of them were able to achieve high conversion as well as a high yield of DMF under certain reaction conditions. However, the main challenge is to reduce the operational cost by using cost-effective catalysts as an alternative to the expensive noble metals. Overall, the approach of using bifunctional catalysts is an important direction for catalysis in general and particularly for reactions that require significantly different types of elementary steps as part of an

overall reaction. For this reason, efforts to use rational design of interfaces will become important for supplementing the promising initial work in demonstrating bifunctional catalysis for catalytic transformations of biomass-derived 5-hydroxymethylfurfural to a potential liquid fuel, 2,5-dimethylfuran. Apart from the different types of metal, it was also observed that reaction conditions, namely the type of solvent, H₂ donor, reaction temperature, reaction time and H₂ pressure, play an important role in influencing the HMF conversion and DMF yield.

Future studies should focus on more variety of inexpensive metal combinations as an alloy and sustainable support without compromising the high yield of DMF. For example, the combination of non-noble metals, such as Ni, Co, Cu and Fe, would be interesting since Ni and Co are capable of converting HMF to DMF, although specific metal ratios and loading are crucial in resulting in a better catalyst. A kinetic study would be helpful to learn the adsorption behaviour of HMF and its intermediates, which would provide some insights into the principles of selectivity control that can guide catalyst selection.

References

- 1. De, S.; Dutta, S.; Saha, B. One-Pot Conversions of Lignocellulosic and Algal Biomass into Liquid Fuels. ChemSusChem 2012, 5, 1826–1833.
- Hu, L.; Tang, X.; Xu, J.; Wu, Z.; Lin, L.; Liu, S. Selective Transformation of 5-Hydroxymethylfurfural into the Liquid Fuel 2,5-Dimethylfuran over Carbon-Supported Ruthenium. Ind. Eng. Chem. Res. 2014, 53, 3056–3064.
- 3. Mitra, J.; Zhou, X.; Rauchfuss, T. Pd/C-catalyzed reactions of HMF: Decarbonylation, hydrogenation, and hydrogenolysis. Green Chem. 2014, 17, 307–313.
- 4. Zhang, J.; Lin, L.; Liu, S. Efficient Production of Furan Derivatives from a Sugar Mixture by Catalytic Process. Energy Fuels 2012, 26, 4560–4567.
- Shun, N.; Naoya, I.; Kohki, E. Selective hydrogenation of biomass-derived 5hydroxymethylfurfural (HMF) to 2,5-dimethylfuran (DMF) under atmospheric hydrogen pressure over carbon supported PdAu bimetallic catalyst. Catalysis Today 2014, 232, 89–98.
- 6. Thananatthanachon, T.; Rauchfuss, T.B. Efficient Production of the Liquid Fuel 2,5-Dimethylfuran from Fructose Using Formic Acid as a Reagent. Angew. Chem. Int. Ed. 2010, 49, 6616–6618.
- 7. Dutta, S.; Mascal, M. Novel Pathways to 2,5-Dimethylfuran via Biomass-Derived 5-(Chloromethyl)furfural. ChemSusChem 2014, 7, 3028–3030.
- 8. Gallezot, P. Conversion of biomass to selected chemical products. Chem. Soc. Rev. 2012, 41, 1538–1558.
- 9. Chatterjee, M.; Ishizaka, T.; Kawanami, H. Hydrogenation of 5-hydroxymethylfurfural in supercritical carbon diox-ide-water: A tunable approach to dimethylfuran selectivity. Green Chem.

2014, 16, 1543–1551.

- 10. Lucas, N.; Kanna, N.R.; Nagpure, A.S.; Kokate, G.; Chilukuri, S. Novel catalysts for valorization of biomass to value-added chemicals and fuels. J. Chem. Sci. 2014, 126, 403–413.
- Zu, Y.; Yang, P.; Wang, J.; Liu, X.; Ren, J.; Lu, G.; Wang, Y. Efficient production of the liquid fuel 2,5-dimethylfuran from 5-hydroxymethylfurfural over Ru/Co3O4 catalyst. Appl. Catal. B Environ. 2014, 146, 244–248.
- Wang, G.-H.; Hilgert, J.; Richter, F.H.; Wang, F.R.; Bongard, H.; Spliethoff, B.; Weidenthaler, C.; Schüth, F. Platinum–cobalt bimetallic nanoparticles in hollow carbon nanospheres for hydrogenolysis of 5-hydroxymethylfurfural. Nat. Mater. 2014, 13, 293–300.
- Saha, B.; Abu-Omar, M.M. Current Technologies, Economics, and Perspectives for 2,5-Dimethylfuran Production from Biomass-Derived Intermediates. ChemSusChem 2015, 8, 1133– 1142.
- Kong, X.; Zheng, R.; Zhu, Y.; Ding, G.; Zhu, Y.; Li, Y.-W. Rational design of Ni-based catalysts derived from hydrotalcite for selective hydrogenation of 5-hydroxymethylfurfural. Green Chem. 2015, 17, 2504–2514.
- 15. Nakagawa, Y.; Tamura, M.; Tomishige, K. Catalytic Reduction of Biomass-Derived Furanic Compounds with Hydrogen. ACS Catal. 2013, 3, 2655–2668.
- 16. Fouilloux, P. The nature of raney nickel, its adsorbed hydrogen and its catalytic activity for hydrogenation reactions (review). Appl. Catal. 1983, 8, 1–42.
- 17. Iriondo, A.; Mendiguren, A.; Güemez, M.; Requies, J.; Cambra, J.F. 2,5-DMF production through hydrogenation of real and synthetic 5-HMF over transition metal catalysts supported on carriers with different nature. Catal. Today 2017, 279, 286–295.
- Nagpure, A.S.; Venugopal, A.K.; Lucas, N.; Manikandan, M.; Thirumalaiswamy, R.; Chilukuri, S. Renewable fuels from biomass-derived compounds: Ru-containing hydrotalcites as catalysts for conver-sion of HMF to 2,5-dimethylfuran. Catal. Sci. Technol. 2015, 5, 1463–1472.
- 19. Vetere, V.; Merlo, A.B.; Ruggera, J.F.; Casella, M.L. Transition metal-based bimetallic catalysts for the chemoselective hydrogenation of furfuraldehyde. J. Braz. Chem. Soc. 2010, 21, 914–920.
- Nakagawa, Y.; Nakazawa, H.; Watanabe, H.; Tomishige, K. Total Hydrogenation of Furfural over a Silica-Supported Nickel Catalyst Prepared by the Reduction of a Nickel Nitrate Precursor. ChemCatChem 2012, 4, 1791–1797.
- Sugano, Y.; Shiraishi, Y.; Tsukamoto, D.; Ichikawa, S.; Tanaka, S.; Hirai, T. Supported Au–Cu Bimetallic Alloy Nanoparticles: An Aerobic Oxidation Catalyst with Regenerable Activity by Visible-Light Irradiation. Angew. Chem. Int. Ed. 2013, 52, 5295–5299.

- 22. Iglesia, E.; Soled, S.; Fiato, R.; Via, G. Bimetallic Synergy in Cobalt Ruthenium Fischer-Tropsch Synthesis Catalysts. J. Catal. 1993, 143, 345–368.
- 23. Zhu, L.; Zheng, L.; Du, K.; Fu, H.; Li, Y.; You, G.; Chen, B.H. An efficient and stable Ru-Ni/C nanobimetallic catalyst with a comparatively low Ru loading for benzene hydrogenation under mild reaction conditions. RSC Adv. 2013, 3, 713–719.
- 24. Ruban, A.V.; Skriver, H.L.; Nørskov, J.K. Surface segregation energies in transition-metal alloys. Phys. Rev. B 1999, 59, 15990–16000.
- Yoon, B.; Pan, H.-B.; Wai, C.M. Relative Catalytic Activities of Carbon Nanotube-Supported Metallic Nanoparticles for Room-Temperature Hydrogenation of Benzene. J. Phys. Chem. C 2009, 113, 1520–1525.
- 26. Oosthuizen, R.S.; Nyamori, V.O. Carbon Nanotubes as Supports for Palladium and Bimetallic Catalysts for Use in Hydrogenation Reactions. Platin. Met. Rev. 2011, 55, 154–169.
- 27. Li, H.; Li, H.; Deng, J.-F. Glucose hydrogenation over Ni–B/SiO2 amorphous alloy catalyst and the promoting effect of metal dopants. Catal. Today 2002, 74, 53–63.
- 28. Jordão, M.H.; Simões, V.; Cardoso, D. Zeolite supported Pt-Ni catalysts in n-hexane isomerization. Appl. Catal. A: Gen. 2007, 319, 1–6.
- 29. Scholz, D.; Aellig, C.; Hermans, I. Catalytic Transfer Hydrogenation/Hydrogenolysis for Reductive Upgrading of Furfural and 5-(Hydroxymethyl)furfural. ChemSusChem 2013, 7, 268–275.
- Chen, B.; Li, F.; Huang, Z.; Yuan, G. Carbon-coated Cu-Co bimetallic nanoparticles as selective and recyclable catalysts for production of biofuel 2,5-dimethylfuran. Appl. Catal. B Environ. 2017, 200, 192–199.
- Luo, J.; Lee, J.D.; Yun, H.; Wang, C.; Monai, M.; Murray, C.B.; Fornasiero, P.; Gorte, R.J. Base metal-Pt alloys: A general route to high selectivity and stability in the production of biofuels from HMF. Appl. Catal. B Environ. 2016, 199, 439–446.
- Yu, L.; He, L.; Chen, J.; Zheng, J.; Ye, L.; Lin, H.; Yuan, Y. Robust and Recyclable Nonprecious Bimetallic Nanoparticles on Carbon Nanotubes for the Hydrogenation and Hydrogenolysis of 5-Hydroxymethylfurfural. ChemCatChem 2015, 7, 1701–1707.
- Bottari, G.; Kumalaputri, A.J.; Krawczyk, K.; Feringa, B.L.; Heeres, H.J.; Barta, K. Copper-Zinc Alloy Nanopowder: A Robust Precious-Metal-Free Catalyst for the Conversion of 5-Hydroxymethylfurfural. ChemSusChem 2015, 8, 1323–1327.
- Sun, J.; Yang, G.; Ma, Q.; Ooki, I.; Taguchi, A.; Abe, T.; Xie, Q.; Yoneyama, Y.; Tsubaki, N. Fabrication of active Cu–Zn nanoalloys on H-ZSM5 zeolite for enhanced dimethyl ether synthesis via syngas. J. Mater. Chem. A 2014, 2, 8637–8643.

- 35. Nakagawa, Y.; Takada, K.; Tamura, M.; Tomishige, K. Total Hydrogenation of Furfural and 5-Hydroxymethylfurfural over Supported Pd–Ir Alloy Catalyst. ACS Catal. 2014, 4, 2718–2726.
- 36. Ni, Z.-M.; Xia, M.Y.; Shi, W.; Qian, P.P. Adsorption and Decarbonylation Reaction of Furfural on Pt (111) Surface. Acta Phys. -Chim. Sinica 2013, 29, 1916–1922.
- 37. Aramendía, M.; Borau, V.; Jiménez, C.; Marinas, J.; Porras, A.; Urbano, F.J. Selective Liquid-Phase Hydrogenation of Citral over Supported Palladium. J. Catal. 1997, 172, 46–54.
- 38. Vicente, A.; Lafaye, G.; Especel, C.; Marécot, P.; Williams, C.T. The relationship between the structural properties of bimetallic Pd–Sn/SiO 2 catalysts and their performance for selective citral hydrogenation. J. Catal. 2011, 283, 133–142.
- Luo, J.; Yun, H.; Mironenko, A.V.; Goulas, K.; Lee, J.D.; Monai, M.; Wang, C.; Vorotnikov, V.; Murray, C.B.; Vlachos, D.G.; et al. Mechanisms for High Selectivity in the Hydrodeoxygenation of 5-Hydroxymethylfurfural over PtCo Nanocrystals. ACS Catalysis 2016, 6, 4095–4104.
- 40. Serp, P.; Figueiredo, J.L. (Eds.) Carbon Materials for Catalysis; John Wiley & Sons: Hoboken, NJ, USA, 2009.
- 41. Priecel, P.; Endot, N.A.; Carà, P.D.; Lopez-Sanchez, J.A. Fast Catalytic Hydrogenation of 2,5-Hydroxymethylfurfural to 2,5-Dimethylfuran with Ruthenium on Car-bon Nanotubes. Ind. Eng. Chem. Res. 2018, 57, 1991–2002.
- 42. Alamillo, R.; Tucker, M.; Chia, M.; Pagan-Torres, Y.; Dumesic, J. The selective hydrogenation of biomass-derived 5-hydroxymethylfurfural using heterogeneous catalysts. Green Chem. 2012, 14, 1413–1419.
- 43. Cai, H.; Li, C.; Wang, A.; Zhang, T. Biomass into chemicals: One-pot production of furan-based diols from carbohydrates via tandem reactions. Catal. Today 2014, 234, 59–65.
- 44. Ohyama, J.; Esaki, A.; Yamamoto, Y.; Arai, S.; Satsuma, A. Selective hydrogenation of 2hydroxymethyl-5-furfural to 2,5-bis(hydroxymethyl)furan over gold sub-nano clusters. RSC Adv. 2013, 3, 1033–1036.
- 45. Mäki-Arvela, P.; Ruiz, D.; Murzin, D.Y. Catalytic Hydrogenation/Hydrogenolysis of 5-Hydroxymethylfurfural to 2,5-Dimethylfuran. ChemSusChem. 2020, 14, 150–168.
- 46. Esteves, L.M.; Brijaldo, M.H.; Oliveira, E.G.; Martínez, J.J.; Rojas, H.; Caytuero, A.; Passos, F.B. Effect of support on selective 5-hydroxymethylfurfural hydrogenation towards 2,5-dimethylfuran over copper catalysts. Fuel 2020, 270, 117524.
- 47. Jae, J.; Zheng, W.; Karim, A.M.; Wei, G.; Lobo, R.F.; Vlachos, D.G. The Role of Ru and RuO2in the Catalytic Transfer Hydrogenation of 5-Hydroxymethylfurfural for the Production of 2,5-Dimethylfuran. ChemCatChem 2014, 6, 848–856.

- 48. Chatterjee, M.; Ishizaka, T.; Kawanami, H. Selective hydrogenation of 5-hydroxymethylfurfural to 2,5-bis-(hydroxymethyl)furan using Pt/MCM-41 in an aqueous medium: A simple approach. Green Chem. 2014, 16, 4734–4739.
- 49. Wang, H.; Zhu, C.; Li, D.; Liu, Q.; Tan, J.; Wang, C.; Cai, C.; Ma, L. Recent advances in catalytic conversion of biomass to 5-hydroxymethylfurfural and 2, 5-dimethylfuran. Renew. Sustain. Energy Rev. 2019, 103, 227–247.

Retrieved from https://encyclopedia.pub/entry/history/show/59256