## The Application of Artificial Intelligence in Magnetic Hyperthermia

Subjects: Engineering, Industrial Contributor: Magdalena Osial, Agnieszka Pregowska

Magnetic hyperthermia (MHT) is more commonly used in various biomedical applications. Magnetic hyperthermia (MH), a clinical alternative to tumor treatments, also became a powerful tool for cancer treatment by exposing tumor tissue to elevated temperatures to achieve a therapeutic effect. It has been successfully applied to the treatment of different types of cancer including the brain, spine, lung, prostate, breast, and pancreas. It is also a promising alternative to traditional cancer therapies, particularly in the case of aggressive brain cancer like glioblastoma. MHT's huge advantages are connected with biosafety, deep tissue penetration, and a focused place of action. The development of nanomedicine involves complex nanomaterial research involving magnetic nanomaterials and their use in magnetic hyperthermia. The selection of the optimal treatment strategies is time-consuming, expensive, unpredictable, and not consistently effective. Delivering personalized therapy that obtains maximal efficiency and minimal side effects is highly important. Thus, Artificial Intelligence (AI) based algorithms provide the opportunity to overcome these crucial issues.

Keywords: artificial intelligence ; magnetic hyperthermia ; drug

### 1. Introduction

Artificial Intelligence (AI), including Machine Learning (ML), can be used to solve various issues of information processing, including pattern recognition, classification, clustering, dimensionality reduction, image recognition, natural language processing, and predictive analysis <sup>[1]</sup>. AI-based algorithms can be applied to solve complex problems <sup>[2][3][4]</sup>. Recent algorithm development enables its application in many areas of everyday life, such as industry, medicine, and nanomedicine; including nanomaterials with magnetic properties <sup>[5]</sup>. Consequently, a new opportunity to predict drug influence and responsiveness based on retrospective databases became available <sup>[6]</sup>. It may contribute to the development of optimized healthcare <sup>[1]</sup>.

An important direction in developing medicine is to provide an effective method of dealing with various neoplastic diseases. The heterogeneous nature of tumors contributes to the problems in selecting effective treatment mechanisms. It is crucial to deliver drugs directly to the tumor core, the area most active in proliferation but less vascularized and hypoxic. Thus, the critical challenge in choosing the optimal therapy is determining the synergy of the drug depending on its dose, administration timing, and current treatment process. The latest development in nanotechnology enables the design of nanocarriers for targeted drug delivery, improving medicine release and beating cancer cells. In turn, manufacturing the nanoparticles, which can be loaded with drugs or other agents (stabilizers, compounds for diagnostics), is a time and financial outlays-consuming process. Thus, the AI-based prediction of the effect of nanoparticles with drugs on living tissues enables the development of targeted nanomedicine <sup>[8](9]</sup>.

# 2. Artificial Intelligence and Machine Learning as Support for Magnetic Hyperthermia-Based Research and Prediction Properties of Nanoparticles

Since each subject is different, and drug synergy gives a different output in an individual case, transforming Artificial Intelligence (AI) to nanomedicine enables the analysis of large data sets and the effective selection of the optimal therapy [10][11]. It is essential in cancer therapy, particularly in the application of magnetic hyperthermia, to predict the optimal parameters of the process. AI includes various algorithms; researchers reviewed the existing solutions in the area of research, which involve the use of magnetic hyperthermia, taking into account their effectiveness, type and size of data sets, input and output parameters, and application fields. In [12], ANN was applied to predict the size of AgNO<sub>3</sub> particles. It turned out that the most sensitive parameters are both AgNO<sub>3</sub> concentration and reaction temperature. As the AgNO<sub>3</sub> suspension has no relation with magnetic hyperthermia, the literature shows the successful use of ANN in the prediction of particular properties of nanomaterials. In [13], the ANN was proposed to predict the shape and size of TiO<sub>2</sub>

nanoparticles. In **Table 1**, the algorithms for the evaluation of the nanoparticle size were compared. It turned out that neural networks, in particular networks based on multilayer perceptrons, enable the prediction of the size of nanoparticles with high accuracy, i.e., 0.97 based on the experimental data.

 Table 1. The comparison of the algorithm's performance takes account of the prediction of the optimal size of the nanoparticles.

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference	
Algorithm	Type: Artificial Neural Network				
		- polymer concentration			
0.94		- drug	- size		
	experimental data	- solvent ratio	0120	[14]	
		- mixing rate			
0.97	experimental data	<ul> <li>polymer molecular weight-number of blocks in the copolymer used</li> <li>ratio of polymer to drug</li> </ul>	- size	[15]	
Algorithm	Type: multilayer perceptron				
		- inherent viscosity			
		- molecular weight			
		- lactide-co-glycolide ratio			
		- inner/outer phase Polyvinyl alcohol (PVA)			
		- concentration			
		- PVA molecular weight			
		- inner phase volume			
0.97	745 experimental data from	- encapsulation rate	- size	[ <u>16]</u>	
	the merature	- mean particle size			
		- concentration			
		- dissolution pH			
		- number of dissolution additives			
		- dissolution additive concentration			
		- production method			
		- dissolution time			

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference
0.99		- particle concentration		
		- reaction temperature		
	experimental data	- UV-visible wavelength	- size	[12]
		- montmorillonite d-		
		- spacing		

The AI-based analysis of thermal conductivity, taking into account different shapes of nanoparticles (i.e., spherical, ellipsoidal, clubbed, and sheet), has been made in [12]. It turned out that AI-based prediction can substantially increase the relative thermal conductivity of nanofluids. In **Table 2**, the algorithms for the evaluation of the thermal conductivity of the nanoparticle were compared.

Table 2. The comparison of the algorithm's performance takes account of effective thermal conductivity.

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference
Algorithm <sup>-</sup>	Type: cascade-forward neural	network		
0.93	1273 data collected from the literature	- temperature-solid volume fraction- solid volume fraction	<ul> <li>effective thermal</li> <li>conductivity</li> </ul>	[ <u>18]</u>
0.99	80 dataset experimental data and 389 data collected from the literature	<ul> <li>temperature concentration</li> <li>shape factor</li> <li>thermal conductivity</li> </ul>	- relative thermal conductivity	[17]
Algorithm <sup>-</sup>	Type: Artificial Neural Network			
0.99	776 experimental data set	<ul><li>average diameter</li><li>volume fraction</li><li>temperature</li></ul>	- the ratio of thermal conductivity	[19]
Algorithm <sup>-</sup> generalized	Type: multilayer perceptron, ra d regression, Least-Squares Si	dial basis function neural network upport Vector Machines		
0.97	80 dataset experimental data and 389 data collected from the literature	<ul> <li>temperature concentration</li> <li>shape factor</li> <li>thermal conductivity</li> </ul>	- relative thermal conductivity	[17]
Algorithm Type: radial basis function neural network				
0.95	80 dataset experimental data and 389 data collected from the literature	<ul> <li>temperature concentration</li> <li>shape factor</li> <li>thermal conductivity</li> </ul>	- relative thermal conductivity	[17]

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference
0.96	80 dataset experimental data and 389 data collected from the literature	<ul><li>temperature concentration</li><li>shape factor</li><li>thermal conductivity</li></ul>	<ul> <li>relative thermal conductivity</li> </ul>	[17]

One of the most important properties of nanoparticles is neurotoxicity <sup>[18]</sup>. In <sup>[20]</sup>, the classification model for evaluation neurotoxicity based on Random Forest was proposed while in <sup>[21]</sup>, the evaluation of antibacterial capacity using different AI-based algorithms was shown. In turn, <sup>[22]</sup> applied ML and perturbation theory to evaluate the toxicity of nanoparticles. In **Table 3** the comparison of the algorithms for the prediction of the neurotoxicity of the nanoparticle was compiled. So far, the ANN can also be used to predict specific parameters for magnetic nanoparticles, see **Table 4**.

 Table 3. The comparison of the algorithms for prediction of the nanoparticle toxicity.

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference
Algorithm	Type: Artificial Neural	Networks		
		- average values of the		
0.97	260 datasets from	- descriptors for nontoxic	- toxicity	[22]
	the interature	- toxic cases with the specific value of the descriptor of		
		each toxic or nontoxic		
Algorithm Vector Mac	Type: Least Absolute :hine	Shrinkage Selection Operator Regression, Ridge Regression E	lastic Net Regressio	on, Support
		- specific surface		
		- area		
	<ul> <li>hydrodyn</li> <li>zeta pote</li> <li>core size</li> <li>exposure</li> <li>datasets from</li> <li>duration</li> </ul>	- hydrodynamic size		
		- zeta potential		
		- core size	- core size	
		- exposure dose		
0.78		- duration	dose	[21]
	interature	- shape	- species of	
		- type	bacterium	
		- coating		
		- bacterium		
		- aggregation		
		Available online: <u>https://github.com/mahsa-</u> <u>mirzaei/RFR_ABA/commits?author=mahsa-mirzaei</u> (accessed on 24 November 2022).		
Algorithm	Type: Random Forest			

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference
		- specific surface		
		- area		
		- hydrodynamic size		
0.78		- zeta potential		
		- core size	- core size	
		- exposure dose	osure dose - exposure ation dose [2	
	datasets from literature	- duration		[ <u>21]</u>
		- shape	<ul> <li>species of bacterium</li> </ul>	
		- type	Jactenum	
		<ul> <li>coating</li> <li>bacterium</li> </ul>		
	<ul> <li>bacterium</li> <li>aggregation</li> </ul>			
		mirzaei/RFR_ABA/commits?author=mahsa-mirzaei (accessed on 24 November 2022).		
		- dose		
		- duration		
		- nanoparticle type		
		- nanoparticle shape		
0.00		- zeta potential	- cell viability	[23]
0.98		- surface area		
		- cell origin		
		- cell type		
		- cell line		
		- assay		

#### Table 4. The comparison of the algorithms for prediction of the optimal properties of nanomaterials performance.

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference	
Algorithm Type: Artificial Neural Network					
0.93 (for Young's modulus) 0.96 (ultimate tensile strength)	153 datasets from the literature	<ul> <li>weight percent</li> <li>- particle size</li> </ul>	<ul><li>Young's modulus</li><li>ultimate tensile strength</li></ul>	[ <u>24]</u>	

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference
		- wavelength		
		- peak intensity	- particle size	
0.97	3404 experimental	- full width at half-	- reaction yield	[25]
	ualasci	maximum	- quantum yield	
		<ul> <li>peak area of the main peak</li> </ul>		
		- extraction time		
		- temperature	- extraction yield of	[00]
).98	experimental data sets	- pressure	essential oils	[26]
		- modifier volume		
0.99	experimental data sets	- composition	<ul> <li>specific absorption</li> </ul>	[27]
			Tale	
		- particle concentration		
		<ul> <li>alternating magnetic field strength</li> </ul>	antimal parameters	
).99	420 experimental data sets	- temperature	- optimal parameters	[28]
		- time		
Algorithm Type: Rando	om Forest			
		- nanoparticle type		
		- nanoparticle core		
		- surface modification		
		- modification type-size		
).75	652 datasets from the literature	- zeta potential	- optimal composition	[29]
		- polydispersity index		
		- corona formation		

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference
0.94 (compressive strength) 0.97 (porosity)	data collected from the literature	<ul> <li>elastic modulus</li> <li>fracture toughness diopside</li> <li>hardystonite</li> <li>bredigite</li> </ul>	<ul> <li>compressive strength</li> <li>porosity</li> </ul>	[ <u>26]</u>

The following research <sup>[5]</sup> described the ML application to the prediction of power losses of magnetic particles, which is an important issue in drug targeting. This research has been done on a limited amount of data containing simulated particles' simulated properties, showing the proposed approach's colossal potential. In **Table 5**, the algorithm's performance in predicting power losses of magnetic particles has been made. The evaluation of the biological and mechanical behavior of the potential candidate for nanomaterials, i.e., silicates bioceramics-magnetite bio-nanocomposites, which can be applied to the magnetic hypothermia based on ANN has been made in <sup>[26]</sup>. In turn, the results presented by <sup>[24]</sup> show that ANN has better accuracy than genetic algorithms (GA) in predicting Young's modulus and ultimate tensile strength of nanocomposites, particularly polyethylene composites with multiple nanoparticles.

**Table 5.** The comparison of the algorithm's performance takes into account the prediction of power losses of magnetic particles.

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference
Algorithm	Type: Neural Network			
0.90	3963 records of simulated records	<ul> <li>temperature</li> <li>vertex field</li> <li>nanoparticles diameter</li> <li>magnetic anisotropy</li> <li>saturation magnetization</li> <li>the identity of nanoparticles</li> </ul>	<ul> <li>coercive field</li> <li>magnetic remanence</li> <li>hysteresis loop area</li> </ul>	[5]
Algorithm	Type: Random Forrest			
0.90	3963 records of simulated records	<ul> <li>temperature</li> <li>vertex field</li> <li>nanoparticles diameter</li> <li>magnetic anisotropy</li> <li>saturation magnetization</li> <li>the identity of nanoparticles</li> </ul>	<ul> <li>coercive field</li> <li>magnetic remanence</li> <li>hysteresis loop area</li> </ul>	[5]

In <sup>[2Z]</sup>, the application of the genetic algorithm for the optimization of agar nanospheres, which were used in the manufacturing process of drug loading, was proposed. The optimization problem was formulated to minimize the size of the particle, release efficiency, and PDI, as well as to maximize the absolute value of zeta potential and loading efficiency. It turned out that a genetics algorithm could successfully predict the parameters of Bupropion hydrochloride-loaded agar nanospheres. In turn, <sup>[28]</sup> the closed-loop optimization of the release process of the Poly (lactic-co-glycolic acid) (PLGA)

biodegradable particles with ANN and genetic algorithms was described. As input data, particle size, and initial burst percent at the desired levels were chosen. It was postulated that the proposed algorithm can predict drug delivery.

In  $\frac{[29]}{2}$ , the ANN was used to predict the optimal composition of two-dimensional graphene–Fe<sub>3</sub>O<sub>4</sub> nanohybrids, which are dedicated to magnetic hyperthermia. It enables the prediction of the composition of the optimal nanohybrid, which can be applied to magnetic hypothermia in low dosage. The optimization based on multilayer perceptron neural networks of the experimental conditions of nanoparticles was described in  $\frac{[30]}{3}$ . The influence on nanoparticle characteristics factors like environmental conditions and type of precipitating agent was investigated. In turn, the mathematical framework for the magnetic drug delivery taking into account the ferrofluid flow was shown in  $\frac{[31]}{3}$ .

Another critical issue in the manufacturing of nanoparticles is the synthesis process <sup>[32][33]</sup>. It should maintain precisely controlled characteristics. Since the synthesis of nanoparticles is a long-term and cost-consuming process due to the involvement of multiple chemical substances, the AI-based algorithm provides the opportunity to develop efficient experimental protocols. The following research describes the application of AI to the synthesis of semiconductor, metal, carbon-based and polymeric nanoparticles <sup>[34]</sup>. In <sup>[25]</sup>, based on ultraviolet-visible (UV-vis) and PL spectrum data, the prediction of the optimal parameters of the synthesis of combinatorial CdSe nanoparticles was proposed. Thus, the heuristic and Bayesian optimization can be applied to the evaluation of the synthesis of the nanoparticles. Such an example is far from the magnetic hyperthermia application, while AI support can improve the experimental work also in the magnetic nanoparticles and magnetic hyperthermia field. In <sup>[35]</sup> the genetics algorithm particle swarm optimization (PSO) was used to predict the magnetic field generation. In <sup>[35]</sup>, GA was used to optimize the Specific Absorption Rate in the case of hyperthermia treatment of the human head.

Recently, attempts were made to apply AI-based algorithms in the research of hydrogels. In reference <sup>[36]</sup>, the Artificial Neural Network and Least Square Support Vector Machine were used to evaluate the swelling degree in the hydrogel, namely poly(NIPAAm-co-AAc) IPN. It turned out that Artificial Intelligence-based algorithms can, successfully and with high accuracy, predict the influence of pH and temperature on hydrogel deswelling behaviors. At the same time, the ANN model has higher computational efficiencies than the LS-SVM approach while maintaining this similar accuracy. Thus, in <sup>[37]</sup>, ANN was used to evaluate the deswelling and heating behavior of the field-sensitive hydrogels, like poly(NIPAAm-co-VSA)/Fe<sub>3</sub>O<sub>4</sub> IPN. The comparison of the algorithms for predicting deswelling behaviors is made in **Table 6**. It turned out that ANN achieved the highest efficiency in predicting deswelling degrees.

Accuracy	Application Field Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference
Algorithm	Type: Artificial Neural Network			
0.99	1638 experimental data set	<ul><li>time</li><li>temperature</li><li>pH</li></ul>	- swelling degree	[ <u>36]</u>
0.99	438 experimental data set	<ul> <li>alternating magnetic field strength</li> <li>time</li> <li>temperature</li> </ul>	<ul><li>swelling degree</li><li>temperature</li></ul>	[ <u>37]</u>
Algorithm	Type: Least Square Support Vector Mac	hine		
0.98	1638 experimental data set	<ul><li>time</li><li>temperature</li><li>pH</li></ul>	- swelling degree	[ <u>36]</u>

Table 6. The comparison of the algorithms for the prediction of deswelling behavior.

Magnetic nanoparticles are also used to remove various types of substances. The efficiency of the approach is strictly connected with the percent of compounds adsorbed onto modified magnetic nanoparticles <sup>[37][38][39]</sup>. Thus, AI-based algorithms can be applied to predict removal efficiency. In <sup>[39]</sup> the application of the Artificial Neural Network and adaptive neuro-fuzzy inference system for the prediction of the chromium removal efficiency was shown. In **Table 7**, the comparison of algorithms for the evaluation of the removal efficiency is presented. It turned out that the combination of the Artificial Neural Network with an adaptive neuro-fuzzy inference system provides higher prediction efficiency.

Table 7. The comparison of the algorithms for prediction of the removal efficiency.

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference
Algorithm	Type: Artificial Neural Network			
0.88	29 experimental data set	<ul> <li>initial dye concentration</li> <li>initial pH</li> <li>contact time</li> <li>temperature</li> </ul>	- maximum removal efficiency	[38]
0.97	experimental data set	<ul> <li>temperature</li> <li>stirring rate</li> <li>initial ethyl benzene</li> <li>xylene (BTEX) concentration</li> <li>contact time</li> <li>pH</li> <li>adsorbent dose</li> </ul>	- removal efficiency	[40]
0.98	18 experimental datasets from the literature	<ul> <li>pH</li> <li>adsorbent dose</li> <li>initial coupons concentration</li> </ul>	- removal efficiency	[41]
0.98	experimental dataset	<ul> <li>pH</li> <li>initial heptachlor concentration</li> <li>contact time</li> <li>stirring rate</li> <li>adsorbent dose</li> </ul>	<ul> <li>heptachlor removal efficiency</li> </ul>	[42]

Accuracy	Database (Type and Size if Available)	Input Parameters	Output Parameters	Reference
0.99	experimental dataset	<ul> <li>dose of photocatalyst</li> <li>the power of visible light</li> <li>initial concentration of tetracycline</li> <li>radiation time</li> <li>oxidant concentration</li> </ul>	<ul> <li>removal percentage of tetracycline</li> </ul>	[4]
Algorithm Type: genetic algorithm				
0.86	29 experimental data set	<ul> <li>initial dye concentration</li> <li>initial pH</li> <li>contact time</li> <li>temperature</li> </ul>	- maximum removal efficiency	[38]
Algorithm Type: adaptive neuro-fuzzy inference system				
0.94	18 experimental datasets from the literature	<ul> <li>pH</li> <li>adsorbent dose</li> <li>initial coupons concentration</li> </ul>	- removal efficiency	[41]
0.98	experimental dataset	<ul> <li>pH</li> <li>initial heptachlor concentration</li> <li>contact time</li> <li>stirring rate</li> <li>adsorbent dose</li> </ul>	- heptachlor removal efficiency	[42]
0.99	experimental data	<ul> <li>dose of photocatalyst</li> <li>the power of visible light</li> <li>initial concentration of tetracycline</li> <li>radiation time</li> <li>oxidant concentration</li> </ul>	<ul> <li>removal percentage of tetracycline</li> </ul>	[4]

### References

1. Joshi, A.V. Machine Learning and Artificial Intelligence; Springer Nature: Cham, Switzerland, 2020.

- Nichols, J.A.; Herbert Chan, H.W.; Baker, M.A.B. Machine learning: Applications of artificial intelligence to imaging and diagnosis. Biophys. Rev. 2019, 11, 111–118.
- 3. Cioffi, R.; Travaglioni, M.; Piscitelli, G.; Petrillo, A.; De Felice, F. Artificial Intelligence and Machine Learning Applications in Smart Production: Progress, Trends, and Directions. Sustainability 2020, 12, 492.
- Nesfchi, M.M.; Pirbazari, A.E.; Saraei, F.E.K.; Rojaee, F.; Mahdavi, F.; Rastegar, S.A.F. Fabrication of plasmonic nanoparticles / cobalt doped TiO2 nanosheets for degradation of tetracycline and modeling the process by artificial intelligence techniques. Mater. Sci. Semicond. Process. 2021, 122, 105465.
- 5. Coïsson, M.; Barrera, G.; Celegato, F.; Allia, P.; Tiberto, P. Specific loss power of magnetic nanoparticles: A machine learning approach. APL Mater. 2022, 10, 081108.
- Martinelli, C.; Biglietti, M. Promising strategies for overcoming cancer drug resistance: From nanomedicine to artificial intelligence. World, J. Med. Innov. 2021, 1, 23–32.
- Jiang, F.; Jiang, Y.; Zhi, H.; Dong, Y.; Li, H.; Ma, S.; Wang, Y.; Dong, Q.; Shen, H.; Wang, Y. Artificial intelligence in healthcare: Past, present and future. Stroke Vasc. Neurol. 2017, 2, 230–243.
- 8. Moore, J.A.; Chow, J.C.L. Recent progress and applications of gold nanotechnology in medical biophysics using artificial intelligence and mathematical modeling. Nano Express 2021, 2, 022001.
- 9. Egorov, E.; Pieters, C.; Korach-Rechtman, H.; Shklover, J.; Schroeder, A. Robotics, microfluidics, nanotechnology and AI in the synthesis and evaluation of liposomes and polymeric drug delivery systems. Drug Deliv. Transl. Res. 2021, 11, 345–352.
- Vrontis, D.; Christofi, M.; Pereira, V.; Tarba, S.; Makrides, A.; Trichin, E. Artificial intelligence, robotics, advanced technologies and human resource management: A systematic review. Int. J. Hum. Resour. Manag. 2022, 33, 1237– 1266.
- 11. Li, Z.; Tian, X.; Qiu, C.W.; Ho, J.S. Metasurfaces for bioelectronics and healthcare. Nat. Electron. 2021, 4, 382–391.
- 12. Shabanzadeh, P.; Senu, N.; Shameli, K.; Tabar, M.M. Artificial Intelligence in Numerical Modeling of Silver Nanoparticles Prepared in Montmorillonite Interlayer Space. Compos. Nanoparticles 2013, 305713.
- Pellegrino, F.; Isopesc, R.; Pelluti, L.; Sordello, F.; Rossi, A.M.; Ortel, E.; Martra, G.; Hodoroaba, V.H.; Maurino, V. Machine learning approach for elucidating and predicting the role of synthesis parameters on the shape and size of TiO2 nanoparticles. Sci. Rep. 2020, 10, 18910.
- Asadi, H.; Rostamizadeh, K.; Salari, D.; Hamidi, M. Preparation of biodegradable nanoparticles of tri-block PLA-PEG-PLA copolymer and determination of factors controlling the particle size using artificial neural network. J. Microencapsul. 2011, 28, 406–416.
- Shalaby, K.S.; Soliman, M.E.; Casettari, L.; Bonacucina, G.; Cespi, M.; Palmieri, G.F.; Sammour, O.A.; El Shamy, A.A. Determination of factors controlling the particle size and entrapment efficiency of noscapine in PEG/PLA nanoparticles using artificial neural networks. Int. J. Nanomed. 2014, 23, 4953–4964.
- Szlęk, J.; Pacławski, A.; Lau, R.; Jachowicz, R.; Mendyk, A. Heuristic modeling of macromolecule release from PLGA microspheres. Int. J. Nanomed. 2013, 8, 4601–4611.
- 17. Cui, W.; Cao, Z.; Li, X.; Lu, L.; Ma, T.; Wang, Q. Experimental investigation and artificial intelligent estimation of thermal conductivity of nanofluids with different nanoparticles shapes. Powder Technol. 2021, 398, 117078.
- 18. Aminian, A. Predicting the effective thermal conductivity of nanofluids for intensification of heat transfer using artificial neural network. Powder Technol. 2016, 301, 288–309.
- 19. Ahmadloo, E.; Azizi, S. Prediction of thermal conductivity of various nanofluids using artificial neural network. Int. Commun. Heat Mass Transf. 2016, 74, 69–75.
- Furxhi, I.; Murphy, F.; Mullins, M.; Poland, C.A. Machine learning prediction of nanoparticle in vitro toxicity: A comparative study of classifiers and ensemble-classifiers using the Copeland Index. Toxicol. Lett. 2019, 312, 157–166.
- Mirzaei, M.; Furxhi, I.; Murphy, F.; Mullins, M. A Machine Learning Tool to Predict the Antibacterial Capacity of Nanoparticles. Nanomaterials 2021, 11, 1774.
- 22. Concu, R.; Kleandrova, V.V.; Speck-Planche, A.; Natália, N.; Cordeiro, D.S. Probing the toxicity of nanoparticles: A unified in silico machine learning model based on perturbation theory. Nanotoxicology 2017, 11, 891–906.
- 23. Furxh, I.; Murphy, F. Predicting In Vitro Neurotoxicity Induced by Nanoparticles Using Machine Learning. Int. J. Mol. Sci. 2020, 21, 5280.
- 24. Vinoth, A.; Datta, S. Design of the ultrahigh molecular weight polyethylene composites with multiple nanoparticles: An artificial intelligence approach. J. Compos. Mater. 2020, 54, 179–192.

- Orimoto, Y.; Watanabe, K.; Yamashita, K.; Uehara, M.; Nakamura, H.; Furuya, T.; Maeda, H. Application of Artificial Neural Networks to Rapid Data Analysis in Combinatorial Nanoparticle Syntheses. J. Phys. Chem. 2012, 116, 17885– 17896.
- 26. Montazeran, A.H.; Samandari, S.S.; Khandan, A. Artificial intelligence investigation of three silicates bioceramicsmagnetite bio-nanocomposite: Hyperthermia and biomedical applications. Nanomed. J. 2018, 5, 163–171.
- 27. Zaki, M.R.; Varshosaz, J.; Fathi, M. Preparation of agar nanospheres: Comparison of response surface and artificial neural network modeling by a genetic algorithm approach. Carbohydr. Polym. 2015, 122, 314–320.
- Dar, M.S.; Akram, K.B.; Sohail, A.; Arif, F.; Zabihi, F.; Yang, S.; Munir, S.; Zhu, M.; Abide, M.; Nauman, M. Heat induction in two-dimensional graphene–Fe3O4 nanohybrids for magnetic hyperthermia applications with artificial neural network modeling. RSC Adv. 2021, 11, 21702–21715.
- 29. Hedayatnasab, Z.; Saadatabadi, A.R.; Shirgahi, H.; Mozafari, M.R. Heat induction of iron oxide nanoparticles with rational artificial neural network design-based particle swarm optimization for magnetic cancer hyperthermia. Materials Res. Bull. 2023, 157, 112035.
- 30. Ban, Z.; Yuan, P.; Yu, F.; Hu, X. Machine learning predicts the functional composition of the protein corona and the cellular recognition of nanoparticles. Proc. Natl. Acad. Sci. USA 2020, 117, 10492–10499.
- Sohail, A.; Fatima, M.; Ellahi, R.; Akram, K.B. A videographic assessment of ferrofluid during magnetic drug targeting: An application of artificial intelligence in nanomedicine. J. Mol. Liq. 2019, 285, 47–57.
- 32. Chen, X.; Lv, H. Intelligent control of nanoparticle synthesis on microfluidic chips with machine learning. NPG Asia Mater. 2022, 14, 69.
- Baghaei, B.; Saeb, M.R.; Jafari, S.H.; Khonakdar, H.A.; Rezaee, B.; Goodarzi, V.; Mohammadi, Y. Modeling and closed-loop control of particle size and initial burst of PLGA biodegradable nanoparticles for targeted drug delivery. J. Appl. Polym. Sci. 2017, 134, 45145.
- 34. Ma, J.M.; Gup, S.N.; Su, R.J.; Yuo, W.N. The Method for Magnetic Hyperthermia Based on Particle Swarm Optimization Algorithm with Levy Flight. Int. J. Pattern Recognit. Artif. Intell. 2016, 30, 1659025.
- 35. Tao, H.; Wu, T.; Aldeghi, M.; Wu, T.C.; Aspuru-Guzik, A.; Kumacheva, E. Nanoparticle synthesis assisted by machine learning. Nat. Rev. Mater. 2021, 6, 701–716.
- Aldhaeebi, M.; Alzabidi, M.; Elshafiey, I. Genetic Algorithm Optimization of SAR Distribution in Hyperthermia Treatment of Human Head. In Proceedings of the 2013 1st International Conference on Artificial Intelligence, Modelling and Simulation, Kota Kinabalu, Malaysia, 3–5 December 2013; pp. 92–97.
- Boztepe, C.; Yüceer, M.; Künkül, A.; Şölener, M.; Kabasakal, O.S. Prediction of the deswelling behaviors of pH- and temperature-responsive poly(NIPAAm-co-AAc) IPN hydrogel by artificial intelligence techniques. Res. Chem. Intermed. 2020, 46, 409–428.
- Boztepe, C.; Daskin, M.; Erdogsn, A. Synthesis of magnetic responsive poly(NIPAAm-co-VSA)/Fe3O4 IPN ferrogels and modeling their deswelling and heating behaviors under AMF by using artificial neural networks. React. Funct. Polym. 2022, 173, 105219.
- Ruan, W.; Hu, J.; Qi, J.; Hou, Y.; Cao, R.; Wei, X. Removal of Crystal Violet by Using Reduced-Graphene-Oxide-Supported Bimetallic Fe/Ni Nanoparticles (rGO/Fe/Ni): Application of Artificial Intelligence Modeling for the Optimization Process. Materials 2018, 11, 865.
- 40. Mahmoudi, K.; Bouras, A.; Bozec, D.; Ivkov, R.; Hadjipanayis, C. Magnetic hyperthermia therapy for the treatment of glioblastoma: A review of the therapy's history, efficacy and application in humans. Int. J. Hyperth. 2018, 34, 1316–1328.
- 41. Alam, G.; Ihsanullah, I.; Naushad, M.; Sillanpää, M. Applications of artificial intelligence in water treatment for optimization and automation of adsorption processes: Recent advances and prospects. Chem. Eng. J. 2022, 427, 130011.
- Mahmoud, A.S.; Ismail, A.; Mostafa, M.K.; Mahmoud, M.S.; Ali, W.; Shawky, A.M. Isotherm and kinetic studies for heptachlor removal from aqueous solution using Fe/Cu nanoparticles, artificial intelligence, and regression analysis. Sep. Sci. Technol. 2020, 55, 684–696.