

Wire and Arc Additive Manufactured Materials Corrosion Behaviour

Subjects: **Materials Science, Characterization & Testing**

Contributor: Davi Alves Marques , João Pedro Oliveira , Ana Catarina Baptista

Wire and Arc Additive Manufacturing (WAAM) is a deposition rate process for the creation and/or repair of large structural metallic components. The non-equilibrium heating and cooling conditions associated with WAAM lead to the development of heterogeneous microstructures. Although there is a large body of work focusing on the microstructure and mechanical properties of WAAM-fabricated components, assessment of the corrosion behaviour of alloys fabricated by WAAM is still in its infancy. Here, the body of knowledge associated with the corrosion behaviour of different WAAM-fabricated engineering alloys is presented and discussed. Future perspectives and potential research topics are also presented. This is the first work focusing on the corrosion of wire and arc additive manufactured materials.

wire and arc additive manufacturing

corrosion

microstructure

1. Introduction

Metallic materials are part of day-to-day life as they are key in the improvement of living conditions around the world. Conventional manufacturing processes for metallic materials allow to create multiple components, but often there are design limitations imposed by the manufacturing process itself. The advent of additive manufacturing (AM) allowed for complex-shaped structures to be easily fabricated in a layer-by-layer fashion and for the construction of complex geometries with satisfactory accuracy [1]. Although AM processes can be applied to any class of engineering materials [2][3][4][5], metal additive manufacturing is currently expanding given the potential applicability prospects associated with the combination of high strength metallic alloys with improved design flexibility enabled by AM processes. Although most AM processes for metallic materials are focused on the fabrication of small- to medium-sized components, there is a significant and urgent need for processes capable of fabricating larger complex-shaped structures in a timely fashion, while decreasing material waste. With regards to this, within the field of metal additive manufacturing, wire and arc additive manufacturing (WAAM) has a large deposition rate and is known for its low implementation costs and easy maintenance [6]. WAAM is already being used in the industry field for multiple applications, ranging from the repair of obsolete metallic components to the fabrication of new parts, as well as in the oil and gas, energy and aerospace industries [7][8][9][10]. In WAAM, the large heat source can be based on gas metal arc welding (GMAW) [11][12][13][14][15], gas tungsten arc welding (GTAW) [16][17][18][19], or plasma arc welding (PAW) [20][21][22][23][24]. The selection of each of these types of heat sources will influence the microstructure development, process stability, deposition rate, implementation costs and industrial uptake.

Currently, WAAM of different engineering alloys is primarily focused on determining the evolution of microstructure and the resulting mechanical properties [25][26][27][28][29][30][31]. Determining the relationships between microstructure and mechanical properties is currently fundamental since the application prospects of WAAM-fabricated components is for them to be used in structural applications. Hence, it is necessary that how the weld thermal cycle impacts the microstructure along the deposited material is understood so that one can develop new processing conditions or post-process heat treatments, targeting an improvement in the resulting mechanical properties. Despite the importance of linking processing conditions to microstructure and mechanical response, there are other key material features that must be comprehensively assessed to further expand the use of WAAM in key industry sectors where the materials are in contact with aggressive environments, such as in the oil and gas and nuclear industries [28][32]. A key topic that has been lacking attention, with scarce literature to be found on it, is the assessment of the corrosion behaviour of WAAM-fabricated components. There is a fundamental need to address the corrosion behaviour of components built by WAAM as the type of applications associated with this technology, namely large metallic components for critical application in the oil and gas, maritime and aerospace industries, often require that the components be used in demanding, aggressive environments. More importantly, it is well-known that the thermal conditions within a part fabricated by WAAM are dependent on the location of the part. Since there is often a correlation between the thermal cycle experienced by the material and the resulting microstructure (coming from the solidification structure or due to solid state transformations imposed by repeated subsequent depositions), the thermophysical properties, including corrosion behaviour of the fabricated component, can be spatially dependent, which can aggravate the deterioration of the structural integrity during the operation of the component.

2. Corrosion Behaviour in WAAM Materials

Corrosion is defined as a spontaneous reaction that results in material degradation as a result of its interaction with the environment [33]. The material's susceptibility to corrosion is a parameter that depends on different factors, including the corrosive environment, the chemical composition of the material, heat treatment, microstructure, surface finish, production and processing methods [34][35].

When addressing wire arc additive manufactured (WAAMed) materials, some of the process parameters, such as travel speed, wire feed rate, current, deposition path and protection gas flow rate [36][37], significantly affect the resulting microstructure and surface finish and, thus, will have an observable impact on the corrosion behaviour, as previously mentioned. This multiple-parameter effect leads to difficulty in determining their isolated influence. Despite this issue, some authors suggested that a synchronous effect can be condensed and analysed in terms of heat input [38][39].

Compared to conventionally produced methods, AM components present complex microstructures because of the different time-dependent temperature profiles and process parameters [40][41][42][43][44][45][46][47][48]. These microstructures are formed by a combination of rapid solidification rates and high thermal gradients [49]. These processes are known to produce complex, non-equilibrium microstructures with poor surface finish, resulting in the necessity of post-processing treatments. Dinovitzer et al. [38] reported an increase in surface roughness with higher

travel speeds and presented an inverse behaviour relative to the current applied during the WAAM process, leading to an increase in corrosion susceptibility [50][51].

Another important factor inherent to this process is the segregation of alloying elements, which is a result of different concentrations and solidification times of the dendritic and interdendritic regions, leading to chemical heterogeneities creating large cathodic regions enabling localised corrosion [52][53].

Despite the increasing attention WAAMed materials are attracting, there is still a lack of information in the literature concerning its corrosion behaviour [54][55][56], which is of fundamental importance prior to a massive industrial application of these materials into industrially relevant settings. During 2018 to 2022, Laser Power-Bed Fusion (L-PBF) corrosion presented twice as much research works [57]. Despite the increase in the number of papers, these studies focus on specific topics related to a particular problem and/or application rather than seek a general comprehension of the corrosion susceptibility [8][25][28][58][59][60][61][62][63][64][65][66].

3. Outlook

Table 1 presents a summary of the effects of the WAAM process on the corrosion susceptibility of the studied alloys. The most common parameter that affected the resistance was the creation of micro-galvanic cells due to solute segregation, emphasising the importance of homogeneous chemical composition within the fabricated material.

Table 1. Summary of the effects of WAAM Process Variables on the Corrosion Susceptibility.

Variables	Effect on Corrosion Susceptibility	WAAM Systems Affected
Solute Segregation	Micro-galvanic cells are created, resulting in localised corrosion [67][68] and different phases along the deposited layer, resulting in distinct corrosion potentials [69].	316LN ER70S-6
		10CrNi3MoV
Refined Grain Size	This variable is still controversial in the literature. Some authors relate coarse and non-equiaxed grains with hindered corrosion behaviour [69][70], while others observe the opposite [68].	10CrNi3MoV 825 alloy
		TI-6Al-4V

Variables	Effect on Corrosion Susceptibility	WAAM Systems Affected
Heat Input	Lower corrosion potentials were observed when applying high heat input [67][69].	10CrNi3MoV 316LN
Current Source	WAAMed materials fabricated using a pulsed current source presented more positive corrosion potentials when compared to constant current sources [71].	SUS 304

1. **Nguyen, T.D., Kashiwai, A., Minodzono, G., Nguyen, K.T.Q., Hui, D.** Additive Manufacturing (3D Printing): A Review of Materials, Methods, Applications and Challenges. *Compos. B Eng.* 2018, 143, 172–196.
2. Krawiec, P.; Czarnecka-komorowska, D.; Warguła, Ł.; Wojciechowski, S. Geometric Specification of Non-circular Pulleys Made with Various Additive Manufacturing Techniques. *Materials* 2021, 14, 1682.
3. Chandrashekharappa, M.P.G.; Chate, G.R.; Parashivamurthy, V.; Kumar, B.S.; Bandukwala, M.A.N.; Kaisar, A.; Giasin, K.; Pimenov, D.Y.; Wojciechowski, S. Analysis and Optimization of Dimensional Accuracy and Porosity of High Impact Polystyrene Material Printed by FDM Process: PSO, JAYA, Rao, and Bald Eagle Search Algorithms. *Materials* 2021, 14, 7479.
4. Das, S.; Vora, J.J.; Patel, V.; Li, W.; Andersson, J.; Pimenov, D.Y.; Giasin, K.; Wojciechowski, S. Experimental Investigation on Welding of 2.25 Cr-1.0 Mo Steel with Regulated Metal Deposition and GMAW Technique Incorporating Metal-Cored Wires. *J. Mater. Res. Technol.* 2021, 15, 1007–1016.
5. Sheshadri, R.; Nagaraj, M.; Lakshmikanthan, A.; Chandrashekharappa, M.P.G.; Pimenov, D.Y.; Giasin, K.; Prasad, R.V.S.; Wojciechowski, S. Experimental Investigation of Selective Laser Melting Parameters for Higher Surface Quality and Microhardness Properties: Taguchi and Super Ranking Concept Approaches. *J. Mater. Res. Technol.* 2021, 14, 2586–2600.
6. Singh, S.R.; Khanna, P. Wire Arc Additive Manufacturing (WAAM): A New Process to Shape Engineering Materials. *Mater Today Proc.* 2021, 44, 118–128.
7. Cunningham, C.R.; Wikshåland, S.; Xu, F.; Kemakolam, N.; Shokrani, A.; Dhokia, V.; Newman, S.T. Cost Modelling and Sensitivity Analysis of Wire and Arc Additive Manufacturing. *Procedia Manuf.* 2017, 11, 650–657.
8. Le, V.T.; Mai, D.S.; Doan, T.K.; Paris, H. Wire and Arc Additive Manufacturing of 308L Stainless Steel Components: Optimization of Processing Parameters and Material Properties. *Eng. Sci. Technol. Int. J.* 2021, 24, 1015–1026.

9. Hönnige, J.R.; Colegrove, P.A.; Ganguly, S.; Eimer, E.; Kabra, S.; Williams, S. Control of Residual Stress and Distortion in Aluminium Wire + Arc Additive Manufacture with Rolling. *Addit. Manuf.* 2018, 22, 775–783.
10. Li, Y.; Han, Q.; Horváth, I.; Zhang, G. Repairing Surface Defects of Metal Parts by Groove Machining and Wire + Arc Based Filling. *J. Mater. Process. Technol.* 2019, 274, 116268.
11. Xiong, J.; Zhang, G. Online Measurement of Bead Geometry in GMAW-Based Additive Manufacturing Using Passive Vision. *Meas. Sci. Technol.* 2013, 24, 115103.
12. Hu, Z.; Qin, X.; Shao, T.; Liu, H. Understanding and Overcoming of Abnormity at Start and End of the Weld Bead in Additive Manufacturing with GMAW. *Int. J. Adv. Manuf. Technol.* 2018, 95, 2357–2368.
13. Shi, J.; Li, F.; Chen, S.; Zhao, Y.; Tian, H. Effect of In-Process Active Cooling on Forming Quality and Efficiency of Tandem GMAW-Based Additive Manufacturing. *Int. J. Adv. Manuf. Technol.* 2019, 101, 1349–1356.
14. Yang, D.; Wang, G.; Zhang, G. Thermal Analysis for Single-Pass Multi-Layer GMAW Based Additive Manufacturing Using Infrared Thermography. *J. Mater. Process. Technol.* 2017, 244, 215–224.
15. Nilsiam, Y.; Sanders, P.; Pearce, J.M. Slicer and Process Improvements for Open-Source GMAW-Based Metal 3-D Printing. *Addit. Manuf.* 2017, 18, 110–120.
16. Yilmaz, O.; Ugla, A.A. Microstructure Characterization of SS308LSi Components Manufactured by GTAW-Based Additive Manufacturing: Shaped Metal Deposition Using Pulsed Current Arc. *Int. J. Adv. Manuf. Technol.* 2017, 89, 13–25.
17. Geng, H.; Li, J.; Xiong, J.; Lin, X.; Zhang, F. Optimization of Wire Feed for GTAW Based Additive Manufacturing. *J. Mater. Process. Technol.* 2017, 243, 40–47.
18. Ma, Y.; Cuiuri, D.; Hoye, N.; Li, H.; Pan, Z. The Effect of Location on the Microstructure and Mechanical Properties of Titanium Aluminides Produced by Additive Layer Manufacturing Using In-Situ Alloying and Gas Tungsten Arc Welding. *Mater. Sci. Eng. A* 2015, 631, 230–240.
19. Wang, J.F.; Sun, Q.J.; Wang, H.; Liu, J.P.; Feng, J.C. Effect of Location on Microstructure and Mechanical Properties of Additive Layer Manufactured Inconel 625 Using Gas Tungsten Arc Welding. *Mater. Sci. Eng. A* 2016, 676, 395–405.
20. Lin, J.; Lv, Y.; Liu, Y.; Sun, Z.; Wang, K.; Li, Z.; Wu, Y.; Xu, B. Microstructural Evolution and Mechanical Property of Ti-6Al-4V Wall Deposited by Continuous Plasma Arc Additive Manufacturing without Post Heat Treatment. *J. Mech. Behav. Biomed. Mater.* 2017, 69, 19–29.
21. Liu, W.; Jia, C.; Guo, M.; Gao, J.; Wu, C. Compulsively Constricted WAAM with Arc Plasma and Droplets Ejected from a Narrow Space. *Addit. Manuf.* 2019, 27, 109–117.

22. Jhavar, S.; Jain, N.K.; Paul, C.P. Development of Micro-Plasma Transferred Arc (μ -PTA) Wire Deposition Process for Additive Layer Manufacturing Applications. *J. Mater. Process. Technol.* 2014, 214, 1102–1110.

23. Jhavar, S.; Paul, C.P.; Jain, N.K. Micro-Plasma Transferred Arc Additive Manufacturing for Die and Mold Surface Remanufacturing. *JOM* 2016, 68, 1801–1809.

24. Alberti, E.A.; Bueno, B.M.P.; D’Oliveira, A.S.C.M. Additive Manufacturing Using Plasma Transferred Arc. *Int. J. Adv. Manuf. Technol.* 2016, 83, 1861–1871.

25. Ayarkwa, K.F.; Williams, S.W.; Ding, J. Assessing the Effect of TIG Alternating Current Time Cycle on Aluminium Wire + Arc Additive Manufacture. *Addit. Manuf.* 2017, 18, 186–193.

26. Yin, B.; Ma, H.; Wang, J.; Fang, K.; Zhao, H.; Liu, Y. Effect of CaF₂ Addition on Macro/Microstructures and Mechanical Properties of Wire and Arc Additive Manufactured Ti-6Al-4V Components. *Mater. Lett.* 2017, 190, 64–66.

27. Oyama, K.; Diplas, S.; M’hamdi, M.; Gunnæs, A.E.; Azar, A.S. Heat Source Management in Wire-Arc Additive Manufacturing Process for Al-Mg and Al-Si Alloys. *Addit. Manuf.* 2019, 26, 180–192.

28. Wang, L.; Suo, Y.; Liang, Z.; Wang, D.; Wang, Q. Effect of Titanium Powder on Microstructure and Mechanical Properties of Wire + arc Additively Manufactured Al-Mg Alloy. *Mater. Lett.* 2019, 241, 231–234.

29. Ding, D.; Pan, Z.; Cuiuri, D.; Li, H. A Practical Path Planning Methodology for Wire and Arc Additive Manufacturing of Thin-Walled Structures. *Robot. Comput. Integr. Manuf.* 2015, 34, 8–19.

30. Li, F.; Chen, S.; Shi, J.; Zhao, Y.; Tian, H. Thermoelectric Cooling-Aided Bead Geometry Regulation in Wire and Arc-Based Additive Manufacturing of Thin-Walled Structures. *Appl. Sci.* 2018, 8, 207.

31. Gu, J.; Wang, X.; Bai, J.; Ding, J.; Williams, S.; Zhai, Y.; Liu, K. Deformation Microstructures and Strengthening Mechanisms for the Wire+arc Additively Manufactured Al-Mg4.5Mn Alloy with Inter-Layer Rolling. *Mater. Sci. Eng. A* 2018, 712, 292–301.

32. Dirisu, P.; Ganguly, S.; Mehmanparast, A.; Martina, F.; Williams, S. Analysis of Fracture Toughness Properties of Wire + Arc Additive Manufactured High Strength Low Alloy Structural Steel Components. *Mater. Sci. Eng. A* 2019, 765, 138285.

33. Dowson, D.; Neville, A. Tribology and Corrosion in Hip Joint Replacements: Materials and Engineering. In *Joint Replacement Technology*; Woodhead Publishing: Cambridge, UK, 2014; pp. 401–442.

34. Dai, C.; Fu, Y.; Guo, J.; Du, C. Effects of Substrate Temperature and Deposition Time on the Morphology and Corrosion Resistance of FeCoCrNiMo0.3 High-Entropy Alloy Coating Fabricated by Magnetron Sputtering. *Int. J. Miner. Metall. Mater.* 2020, 27, 1388–1397.

35. Tayyab, K.B.; Farooq, A.; Alvi, A.A.; Nadeem, A.B.; Deen, K.M. Corrosion Behavior of Cold-Rolled and Post Heat-Treated 316L Stainless Steel in 0.9wt% NaCl Solution. *Int. J. Miner. Metall. Mater.* 2021, 28, 440–449.

36. Aldalur, E.; Veiga, F.; Suárez, A.; Bilbao, J.; Lamikiz, A. High Deposition Wire Arc Additive Manufacturing of Mild Steel: Strategies and Heat Input Effect on Microstructure and Mechanical Properties. *J. Manuf. Process.* 2020, 58, 615–626.

37. Su, C.; Chen, X.; Gao, C.; Wang, Y. Effect of Heat Input on Microstructure and Mechanical Properties of Al-Mg Alloys Fabricated by WAAM. *Appl. Surf. Sci.* 2019, 486, 431–440.

38. Dinovitzer, M.; Chen, X.; Laliberte, J.; Huang, X.; Frei, H. Effect of Wire and Arc Additive Manufacturing (WAAM) Process Parameters on Bead Geometry and Microstructure. *Addit. Manuf.* 2019, 26, 138–146.

39. Klein, T.; Schnall, M. Control of Macro-/Microstructure and Mechanical Properties of a Wire-Arc Additive Manufactured Aluminum Alloy. *Int. J. Adv. Manuf. Technol.* 2020, 108, 235–244.

40. MacDonald, E.; Wicker, R. Multiprocess 3D Printing for Increasing Component Functionality. *Science* (1979) 2016, 353, aaf2093.

41. Selvi, S.; Vishvaksenan, A.; Rajasekar, E. Cold Metal Transfer (CMT) Technology—An Overview. *Def. Technol.* 2018, 14, 28–44.

42. Chen, S.; Tong, Y.; Liaw, P. Additive Manufacturing of High-Entropy Alloys: A Review. *Entropy* 2018, 20, 937.

43. Everton, S.K.; Hirsch, M.; Stravroulakis, P.; Leach, R.K.; Clare, A.T. Review of In-Situ Process Monitoring and in-Situ Metrology for Metal Additive Manufacturing. *Mater. Des.* 2016, 95, 431–445.

44. Beese, A.M.; Carroll, B.E. Review of Mechanical Properties of Ti-6Al-4V Made by Laser-Based Additive Manufacturing Using Powder Feedstock. *JOM* 2016, 68, 724–734.

45. Khorasani, A.; Gibson, I.; Veetil, J.K.; Ghasemi, A.H. A Review of Technological Improvements in Laser-Based Powder Bed Fusion of Metal Printers. *Int. J. Adv. Manuf. Technol.* 2020, 108, 191–209.

46. Frazier, W.E. Metal Additive Manufacturing: A Review. *J. Mater. Eng. Perform.* 2014, 23, 1917–1928.

47. Huang, S.H.; Liu, P.; Mokasdar, A.; Hou, L. Additive Manufacturing and Its Societal Impact: A Literature Review. *Int. J. Adv. Manuf. Technol.* 2013, 67, 1191–1203.

48. Bandyopadhyay, A.; Heer, B. Additive Manufacturing of Multi-Material Structures. *Mater. Sci. Eng. R Rep.* 2018, 129, 1–16.

49. Haghdadi, N.; Laleh, M.; Moyle, M.; Primig, S. Additive Manufacturing of Steels: A Review of Achievements and Challenges. *J. Mater. Sci.* 2021, 56, 64–107.

50. Xu, F.; Luo, L.; Xiong, L.; Liu, Y. Microstructure and Corrosion Behavior of ALD Al₂O₃ Film on AZ31 Magnesium Alloy with Different Surface Roughness. *J. Magnes. Alloys* 2020, 8, 480–492.

51. Sasaki, K.; Burstein, G.T. The Generation of Surface Roughness during Slurry Erosion-Corrosion and Its Effect on the Pitting Potential. *Corros. Sci.* 1996, 38, 2111–2120.

52. Zhang, X.; Lv, Y.; Tan, S.; Dong, Z.; Zhou, X. Microstructure and Corrosion Behaviour of Wire Arc Additive Manufactured AA2024 Alloy Thin Wall Structure. *Corros. Sci.* 2021, 186, 109453.

53. Bajaj, P.; Hariharan, A.; Kini, A.; Kürnsteiner, P.; Raabe, D.; Jägle, E.A. Steels in Additive Manufacturing: A Review of Their Microstructure and Properties. *Mater. Sci. Eng. A* 2020, 772, 138633.

54. Sander, G.; Tan, J.; Balan, P.; Gharbi, O.; Feenstra, D.R.; Singer, L.; Thomas, S.; Kelly, R.G.; Scully, J.R.; Birbilis, N. Corrosion of Additively Manufactured Alloys: A Review. *Corrosion* 2018, 74, 1318–1350.

55. Raut, L.P.; Taiwade, R. v Wire Arc Additive Manufacturing: A Comprehensive Review and Research Directions. *J. Mater. Eng. Perform.* 2021, 30, 4768–4791.

56. Ko, G.; Kim, W.; Kwon, K.; Lee, T.-K. The Corrosion of Stainless Steel Made by Additive Manufacturing: A Review. *Metals* 2021, 11, 516.

57. Available online: <https://Www.Sciencedirect.Com> (accessed on 24 January 2023).

58. Ahsan, M.R.U.; Seo, G.-J.; Fan, X.; Liaw, P.K.; Motaman, S.; Haase, C.; Kim, D.B. Effects of Process Parameters on Bead Shape, Microstructure, and Mechanical Properties in Wire + Arc Additive Manufacturing of Al0.1CoCrFeNi High-Entropy Alloy. *J. Manuf. Process.* 2021, 68, 1314–1327.

59. Wu, B.; Pan, Z.; Ding, D.; Cuiuri, D.; Li, H. Effects of Heat Accumulation on Microstructure and Mechanical Properties of Ti6Al4V Alloy Deposited by Wire Arc Additive Manufacturing. *Addit. Manuf.* 2018, 23, 151–160.

60. Qi, Z.; Cong, B.; Qi, B.; Zhao, G.; Ding, J. Properties of Wire + arc Additively Manufactured 2024 Aluminum Alloy with Different Solution Treatment Temperature. *Mater. Lett.* 2018, 230, 275–278.

61. Wu, B.; Pan, Z.; Ding, D.; Cuiuri, D.; Li, H.; Fei, Z. The Effects of Forced Interpass Cooling on the Material Properties of Wire Arc Additively Manufactured Ti6Al4V Alloy. *J. Mater. Process. Technol.* 2018, 258, 97–105.

62. Guo, J.; Zhou, Y.; Liu, C.; Wu, Q.; Chen, X.; Lu, J. Wire Arc Additive Manufacturing of AZ31 Magnesium Alloy: Grain Refinement by Adjusting Pulse Frequency. *Materials* 2016, 9, 823.

63. Donoghue, J.; Antonysamy, A.A.; Martina, F.; Colegrove, P.A.; Williams, S.W.; Prangnell, P.B. The Effectiveness of Combining Rolling Deformation with Wire–Arc Additive Manufacture on β -Grain Refinement and Texture Modification in Ti–6Al–4V. *Mater. Charact.* 2016, 114, 103–114.

64. Osintsev, K.; Konovalov, S.; Zaguliaev, D.; Ivanov, Y.; Gromov, V.; Panchenko, I. Investigation of Co-Cr-Fe-Mn-Ni Non-Equiatomic High-Entropy Alloy Fabricated by Wire Arc Additive Manufacturing. *Metals* 2022, 12, 197.

65. Wu, B.; Pan, Z.; Ding, D.; Cuiuri, D.; Li, H.; Xu, J.; Norrish, J. A Review of the Wire Arc Additive Manufacturing of Metals: Properties, Defects and Quality Improvement. *J. Manuf. Process.* 2018, 35, 127–139.

66. Chen, W.; Chen, Y.; Zhang, T.; Wen, T.; Yin, Z.; Feng, X. Effect of Ultrasonic Vibration and Interpass Temperature on Microstructure and Mechanical Properties of Cu-8Al-2Ni-2Fe-2Mn Alloy Fabricated by Wire Arc Additive Manufacturing. *Metals* 2020, 10, 215.

67. Wen, D.; Long, P.; Li, J.; Huang, L.; Zheng, Z. Effects of Linear Heat Input on Microstructure and Corrosion Behavior of an Austenitic Stainless Steel Processed by Wire Arc Additive Manufacturing. *Vacuum* 2020, 173, 109131.

68. Zhang, L.N.; Ojo, O.A. Corrosion Behavior of Wire Arc Additive Manufactured Inconel 718 Superalloy. *J. Alloys Compd.* 2020, 829, 154455.

69. Tian, G.; Wang, X.; Wang, W.; Chang, Q.; Zhao, Y.; Han, G.; Ren, Z.; Zhu, S. Microstructure, Mechanical Properties, and Galvanic Corrosion of 10CrNi3MoV Fabricated by Wire Arc Additive Manufacturing. *Metals* 2021, 11, 1235.

70. Yang, J.; Yang, H.; Yu, H.; Wang, Z.; Zeng, X. Corrosion Behavior of Additive Manufactured Ti-6Al-4V Alloy in NaCl Solution. *Metall. Mater. Trans. A* 2017, 48, 3583–3593.

71. Hao, Z.; Ao, S.; Cai, Y.; Zhang, W.; Luo, Z. Formation of SUS304/Aluminum Alloys Using Wire and Arc Additive Manufacturing. *Metals* 2018, 8, 595.

Retrieved from <https://encyclopedia.pub/entry/history/show/97466>