

# Electrospinning for Neural Applications

Subjects: Engineering, Biomedical

Contributor: Ryan J. Gilbert

Electrospinning is a fabrication technique used to produce nano- or micro- diameter fibers to generate biocompatible, biodegradable scaffolds for tissue engineering applications. Electrospun fiber scaffolds are advantageous for neural regeneration because they mimic the structure of the nervous system extracellular matrix and provide contact guidance for regenerating axons. Glia are non-neuronal regulatory cells that maintain homeostasis in the healthy nervous system and regulate regeneration in the injured nervous system. Electrospun fiber scaffolds offer a wide range of characteristics, such as fiber alignment, diameter, surface nanotopography, and surface chemistry that can be engineered to achieve a desired glial cell response to injury. Further, electrospun fibers can be loaded with drugs, nucleic acids, or proteins to provide local, sustained release of such therapeutics to alter glial cell phenotype to better support regeneration.

Keywords: Electrospinning ; Neural Regeneration

---

## 1. Introduction

Electrospinning is a versatile technique used to generate biocompatible, biodegradable scaffolds for tissue engineering applications. Electrospun polymer fibers are frequently used in regenerative medicine, drug delivery, and in vitro modeling for a variety of biomedical applications, including wound healing, bone regeneration, and nervous system regeneration <sup>[1][2][3][4][5][6]</sup>.

## 2. Electrospinning

Electrospinning is a fabrication technique used to produce nanometer or micrometer diameter fibers using an electric voltage drop to draw a thin polymer jet from a metal needle and deposit fibers onto a grounded collector <sup>[7][8]</sup>. The solvent used to dissolve the polymer evaporates as the jet rapidly elongates and whips through the air <sup>[9]</sup>. The whipping results in the random collection of thin polymer fibers on the collector, usually a metal plate. However, the orientation of the fibers can be controlled by collecting the fibers on a rotating mandrel <sup>[10][11]</sup> (Figure 1A), an oscillating collection plate <sup>[12]</sup>, or between two parallel plates <sup>[13][14]</sup>. Studies using electrospun fibers as scaffolds for peripheral nerve or spinal cord regeneration have shown that an aligned fiber arrangement is critical for directionally guiding neuronal regeneration through the injury site, as the aligned fibers mimic the aligned topography of the uninjured anatomy in peripheral nerves and the white matter tracts found in the spinal cord <sup>[15][16][17][18][19][20][21][22]</sup>.

**Figure 1.** Electrospinning apparatus configurations and examples of electrospun fiber features that affect glial cell behavior. (A) Electrospinning apparatus configuration for generating randomly oriented fibers on a flat plate (left) and aligned fibers on a rotating mandrel (right). Electrospinning apparatus parameters and the materials used for electrospinning can be tuned to alter fiber (B) nanotopography, (C) conductivity, (D) functionalization, or (E) drug-loading to engineer a desired cell response.

The process of electrospinning is versatile in that several parameters can be adjusted to produce fibers with desired properties. Fiber diameter can range from tens of nanometers to tens of micrometers and is modified by altering the concentration of the polymer solution, the dielectric constant and vapor pressure of the solvent, the polymer solution flow rate, and the distance between the needle tip and the collector <sup>[17][23]</sup>. The nanotopography on the surface of each

individual fiber can also vary from smooth to pits, divots, pores, or grooves by incorporating a nonsolvent into the electrospinning solution or varying the humidity of the electrospinning environment [24][25][26] (Figure 1B). Electrospun fiber diameter, alignment, density, and surface nanotopography have all been shown to affect neuronal and glial behavior [24][27][28][29]. Additionally, the unique properties of various materials used to generate electrospun fibers, such as biocompatibility, degradation rate, and conductivity (Figure 1C), can affect cell adhesion, migration, and phenotype [30][31][32]. Fibers can also be further functionalized by incorporating drugs or surface coatings to produce a desirable effect for a given application [1][6][23][33] (Figure 1D,E)

### 3. Conclusions

Electrospun fiber scaffolds mimic the native ECM in the nervous system and provide contact guidance for regenerating neurons. The major glia in the PNS and CNS are affected by several electrospun fiber characteristics both in vitro and in vivo. The complex pathophysiology of nervous system injury requires therapies that target multiple aspects of the repair and regeneration process for various durations. Electrospun fiber scaffolds offer a wide range of design parameters that can be tailored to achieve this; fiber diameter, alignment, density, biocompatibility, surface nanotopography, and surface chemistry can be tuned to elicit a desired cell response. Further, electrospun fibers can be loaded with drugs, nucleic acids, and growth factors to provide the local and sustained release of therapeutics to alter the glial cell phenotype and create a regenerative environment.

---

### References

1. Pertici, V.; Martrou, G.; Gignes, D.; Trimaille, T. Synthetic Polymer-Based Electrospun Fibers: Biofunctionalization Strategies and Recent Advances in Tissue Engineering, Drug Delivery and Diagnostics. *Curr. Med. Chem.* 2018, 25, 2385–2400.
2. Lyu, S.; Huang, C.; Yang, H.; Zhang, X. Electrospun Fibers as a Scaffolding Platform for Bone Tissue Repair. *J. Orthop. Res. Off. Publ. Orthop. Res. Soc.* 2013, 31, 1382–1389.
3. Memic, A.; Abudula, T.; Mohammed, H.S.; Joshi Navare, K.; Colombani, T.; Bencherif, S.A. Latest Progress in Electrospun Nanofibers for Wound Healing Applications. *ACS Appl. Bio Mater.* 2019, 2, 952–969.
4. Liu, M.; Zhang, Y.; Sun, S.; Khan, A.R.; Ji, J.; Yang, M.; Zhai, G. Recent Advances in Electrospun for Drug Delivery Purpose. *J. Drug Target.* 2019, 27, 270–282.
5. Seif, S.; Planz, V.; Windbergs, M. Delivery of Therapeutic Proteins Using Electrospun Fibers—Recent Developments and Current Challenges. *Arch. Pharm. (Weinheim)* 2017, 350, 1700077.
6. Ye, K.; Kuang, H.; You, Z.; Morsi, Y.; Mo, X. Electrospun Nanofibers for Tissue Engineering with Drug Loading and Release. *Pharmaceutics* 2019, 11, 182.
7. Reneker, D.H.; Yarin, A.L. Electrospinning Jets and Polymer Nanofibers. *Polymer* 2008, 49, 2387–2425.
8. Bhardwaj, N.; Kundu, S.C. Electrospinning: A Fascinating Fiber Fabrication Technique. *Biotechnol. Adv.* 2010, 28, 325–347.
9. Reneker, D.H.; Yarin, A.L.; Fong, H.; Koombhongse, S. Bending Instability of Electrically Charged Liquid Jets of Polymer Solutions in Electrospinning. *J. Appl. Phys.* 2000, 87, 4531–4547.
10. Gupta, D.; Venugopal, J.; Prabhakaran, M.P.; Dev, V.R.G.; Low, S.; Choon, A.T.; Ramakrishna, S. Aligned and Random Nanofibrous Substrate for the in Vitro Culture of Schwann Cells for Neural Tissue Engineering. *Acta Biomater.* 2009, 5, 2560–2569.
11. Wang, H.B.; Mullins, M.E.; Cregg, J.M.; Hurtado, A.; Oudega, M.; Trombley, M.T.; Gilbert, R.J. Creation of Highly Aligned Electrospun Poly-L-Lactic Acid Fibers for Nerve Regeneration Applications. *J. Neural Eng.* 2009, 6, 016001.
12. Fong, H.; Liu, W.; Wang, C.-S.; Vaia, R.A. Generation of Electrospun Fibers of Nylon 6 and Nylon 6-Montmorillonite Nanocomposite. *Polymer* 2002, 43, 775–780.
13. Kakade, M.V.; Givens, S.; Gardner, K.; Lee, K.H.; Chase, D.B.; Rabolt, J.F. Electric Field Induced Orientation of Polymer Chains in Macroscopically Aligned Electrospun Polymer Nanofibers. *J. Am. Chem. Soc.* 2007, 129, 2777–2782.
14. Jeffries, E.M.; Wang, Y. Incorporation of Parallel Electrospun Fibers for Improved Topographical Guidance in 3D Nerve Guides. *Biofabrication* 2013, 5, 035015.

15. Du, J.; Liu, J.; Yao, S.; Mao, H.; Peng, J.; Sun, X.; Cao, Z.; Yang, Y.; Xiao, B.; Wang, Y.; et al. Prompt Peripheral Nerve Regeneration Induced by a Hierarchically Aligned Fibrin Nanofiber Hydrogel. *Acta Biomater.* 2017, 55, 296–309.
16. Hurtado, A.; Cregg, J.M.; Wang, H.B.; Wendell, D.F.; Oudega, M.; Gilbert, R.J.; McDonald, J.W. Robust CNS Regeneration after Complete Spinal Cord Transection Using Aligned Poly-L-Lactic Acid Microfibers. *Biomaterials* 2011, 32, 6068–6079.
17. Schaub, N.J.; Johnson, C.D.; Cooper, B.; Gilbert, R.J. Electrospun Fibers for Spinal Cord Injury Research and Regeneration. *J. Neurotrauma* 2016, 33, 1405–1415.
18. D'Amato, A.R.; Ziemba, A.M.; Johnson, C.D.L.; Gilbert, R.J. 18-Advances in the use of electrospun fibers for the central nervous system. In *Electrofluidodynamic Technologies (EFDTs) for Biomaterials and Medical Devices*; Guarino, V., Ambrosio, L., Eds.; Woodhead Publishing Series in Biomaterials; Woodhead Publishing: Cambridge, UK, 2018; pp. 377–398. ISBN 978-0-08-101745-6.
19. Frost, H.K.; Andersson, T.; Johansson, S.; Englund-Johansson, U.; Ekström, P.; Dahlin, L.B.; Johansson, F. Electrospun Nerve Guide Conduits Have the Potential to Bridge Peripheral Nerve Injuries in Vivo. *Sci. Rep.* 2018, 8, 16716.
20. Xie, J.; MacEwan, M.R.; Schwartz, A.G.; Xia, Y. Electrospun Nanofibers for Neural Tissue Engineering. *Nanoscale* 2010, 2, 35–44.
21. Daly, W.; Yao, L.; Zeugolis, D.; Windebank, A.; Pandit, A. A Biomaterials Approach to Peripheral Nerve Regeneration: Bridging the Peripheral Nerve Gap and Enhancing Functional Recovery. *J. R. Soc. Interface* 2012, 9, 202–221.
22. Ziemba, A.M.; Gilbert, R.J. Biomaterials for Local, Controlled Drug Delivery to the Injured Spinal Cord. *Front. Pharmacol.* 2017, 8.
23. Haider, A.; Haider, S.; Kang, I.-K. A Comprehensive Review Summarizing the Effect of Electrospinning Parameters and Potential Applications of Nanofibers in Biomedical and Biotechnology. *Arab. J. Chem.* 2018, 11, 1165–1188.
24. Schaub, N.J.; Britton, T.; Rajachar, R.; Gilbert, R.J. Engineered Nanotopography on Electrospun PLLA Microfibers Modifies RAW 264.7 Cell Response. *ACS Appl. Mater. Interfaces* 2013, 5, 10173–10184.
25. Johnson, C.D.; D'Amato, A.R.; Puhl, D.L.; Wich, D.M.; Vesperman, A.; Gilbert, R.J. Electrospun Fiber Surface Nanotopography Influences Astrocyte-Mediated Neurite Outgrowth. *Biomed. Mater.* 2018, 13, 054101.
26. Omidinia-Anarkoli, A.; Rimal, R.; Chandorkar, Y.; Gehlen, D.B.; Rose, J.C.; Rahimi, K.; Haraszti, T.; De Laporte, L. Solvent-Induced Nanotopographies of Single Microfibers Regulate Cell Mechanotransduction. *ACS Appl. Mater. Interfaces* 2019, 11, 7671–7685.
27. Johnson, C.D.L.; Zuidema, J.M.; Kearns, K.R.; Maguire, A.B.; Desmond, G.P.; Thompson, D.M.; Gilbert, R.J. The Effect of Electrospun Fiber Diameter on Astrocyte-Mediated Neurite Guidance and Protection. *ACS Appl. Bio Mater.* 2019, 2, 104–117.
28. Wang, H.B.; Mullins, M.E.; Cregg, J.M.; McCarthy, C.W.; Gilbert, R.J. Varying the Diameter of Aligned Electrospun Fibers Alters Neurite Outgrowth and Schwann Cell Migration. *Acta Biomater.* 2010, 6, 2970–2978.
29. Zuidema, J.M.; Hyzinski-García, M.C.; Vlasselaer, K.V.; Zaccor, N.; Plopper, G.E.; Mongin, A.A.; Gilbert, R.J. Enhanced GLT-1 Mediated Glutamate Uptake and Migration of Primary Astrocytes Directed by Fibronectin-Coated Electrospun Poly-L-Lactic Acid Fibers. *Biomaterials* 2014, 35, 1439–1449.
30. Mu, Y.; Wu, F.; Lu, Y.; Wei, L.; Yuan, W. Progress of Electrospun Fibers as Nerve Conduits for Neural Tissue Repair. *Nanomedicine* 2014, 9, 1869–1884.
31. Prabhakaran, M.P.; Ghasemi-Mobarakeh, L.; Jin, G.; Ramakrishna, S. Electrospun Conducting Polymer Nanofibers and Electrical Stimulation of Nerve Stem Cells. *J. Biosci. Bioeng.* 2011, 112, 501–507.
32. Zha, F.; Chen, W.; Hao, L.; Wu, C.; Lu, M.; Zhang, L.; Yu, D. Electrospun Cellulose-Based Conductive Polymer Nanofibrous Mats: Composite Scaffolds and Their Influence on Cell Behavior with Electrical Stimulation for Nerve Tissue Engineering. *Soft Matter* 2020, 16, 6591–6598.
33. Johnson, C.D.L.; D'Amato, A.R.; Gilbert, R.J. Electrospun Fibers for Drug Delivery after Spinal Cord Injury and the Effects of Drug Incorporation on Fiber Properties. *Cells Tissues Organs* 2016, 202, 116–135.