

Polymers in Wastewater Treatment

Subjects: Environmental Sciences

Contributor: Mohamad Fared Murshed

The utilization of various types of natural and modified polymers for removing toxicant dyes in wastewater generated by the dye industry is reviewed in this article. Dye wastewater contains large amounts of metals, surfactants, and organic matter, which have adverse effects on human health, potentially causing skin diseases and respiratory problems. The removal of dyes from wastewaters through chemical and physical processes has been addressed by many researchers. Currently, the use of natural and modified polymers for the removal of dyes from wastewater is becoming more common. Although modified polymers are preferred for the removal of dyes, due to their biodegradability and non-toxic nature, large amounts of polymers are required, resulting in higher costs.

Keywords: natural and modified polymer ; biodegradability ; toxicant dyes ; industrial wastewater treatment

1. Introduction

The wastewater generated from different manufacturing processes poses serious problems for organisms and aquacultures, due to the high toxicity of these wastes, which contain different types of pollutants, such as plastic, leather, ink, fabric, palm oil, soap, pulp, and paper. These wastes are disposed of directly (with partial treatment) into the environment and natural water systems. Short-term exposure to these pollutants causes tremors and nervous system disorders, while long-term exposure causes thyroid dysfunction, weight loss, and generalized hypoxia ^[1]. Therefore, the treatment of the dye-containing wastewater before the final disposal is an urgent matter, not only to meet international standards but also to protect the biodiversity in nature and to ensure the availability of pure water for future generations. The dye-containing wastewaters have been of great interest to researchers during the past several years, primarily due to the high tectorial values of the dyes, where the discharge of less than 1 ppm of a dye into the water might cause significant changes in the water's physical and chemical characteristics. The traditional treatment methods used for the treatment of wastewaters depend mainly on chemical, physical, and biological processes, which contribute effectively to improving the quality of the effluent parameters, such as the chemical oxygen demand (COD), biochemical oxygen demand (BOD), total suspension solids (TSS), and turbidity. Unfortunately, these methods are insufficient to remove the dyes from the wastewater. Coagulation/flocculation is a potential alternative and a highly efficient method of removing dyes from dye-containing wastewaters.

The conventional coagulation/flocculation process, using inorganic polymers (synthetic or semi-synthetic), such as alum and ferrous sulphate (FeSO_4), could increase the environmental pollution levels by introducing non-biodegradable compounds ^[2]. Therefore, many researchers have shifted to using natural coagulants for wastewater treatment due to the advantages of these coagulants over chemical agents, particularly their low toxicity, low residual sludge production, and biodegradability ^[3]. Natural coagulants are of great interest to scientists, since they are natural, low-cost products, characterized by their environmentally friendly behavior, and are presumed to be safe for human health ^[4]. However, in many of these studies, the utilization of natural coagulants was associated with the addition of natural polymers, in order to enhance the floc size by attracting smaller particles to generate much larger flocs, and, in some of the studies, natural polymers were used, without adding any coagulant, due to the high efficacies of natural polymers in the flocculation process (direct flocculation) ^{[5][6]}.

The use of natural polymers (plant or animal sources) is a promising method for treating wastewater and removing dyes, due to the chemical structure and the composition of the polymers, such as the presence of many functional groups, which contribute effectively towards the removal of dyes from the wastewater. In addition, natural polymers are non-toxic, low-cost, renewable, biodegradable, and biocompatible ^[7]. Natural polymers are synthesized from plant products, such as starch, guar gum, gum acacia, locust bean gum, pectin, nirmali seeds (*Strychnos potatorum*), and drumstick trees (*Moringa oleifera*), as well as from non-plant sources, such as alginates, carrageenans, chitin, chitosan, bacteria, algae, and fungi ^{[8][9][10][11][12][13][14]}. Nonetheless, in many cases, natural polymers are not sufficient to remove the dyes from highly complex dye-containing wastewaters, containing different types of pollutants, such as heavy metals, which have a negative effect on the attraction of dyes to natural polymers. Therefore, these polymers should be subjected to a

modification process, involving chemical or physical treatment, in order to increase their efficiency in removing dyes from complex wastewaters. It is vital to modify the polymers according to the target application with tailor-made specifications, designed using blending, grafting, curing or derivatization methods. The natural polymer can be chemically modified by mineral acids, bases, salts of weak acids, enzymes, acetylation, saponification, concentrated ammonium systems, and primary aliphatic amines [15]. The physical modification process includes the blending of two or more types of the polymer at ambient temperature or elevated temperature. Polymer grafting involves the monomer being covalently bonded onto the polymeric chain, which requires a longer time compared to curing. Curing forms, a coat of oligomers mixture onto the substrate using physical forces. In derivatization, the substitution of a simple molecule with a reactive group on the polymeric chain occurs to provide additional functional groups.

2. Application of Polymers in Wastewater Treatment

A polymer, whether grafted as a polysaccharide base, is highly efficient at binding and linking particles to itself and vice versa during collisions, resulting in the formation of larger, more settled flocs [16]. Polymers used in flocculation and coagulation might be inorganic or organic, and might be generated from natural resources, such as tannin, pectin, sodium alginate, chitosan, cellulose, gums, and mucilages, which are derived from polysaccharides and proteins [17], or synthesized, such as acrylamide based poly-(2-methacryloyloxyethyl)-trimethylammonium chloride [18][19][20]. However, most of the previous studies focus extensively on the utilization of natural polymers, due to their high biodegradability. Many of the natural polymers discussed in the literature have been extracted from *Moringa oleifera*, *Strychnos potatorum*, *Pseudomonas plecoglossicida*, *Spirogyra* sp., and *Aspergillus niger* [21][22][23][24][25]. The extraction of polymers from agro-waste, such as guar gum, pectin, tannin, and locust bean gum, is explored due to these being environmentally safe, natural compounds from renewable resources, and not producing unintended hazardous wastes [26]. The high efficiency of the natural polymers in the removal of dyes from wastewater lies in the presence of different functional groups, such as the carboxyl, hydroxyl, phosphate, amine functional groups, which can bind to the cationic charges on the dye molecules by using electrostatic force [27]. Moreover, renewable resources are abundant, and the aspect of biodegradability attracts many researchers [28]. The studies concerning the application of natural polymers in water and wastewater treatment are listed in Table 1.

Table 1. Treatment of several types of wastewater using natural polymers.

| Natural Polymer | Types Of Wastewater | Treatment Process | Condition | Type Of Dye | Colour Removal | References |
|-----------------|---------------------|------------------------------|---|-------------------------|----------------|------------|
| Pectin | Textile wastewater | Coagulation and flocculation | pH 5, 427.4 mg/l $MgCl_2$ and 21.9 mg/l pectin | -NA- | 54.20% | [29] |
| | Synthetic dye | Adsorption | pectin dose 20 mg; pH 8 20 mg/l of Methylene blue | Methylene blue dye | 45.00% | [30] |
| | Synthetic dye | Adsorption | pH 2, 247.4 mg/l dose; 34.32 mg/l dye concentration; 540-min time | Crystal Ponceau 6 R dye | 99.20% | [31] |

| | | | | | | |
|----------|---------------|----------------------------|---|-----------------------------|--|------|
| | Synthetic dye | Adsorption | no pH adjustment; 20 mg of beads were added to 50 mL of the dye solution | Methylene blue dye | 1550.3 mg/g for Pectin bead and 2307.9 mg/g for pectin/cellulose microfiber bead | [32] |
| Chitosan | Synthetic dye | Coagulation & flocculation | pH 4.0, coagulant dose of 25 mg/l, flocculation time of 60 min, and temperature of 340 K | Congo Red (CR) dye removal- | 94.50% | [33] |
| | Synthetic dye | Adsorption | chitosan beads, 1-butyl-3-methylimidazolium acetate and 1-butyl-3-methylimidazolium (pH 4.0, a dose of 0.008 g, and agitation time of 20 min) | Malachite Green (MG) dye | 8.07 mg g ⁻¹ and 0.24 mg g ⁻¹ | [34] |

References

- Uppal, H.; Tripathy, S.S.; Chawla, S.; Sharma, B.; Dalai, M.K.; Singh, S.P.; Singh, S.; Singh, N. Study of cyanide removal from contaminated water using zinc peroxide nanomaterial. *J. Environ. Sci.* 2017, 55, 76–85.
- Huang, X.; Sun, S.; Gao, B.; Yue, Q.; Wang, Y.; Li, Q. Coagulation behavior and floc properties of compound bioflocculant–polyaluminum chloride dual-coagulants and polymeric aluminum in low temperature surface water treatment. *J. Environ. Sci.* 2015, 30, 215–222.
- Thakur, S.S.; Choubey, S. Use of Tannin based natural coagulants for water treatment: An alternative to inorganic chemicals. *Int. J. Chem. Tech. Res.* 2014, 6, 3628–3634.
- Mishra, A.; Bajpai, M. Flocculation behaviour of model textile wastewater treated with a food grade polysaccharide. *J. Hazard. Mater.* 2015, 118, 213–217.
- Lee, C.S.; Robinson, J.; Chong, M.F. A review on application of flocculants in wastewater treatment. *Process Saf. Environ. Prot.* 2014, 92, 489–508.
- Mishra, A.; Srinivasan, R.; Bajpai, M.; Dubey, R. Use of polyacrylamide-grafted *Plantago psyllium* mucilage as a flocculant for treatment of textile wastewater. *Colloid Polym. Sci.* 2004, 282, 722–727.
- Anastakis, K.; Kalders, D.; Diamadopoulos, E. Flocculation behavior of mallow and okra mucilage in treating wastewater. *Desalination* 2009, 249, 786–791.
- Rakhshaei, R.; Panahandeh, M. Stabilization of a magnetic nano-adsorbent by extracted pectin to remove methylene blue from aqueous solution: A comparative studying between two kinds of cross-liked pectin. *J. Hazard. Mater.* 2011, 189, 158–166.
- Junior, O.M.C.; Barros, M.A.S.D.; Pereira, N.C. Study on coagulation and flocculation for treating effluents of textile industry. *Acta Sci. Technol.* 2012, 35, 83–88.
- Elieh-Ali-Komi, D.; Hamblin, M.R. Chitin and chitosan: Production and application of versatile biomedical nanomaterials. *Int. J. Adv. Res.* 2016, 4, 411.
- Das, M.; Adholeya, A. Potential Uses of immobilized bacteria, fungi, algae, and their aggregates for treatment of organic and inorganic pollutants in wastewater. *Water Chall. Solut. Glob. Scale* 2015, 1206, 319–337.
- Jia, H.; Yuan, Q. Removal of nitrogen from wastewater using microalgae and microalgae–bacteria consortia. *Cogent Environ. Sci.* 2016, 2, 1275089.
- Robinson, T.; McMullan, G.; Marchant, R.; Nigam, P. Remediation of dyes in textile effluent: A critical review on current treatment technologies with a proposed alternative. *Bioresour. Technol.* 2001, 77, 247–255.

14. Sen, G.; Ghosh, S.; Jha, U.; Pal, S. Hydrolyzed polyacrylamide grafted carboxymethylstarch (Hyd.CMS-g-PAM): An efficient flocculant for the treatment of textile industry wastewater. *Chem. Eng. J.* 2011, 171, 495–501.
15. Achor, M.F. Direct flocculation process for wastewater treatment. In *Advances in Water Treatment and Technology*; Springer: Dordrecht, The Netherlands, 2012.
16. Babel, S.; Kurniawan, T.A. Low-cost adsorbents for heavy metals uptake from contaminated water: A review. *J. Hazard. Mater.* 2003, 97, 219–243.
17. Shen, Y.; Yang, R.; Liao, Y.; Ma, J.; Mao, H.; Zhao, S. Tannin modified aminated silica as effective absorbents for removal of light rare earth ions in aqueous solution. *Desalin. Water Treat.* 2016, 57, 18529–18536.
18. Akter, N.; Hossain, M.A.; Hassan, M.A.; Ali, M.K.; Eliaz, U.M.; Rahman, M.M.; Asir, A.Z.; Siddiquey, T.A.; Hasnat, M.A. Moringa Oleifera Seeds (Mos) Synthetic dyes Adsorption of Brilliant Green dye. *J. Environ. Chem. Eng.* 2016, 4, 1231–1241.
19. Ho, Y.C.; Norli, I.; Abbas, F.M.A.; Morad, N. Enhanced turbidity removal in water treatment by using emerging vegetal biopolymer composite: A characterization and optimization study. *Desalin. Water Treat.* 2016, 57, 1779–1789.
20. Bongiovani, M.C.; Camacho, F.P.; Coldebella, P.F.; Valverde, K.C.; Nishimiy, Bergamasco, R. Removal of natural organic matter and trihalomethane minimization by coagulation/flocculation using a natural tannin. *Desalin. Water Treat.* 2016, 57, 5406–5415.
21. Jung, Y.; Kwon, M.; Kye, H.; Abrha, Y.W.; Kang, J.W. Evaluation of Moringa oleifera seed extract by extraction time: Effect on coagulation efficiency and extract characteristic. *J. Water Health* 2018, 16, 904–913.
22. Salehizadeh, H.; Yari, N.; Parnood, R. Recent advances in polysaccharide bio-based flocculants. *Biotechnol. Adv.* 2018, 36, 92–119.
23. Arunkumar, P.; Sadish Kumar, V.; Saran, S.; Bindu, P.; Deepa, S.P. Isolation of active coagulant protein from the seeds of Strychnos nitorum—a potential water treatment agent. *Environ. Technol.* 2018, 40, 1624–1632.
24. Roy, U.; Sengupta, S.; Banerjee, P.; Das, P.; Bhowal, A.; Datta, S. Assessment on the decolourization of textile dye (Reactive Yellow) using Pseudomonas sp. immobilized on fly ash: Response surface methodology optimization and toxicity evaluation. *J. Environ. Manag.* 2018, 223, 185–195.
25. Mathur, M.; Gola, D.; Panja, R.; Malik, A.; Ahammad, S.Z. Performance evaluation of two Aspergillus spp. for the decolourization of reactive dyes by bioaccumulation and biosorption. *Environ. Sci. Pollut. Res.* 2018, 25, 345–352.
26. Jeyaseelan, K.; Murugesan, A.; Palanisamy, S.B. Biopolymer Technologies for Environmental Applications. In *Nanoscience and Biotechnology for Environmental Applications*; Springer: Cham, Switzerland, 2019; pp. 55–83.
27. Gunatilake, S.K. Methods of removing heavy metals from industrial wastewater. *Methods* 2015, 1, 14.
28. Du, Q.; Wei, H.; Li, A.M. Multi-functional natural polymer based water treatment agents. *Environ. Chem.* 2018, 37, 1293–1310.
29. Aisyah, S.I.; Norfariha, M.S.; Azlan, M.A.; Norli, I. Comparison of Synthetic and Natural Organic Polymers as Flocculant for Textile Wastewater Treatment. *Iran. J. Energy Environ.* 2014, 5, 436–445.
30. Onukwuli, O.D.; Obiora-Okafo, I.A.; Omotoma, M. Characterization and Colour Removal from An Aqueous Solution Using Bio-Coagulants: Response Surface Methodological Approach. *J. Chem. Technol. Metall.* 2019, 54, 77–89.
31. Jagaba, A.H.; Abubakar, S.; Lawal, I.M.; Lati, A.A.A.; Umar, I. Wastewater Treatment Using Alum, the Combinations of Alum-Ferric Chloride, Alum-Chitosan, Alum-Zeolite and Alum-Moringa Oleifera as Adsorbent and Coagulant. *Int. J. Eng. Manag.* 2018, 2, 67–75.
32. Janki, V.; Vijayaraghavan, K.; Oh, B.T.; Ramasamy, A.K.; Kamala-Kannan, S. Synthesis, characterization and application of cellulose/polyaniline nanocomposite for the treatment of simulated textile effluent. *Cellulose* 2013, 20, 1153–1166.
33. Vijayaraghavan, G.; Kumar, P.V.; Chandrakanthan, K.; Selvakumar, S. Acanthocereus tetragonus as effective natural coagulant for decolorization of synthetic dye wastewater. *J. Mater. Environ. Sci.* 2017, 8, 3028–3033.
34. Naseeruteen, F.; Hamid, N.S.A.; Suah, F.B.M.; Ngah, W.S.W.; Mehamod, F.S. Adsorption of malachite green from aqueous solution by using novel chitosan ionic liquid beads. *Int. J. Biol. Macromol.* 2018, 107, 1270–1277.
35. Aboulhassan, M.A.; Souabi, S.; Yaacoubi, A.; Baudu, M. Coagulation efficacy of a tannin coagulant agent compared to metal salts for paint manufacturing wastewater treatment. *Desalin. Water Treat.* 2016, 57, 19199–19205.

3. Conclusion

36. Sanghi, R.; Bhattacharya, B.; Singh, V. Use of Cassia javahikai seed gum and gum-g-polyacrylamide as coagulant aid for the decolorization of textile dye solutions. *Bioresour. Technol.* 2006, 97, 1259–1264.
37. Ashaoungata, M.; El-Farouk, J.; Al-Abdoun, M.; Al-Johay, F.; Saggoff, B.; Ossen, S.A.; Amin, T. Removal of reactive dyes from their aqueous solutions using Moringa oleifera seeds and Grewia venusta Peel. *Desalin. Water Treat.* 2018, 161, 107–114.

treatment. Thus, an effective solution is required in order to improve water quality. Grafted natural polymers could replace commercial polymers with an additional incentive of reduced costs. The characteristics of effective coagulants can be enhanced by using specific types of polymers, the concentration and mixing conditions, functional groups, higher molecular weight, and charge density according to the target dyes pollutant. The chemical modification of polymers provided the opportunity to explore beyond conventional applications. A thorough understanding of the polymer and its chemical modification has a vast potential to be the future trend for the use of cosmetics, pharmaceutical, food, leather, paper, and textile industries.

Retrieved from <https://encyclopedia.pub/entry/history/show/6362>