Cryogenic Treatments in Energy Sector

Subjects: Energy & Fuels

Contributor: Patricia Jovičević-Klug , Michael Rohwerder

Cryogenic treatment (CT) is one of the possible solutions for an environmentally friendly, sustainable, and costeffective technology for tailoring the properties of different metallic materials.

energy sectorrenewable energyfusionmetallic materialscryogenic treatment

1. Introduction

The technology of cryogenic treatment (CT) has made tremendous progress in the last 10 years in its application on metallic materials in various sectors ranging from medicine, aerospace, robotics, materials science (including the steel industry), nanotechnology, and mining to even more specialized disciplines ^{[1][2]}. The technique has evolved from the first attempts to treat materials at cryogenic temperatures in the 19th century by James Dewar and Karol Olszewski using liquefied gases (nitrogen and hydrogen). Later, the first real scientific observation and documentation of CT was made by NASA (National Aeronautics and Space Administration) in the mid-20th century, when they observed changes in the properties of materials used in space shuttles returning from space ^{[1][2]}. The selected aluminum components were harder and more wear-resistant after returning to Earth than they were before the space mission ^{[1][2]}. Since then, CT has been slowly adapted with different techniques and applications to metallic materials in order to improve macroscopic and microscopic properties. In the literature, CT can also be called sub-zero treatment, ultra-low temperature processing, or cryo-processing ^{[1][2][3][4][5]}.

The application of CT in the energy sector can be of particular interest due to the variety of metallic materials that are used in extreme conditions (high-temperature and high-pressure environments, highly corrosive environments, highly abrasive environments, etc.). However, the application of CT in the energy sector is still in its infancy, mainly due to the slow introduction and development of this treatment scheme and the limited research focus on applications in the energy sector.

2. Mechanisms of Cryogenic Treatments

The mechanisms of CTs are based on the type, which is defined by the selected temperature regime for the CT (**Figure 1**). CT is usually applied after the material has been hardened and quenched and before being tempered, usually for 24 h at a predetermined temperature ^{[1][2][6][7][8][9][10]}. The most common and the one with the longest tradition is the conventional cryogenic treatment (CCT), where temperatures as low as 193 K are used ^[11].



Figure 1. The heat treatment route(s) for both ferrous and non-ferrous alloys when CT is applied.

The reason for CCT being the most-used type in the past was the easy availability of media to which the material is exposed, namely dry ice (solid CO₂) ^{[2][11]}. In the past, it was also believed that temperatures as low as 193 K were sufficient to transform all the retained austenite (RA) in ferrous alloys to martensite, thereby increasing wear resistance and fatigue strength ^{[2][11]}. The transformation of RA to martensite, particularly in steels, was one of the key properties for which CTs were commonly applied, which also propagated the initial research on CT ^{[2][11]}. Unfortunately, the negative results of the first experiments with CCT led many companies to abandon the application and development of this treatment (1940s–1950s) ^{[2][11]}. This was mainly due to a misunderstanding of the martensitic transformation and its temperatures as well as simplistic and inconsistent treatment procedures ^[2] ^[11]. It was not until years later, after NASA observations and detailed documentation of the changes at lower temperatures, that the next two types of CT were developed and tested for materials science applications: shallow (SCT) and deep cryogenic treatment (DCT) ^{[2][11]}.

Shallow cryogenic treatment is defined between 193 K and 113 K. During SCT, more than 50% of the RA is converted to martensite for generally any ferrous alloy that has instable austenite formation during quenching, causing a change in mechanical properties (increased hardness), size reduction of carbides, and increased precipitation of carbides ^{[12][13]}. With the positive results of SCT, the research on CT blossomed and led to further research at even lower temperatures, resulting in the development of deep cryogenic treatment.

Temperatures for deep cryogenic treatment are below 113 K and typically go as low as 4 K, which is the temperature of liquid helium. However, the most-used temperature is 77 K, the temperature of liquid nitrogen, which is the most-used medium in DCT due to abundancy of the media and economic reasons. With DCT, for ferrous alloys, most of the RA is converted to martensite (>90%), the precipitation of carbides is increased, grain refinement and precipitation of nanocarbides occurs, and changes to residual stresses are formed ^[14]. Special

mention should be made to a specific type of DCT, the multi-stage deep cryogenic treatment (MCT), where the DCT treatment of the material consists of rapid changes between SCT and DCT temperatures for a predefined time and number of cycles to manipulate predefined properties ^[15]. DCT performance is influenced by the selected cooling temperature, cooling–warming rate, time the material is exposed to DCT, type of metallic material (ferrous/non-ferrous alloy or type of steel), chemical composition of the metallic material, hardening process, tempering temperature, and also the microstructural phenomena present within the microstructure (such as transformation-induced plasticity (TRIP), austenite reversion transformation (ART), and twinning-induced plasticity (TWIP)) ^{[16][17][18][19][20][21][22]}.

All types of CT alter the bulk and surface properties of metallic materials. The bulk properties affected by CT are mechanical properties ((micro)hardness ^{[23][24][25][26]}, toughness ^{[23][27][28][29]}, strength ^{[30][31][32]}, and fatigue ^{[19][33]} ^[34]) and magnetism ^{[16][35]}. The surface properties affected by CT are corrosion resistance ^{[36][37][38][39][40][41][42][43]} ^[44], wear resistance ^{[33][45][46][47]}, roughness ^[48], and oxide formation ^{[36][37][38][48]}.

Bulk properties and, to some extent, selected surface properties have been studied in more detail than others. There are still many unknowns and great potential in surface properties and corrosion resistance.

3. Energy Sector and Position of Cryogenic Treatments

Cryogenic processing has a great potential in the energy sector due to the use of different materials, from metallic to non-metallic. The application of CT, especially for metallic materials, has a great potential because it improves the properties of metallic materials needed in different energy sectors, from corrosion and wear resistance to mechanical properties and surface modifications ^{[49][50]}. At the same time, it does not require the additional application of any other coating treatment to improve the properties.

However, the application of CT in this sector has not been widespread due to the lack of known test methods and quantification and qualification methods. Only a few attempts have been made to provide systematic guidelines for standards and application of CT for metallic materials ^{[2][18][21][51][52][53]}. An additional obstacle was that in the past, there were no large capacity tanks, and no providers of these services or systems were available on an industrial scale, but this is now changing and, in some cases, improving with the establishment of CT-specialized companies, communities, and even patents ^{[3][4][5][44][54][55][56][57][58][59]}. CT was also not well transferred to other disciplines, as CT was mainly reserved and developed for improving tools. The research was (and still is) mainly focused on tool steels, such as high-speed steels, hot work tool steels, and cold work tool steels, where the emphasis is on mechanical and wear properties ^{[46][60][61][62][63]}.

As a result, the majority of other types of steels and alloys have been left out of the focus. There is some limited research on non-ferrous alloys, but even these are mostly related to aluminum alloys used or related to the tooling industry. The study of non-ferrous alloys (Al-, Ni-, and Ti-based alloys) showed the improvement of mechanical properties ^{[64][65][66][67][68][69][70]} such as microhardness ^{[64][66][71][72][73]}, fatigue ^[64], fracture toughness ^{[74][75]}, impact toughness ^[64], and tensile strength ^{[64][66]}.

4. Effect of Cryogenic Treatments on Surface, Interface, and Corrosion Properties of Metallic Mateirals Used in the Energy Sector

4.1. Metallic Materials Being Tested for the Use in the Energy Sector

There are many metallic materials (ferrous and non-ferrous alloys) that are suitable for use in the energy sector that have already been tested through various cryogenic treatments, and studies have resulted in changes in the microstructure of metallic materials, resulting in changes in the properties of the material. The following ferrous and non-ferrous alloys are used in the following sectors (**Table 1**).

Table 1. The list of ferrous alloys that were cryogenically treated and have the potential for use in the energy sector.

Ferrous Alloys	Grades of Steel	Tested Properties	Possibilities of Application in Selected Energy Sector
Austenitic stainless steel	AISI 304 [76][77][78][79][80][81][82], AISI 304L [20][31][83][84][85][86], AISI 304LN [86], AISI 316 [86][87][88][89][90][91][92], AISI 316L [53][60][93][94][95][96][97], AISI 316LN [86][98], AISI 321 [99][100], AISI 347 [101][102]	Hardness, microhardness, wear (abrasive wear), fracture toughness, impact toughness, compressive strength, tensile strength, yield strength, elongation, friction, erosion, strain- hardening exponent, surface roughness, machining of steel, fatigue, residual stress, surface chemistry, and oxidation	In all energy sectors
Martensitic stainless steel	AISI 410 ^[103] , AISI 420 ^[61] [103][104] ^[105] , AISI 420 MOD ^[105] , AISI 430 ^[106] [107], AISI 431 ^[16] [21][108], AISI 440C ^[78] , AISI P91 ^[109] , 10Cr13Co13Mo5NiW1VE ^[110] , 13Cr4NiMo ^[27] , 10Cr ^[111] .	Yield strength, elongation, tensile strength, wear, hardness, impact toughness, fracture toughness, magnetism tribocorrosion, electrochemistry, and corrosion resistance (also stress corrosion cracking)	In all energy sectors.

Ferrous Allo	ys Grades of Ste	el	Tested Properties		Possibilities of Application in Selected Energy Sector	
Duplex steels	AISI 2205 ^{[112][113]} , AISI ([115][116][117]	2507 ^[114]	Hardness, wear, machinabilit residual stress, and corrosior resistance	У, Г 1	Mostly in wind and solar energy	
Carbon steels	IS 2062 ^{[<u>118</u>], AISI 1045 [[] [<u>122][123][124][125</u>], AISI 101}	<u>119 [120 [121]</u> .8 [<u>126</u>]	Hardness, wear, surface roughness, tensile strength, y strength, ultimate tensile stre elongation, and residual stres	vield ngth, ss	Steels can be used in hydroelectrical, biomass, solar, and geothermal energy	
Other steels	Nitronic steels 40 ^[127] , 5 High-strength steels AST	0 ^[128] TM A36 ^[129]				
	Cast steels ASTM A743 ^[130] , SAE J431 G10 ^[131]					
	ACSR [132]		Residual tress, hardness, fric wear, fatigue, impact toughne	ion, ss, In all energy		
	Bearing steel AISI 52100 [<u>134][135]</u>) [<u>38][40][133]</u>	corrosion resistance, and machinability		sectors	ind futi
	Low-alloyed steels SAE AISI 4340 ^[137] , AISI 414	1008 ^{[<u>136</u>], 0 ^[<u>137</u>]}				anerav
	Structural steel S235 ^[13] [139][140], S460 ^[141]	^{3]} , S355				shergy
Non- Ferrous Alloys	Grades of Alloys		Tested Properties	Possibili Select	ies of Application in ed Energy Sector	
Al- based	2xxx series: 2024 ^[66] F [<u>142]</u> r	Hardness, wear (abrasion), corrosion resistance, tensile strength, machinability, fatigue, strain-hardening coefficient, residual stress, fracture toughness, and corrosion resistance		Mostly in hydroelectrical, biomass, wind, and solar energy		
anoy	3xxx series: A356 ^[143] [144], A390 ^[145]					

Non- Ferrous Alloys	Grades of Alloys	Tested Properties	Possibilities of Application in Selected Energy Sector	
	6xxx series: 6026 ^[64] [<u>146][147][148]</u> , 6061 ^[65] [<u>149][150]</u> , 6063 ^[74]			
	7xxx series: 7075 [42][43] [73][151][152][153][154][155]			
Ni- based alloy	Inconel: 200 ^[156] , 600 [157][158], 617 ^[159] , 625 [160][161][162], 690 ^[163] , 800 ^[164] , 800H ^{[165][166]} [167]	Fatigue, surface roughness, machinability, durability, impact toughness, microhardness, and tensile strength	In all energy sectors	
	Hastelloy C276 ^[168] , C22 ^{[169][170]} , X ^[171]			
Other alloys	HEA [172]			
	W-based alloys ^[173]	Microhardness, compressive strength, and plasticity	Mostly in advanced nuclear power (fusion),	
	Cu-based alloys ^[174]		geothermal, and solar energy	
	Ti-based alloys Ti6Al4V [<u>164][175]</u>			

The surface properties that are the focus of this research and that also need more attention in order to carry out more research on them are corrosion resistance and oxide formation, while wear resistance and roughness have been observed and researched by many studies in the cryogenic community.

5.1. Oxide Formation

Oxide formation is one of the properties that is seldomly researched and not fully understood in CT. The fact is that most of the studies focus on the corrosion resistance and its improvement by CT, and not many studies strive for deeper understanding of the origin of altered corrosion resistance by CT. A major contribution is provided by passive layers and oxide formation (corrosion products) that can be manipulated by CT and CT-induced changes to the bulk properties of the treated material. The influence of CT on oxide formation has been demonstrated for bearing, high-speed, and cold work tool steels ^{[36][37][38][48]}. The oxidation dynamics after the application of CT was

mainly studied by Jovičević-Klug et al., where the observations showed a different development of oxides compared to conventional heat treatment (CHT).

Jovičević-Klug et al. 2021 ^[48] suggested that the chemical composition of the oxide formation directly corresponds to the higher number of precipitates and the higher surface-to-volume ratio of the carbides. Furthermore, the study indicates that the reduced amount of carbide clusters after CT could be directly correlated with the passivation layer and the oxidation state of the surface and the corresponding corrosion products.

In the next study, Jovičević-Klug et al. 2021 ^[37] suggested that the Cr oxide layer is thicker on the cryogenically treated samples compared to the CHT samples. These observations also suggest that due to the formation of the Cr-oxide-passivation layer on the CT sample, there is no microscopic-related stress corrosion cracking of the matrix, which in turn, combined with the thicker passivation layer, reduces corrosion propagation.

The next factor observed in relation to CT was the formation of Fe oxides. The study by Jovičević-Klug et al. ^[38] suggested that Fe-oxides form different layers compared to the CT sample, which is attributed to the local excessive corrosion damage in the CHT sample.

The same researchers, Jovičević-Klug et al. 2022 ^[36], also observed the different layering of the oxides in the samples. The results of ToF-SIMS provided the novel insight that nitrogen from CT is present in greater amounts in the CT samples, which then influences the complex oxide formations (corrosion products), which ultimately influence the corrosion resistance. Nitrogen acts as an exalter for the formation of green rust, which then acts as a precursor for the formation of the next layer (magnetite). As a result, corrosion propagation is greatly retarded due to the higher density and stability of magnetite. The same study also confirmed that the CT-induced passive film is more stable than its CHT counterpart. As a result, the CT-treated sample showed lower corrosion and wear loss, which was also confirmed in extreme environments (elevated temperatures and vibrations).

The above examples show that there is a need for research on oxide formation as the basis for successful tailoring of corrosion resistance and prolonged component life of treated materials. The studies only focused on tool and bearing steels, which means that other steels such as high-Cr steels, stainless steels, duplex steels, and non-ferrous alloys are still potential research areas with great opportunities for the application of CT to manipulate oxide formation and modify corrosion resistance. To date, no similar studies or research have been conducted or found for non-ferrous alloys.

5.2. Corrosion Resistance

The influence of CT on corrosion resistance has not only been investigated in relation to tool steels, but many studies have also tested other ferrous (bearing steels and stainless steels) and non-ferrous (mostly Al-based alloys) alloys. The first part focuses on the corrosion testing of ferrous alloys, while the second part focuses on the non-ferrous alloys in relation to CT.

Corrosion Resistance of Ferrous Alloys

The studies on tool steels showed that corrosion resistance is influenced by CT [41][105][176][177][178][179]. The corrosion resistance of bearing and tool steels can be improved by up to 65% in an alkaline environment, with the improvement depending on the steel type and heat treatment strategy [38]. This was also observed by Senthilkumar 2014 ^[39], who found that in alkali conditions, CT improves corrosion resistance, which was postulated to be a result of formation of more stable passive film. Furthermore, in extreme alkaline environments, such as elevated temperatures and vibrations, the CT-treated samples (tool steels) suggested improvement of corrosion resistance by 90% in the study of Jovičević-Klug et al. 2022 [36]. Also, the study by Jovičević-Klug et al. 2021 [38] showed that in an alkaline environment, the formation of pits is modified by CT (for tool and bearing steels). The study showed that pits in CT specimens expand only in the exposed upper part and decrease continuously deeper into the material. It was suggested that this is due to the confinement of the corrosion attack to the grain boundaries and the exposure of the pit opening to the oxidative media, which is limited by the change in orientation of the crack with respect to the sample surface. In addition, the 2021 study by Jovičević-Klug et al. [37] also showed that in the alkaline environment, the CT samples did not show any stress corrosion cracking of the passivation layer, and the presence of Mo in the steel allowed the continuous growth of the protective Cr oxide layer, which reduced the formation and growth of pits. The results show that CT samples have a 3× slower corrosion rate of pitting corrosion, which can be directly correlated to the slower material degradation and prolonged functionality of the metallic material.

Only a few studies have been conducted on stainless steels and a few other types of steels that are more commonly used in energy sector applications. The studies showed different results of CT on the corrosion resistance of steels used in the energy sector. A study by Wang et al. 2020 ^[180] showed that there is an increase in corrosion resistance for high-strength stainless steel. On contrary, a study by Baldissera and Delprete 2010 ^[181] postulated that CT has no effect on austenitic stainless steel. Another study by Cai et al. 2016 ^[182] indicated that for austenitic stainless steel, CT could improve corrosion resistance, which is suggested through Cr-carbide precipitation at the austenite grain boundary, which then reduces the intergranular corrosion. For martensitic stainless steels, CT has been shown to improve corrosion resistance in correlation with both the general and pitting corrosion, as was shown by Ramos et al. 2017 ^[78]. Another explanation for the higher pitting corrosion potential was proposed by He et al. 2021 ^[183], in which pitting corrosion was reduced by increased carbide precipitation and Si segregation at the interface boundaries between M₂₃C₆ and martensite in the matrix. For structural steels, a 95% improvement in corrosion resistance was determined by Ramesh et al. 2019 ^[105], which is suggested to be a consequence of uniform and homogenous carbide precipitation and microstructure modification.

The above research shows that there has been some research on corrosion enhancement with CT but only on a limited selection of ferrous alloys. Furthermore, the research shows that there is a great need for research on the corrosion resistance of ferrous alloys used in the energy sector in combination with CT. Such research could open up new avenues and applications for CT to improve corrosion resistance alone or in combination with coatings, which could further expand the energy sector from both an economic and sustainable point of view.

Corrosion Resistance of Non-Ferrous Alloys

The corrosion resistance of CT-treated non-ferrous alloys has been mainly focused on the Al-based alloys of the 2xxx ^[184], 5xxx ^[67], and 7xxx ^{[42][43][153]} series. The study by Cabeza et al. 2015 ^[184] on Al-based alloys from the 2xxx series suggested that CT improves the resistance to stress corrosion cracking due to changes in compressive residual stresses. Another study by Aamir et al. 2016 ^[67] showed that for the 5xxx Al-alloy, the corrosion resistance is increased due to the minimization of dislocation densities and noncontinuous distribution of the β -phase. From the 7xxx series, the tested representative was the 7075 Al-alloy. A study by Ma et al. 2021 ^[153] showed an improvement in corrosion resistance after the application of CT, which was attributed to the increased precipitation of the η' phase. They postulated that the grain boundary from the η' resulted in short chains of carbides, which then blocked corrosion channeling, thus enhancing the corrosion resistance of the alloy. Similar observations were also made by Su et al. 2021 ^[43]. Ma et al., from their study in 2022 ^[42], additionally showed that the optimized combination of aging and CT can influence the rate of the corrosion improvement when CT is applied.

Compared to ferrous alloys, research on non-ferrous alloys is also considered to be lacking and is mostly focused on specific alloys, mainly aluminum alloys. The research clearly confirms the lack of research on non-ferrous alloys, which have a great potential for use in the future energy sector. The lack of research can be particularly evident in the case of Ni alloys and corrosion resistance in combination with CT, which are one of the main nonferrous alloys used in different energy sectors due to their versatility. Other non-ferrous alloys such as Cu-based, Mg-based, V-based, W-based, etc., are also completely excluded from the studies, and therefore, this could be another potentially interesting niche to study in more depth the influence of CT on these alloys, which could be applied to the future energy sector. Furthermore, in most cases, the reasons for improved or sometimes reduced corrosion performance are based on speculation. Fundamental research is needed to elucidate the reasons for the effects of CT on corrosion performance.

References

- 1. Jovičević-Klug, P.; Podgornik, B. Review on the Effect of Deep Cryogenic Treatment of Metallic Materials in Automotive Applications. Metals 2020, 10, 434.
- 2. Jovičević-Klug, P. Mechanisms and Effect of Deep Cryogenic Treatment on Steel Properties; Institute of Metals and Technology: Ljubljana, Slovenia, 2022.
- 3. Workman, K.J.; Pitts, D.W. Method of Treating Brake Pads. U.S. Patent US5447035A, 29 September 1994.
- 4. Leach, J.M.; Harvey, W.L. Method of Cryogenically Hardening an Insert in an Article. U.S. Patent No. 4,336,077, 3 March 1980.
- 5. Voorhees, J.E. Process for Treating Materials to Improve Their Structural Characteristics. U.S. Patent No. 4,482,005, 13 November 1984.

- Baldissera, P.; Delprete, C. Deep Cryogenic Treatment: A Bibliographic Review. Open Mech. Eng. J. 2008, 2, 32–39.
- 7. Vengatesh, M.; Srivignesh, R.; Pradeep, T.; Karthik, N.R. Review on Cryogenic Trearment of Steels. Int. Res. J. Eng. Technol. 2016, 3, 417–422.
- 8. Sonar, T.; Lomte, S.; Gogte, C. Cryogenic Treatment of Metal—A Review. Mater. Today Proc. 2018, 5, 25219–25228.
- 9. Yildiz, Y.; Nalbant, M. A Review of Cryogenic Cooling in Machining Processes. Int. J. Mach. Tools Manuf. 2008, 48, 947–964.
- 10. Akincioğlu, S.; Gökkaya, H.; Uygur, İ. A Review of Cryogenic Treatment on Cutting Tools. Int. J. Adv. Manuf. Technol. 2015, 78, 1609–1627.
- 11. Barron, R.F. Cryogenic Treatment of Metals to Improve Wear Resistance. Cryogenics 1982, 22, 409–413.
- 12. Senthilkumar, D.; Rajendran, I. Influence of Shallow and Deep Cryogenic Treatment on Tribological Behavior of En 19 Steel. J. Iron Steel Res. Int. 2011, 18, 53–59.
- Senthilkumar, D.; Rajendran, I.; Pellizzari, M.; Siiriainen, J. Influence of Shallow and Deep Cryogenic Treatment on the Residual State of Stress of 4140 Steel. J. Mater. Process. Technol. 2011, 211, 396–401.
- Senthilkumar, D. Cryogenic Treatment: Shallow and Deep. In Encyclopedia of Iron, Steel, and Their Alloys; Totten, G.E., Colas, R., Eds.; Taylor and Francis: New York, NY, USA, 2016; pp. 995–1007. ISBN 9781351254496.
- Ciski, A.; Nawrocki, P.; Babul, T.; Hradil, D. Multistage Cryogenic Treatment of X153CrMoV12 Cold Work Steel. In Proceedings of the 5th International Conference Recent Trends in Structural Materials, Pilsen, Czech Republic, 14–16 November 2018; Volume 461, pp. 0120121–0120126.
- Jovičević-Klug, P.; Jovičević-Klug, M.; Thormählen, L.; McCord, J.; Rohwerder, M.; Godec, M.; Podgornik, B. Austenite Reversion Suppression with Deep Cryogenic Treatment: A Novel Pathway towards 3rd Generation Advanced High-Strength Steels. Mater. Sci. Eng. A 2023, 873, 145033.
- Jovičević-Klug, P.; Tegg, L.; Jovičević-Klug, M.; Parmar, R.; Amati, M.; Gregoratti, L.; Almasy, L.; Cairney, J.M.; Podgornik, B. Understanding Carbide Evolution and Surface Chemistry during Deep Cryogenic Treatment in High-Alloyed Ferrous Alloy. Appl. Surf. Sci. 2023, 610, 155497.
- Jovičević-Klug, P.; Puš, G.; Jovičević-Klug, M.; Žužek, B.; Podgornik, B. Influence of Heat Treatment Parameters on Effectiveness of Deep Cryogenic Treatment on Properties of High-Speed Steels. Mater. Sci. Eng. A 2022, 829, 142157.

- Jovičević-Klug, P.; Guštin, A.Z.; Jovičević-Klug, M.; Šetina Batič, B.; Lebar, A.; Podgornik, B. Coupled Role of Alloying and Manufacturing on Deep Cryogenic Treatment Performance on High-Alloyed Ferrous Alloys. J. Mater. Res. Technol. 2022, 18, 3184–3197.
- Jovičević-Klug, P.; Lipovšek, N.; Jovičević-Klug, M.; Mrak, M.; Ekar, J.; Ambrožič, B.; Dražić, G.; Kovač, J.; Podgornik, B. Assessment of Deep Cryogenic Heat-Treatment Impact on the Microstructure and Surface Chemistry of Austenitic Stainless Steel. Surf. Interfaces 2022, 35, 102456.
- Jovičević-Klug, P.; Jovičević-Klug, M.; Sever, T.; Feizpour, D.; Podgornik, B. Impact of Steel Type, Composition and Heat Treatment Parameters on Effectiveness of Deep Cryogenic Treatment. J. Mater. Res. Technol. 2021, 14, 1007–1020.
- 22. Pellizzari, M. Influence of Deep Cryogenic Treatment on the Properties of Conventional and PM High Speed Steels. Metall. Ital. 2008, 100, 17–22.
- 23. Senthilkumar, D. Influence of Deep Cryogenic Treatment on Hardness and Toughness of En31 Steel. Adv. Mater. Process. Technol. 2019, 5, 114–122.
- 24. Baldissera, P. Deep Cryogenic Treatment of AISI 302 Stainless Steel: Part I—Hardness and Tensile Properties. Mater. Des. 2010, 31, 4725–4730.
- 25. Amini, K.; Negahbani, M.; Ghayour, H. The Effect of Deep Cryogenic Treatment on Hardness and Wear Behavior of the H13 Tool Steel. Metall. Ital. 2015, 107, 53–58.
- 26. Elango, G.; Raghunath, B.K.; Thamizhmaran, K. Effect of Cryogenic Treatment on Microstructure and Micro Hardness of Aluminium (LM25)—SiC Metal Matrix Composite. J. Eng. Res. 2014, 10, 64–68.
- Peng, J.; Zhou, B.; Li, Z.; Huo, D.; Xiong, J.; Zhang, S. Effect of Tempering Process on the Cryogenic Impact Toughness of 13Cr4NiMo Martensitic Stainless Steel. J. Mater. Res. Technol. 2023, 23, 5618–5630.
- 28. Çakir, F.H.; Çelik, O.N. The Effects of Cryogenic Treatment on the Toughness and Tribological Behaviors of Eutectoid Steel. J. Mech. Sci. Technol. 2017, 31, 3233–3239.
- 29. Sola, R.; Giovanardi, R.; Parigi, G.; Veronesi, P. A Novel Method for Fracture Toughness Evaluation of Tool Steels with Post-Tempering Cryogenic Treatment. Metals 2017, 7, 75.
- 30. Nanesa, C.H.; Jahazi, M. Simultaneous Enhancement of Strength and Ductility in Cryogenically Treated AISI D2 Tool Steel. Mater. Sci. Eng. A 2014, 598, 413–419.
- 31. Jovičević-Klug, P.; Jovičević-Klug, M.; Rohwerder, M.; Godec, M.; Podgornik, B. Complex Interdependency of Microstructure, Mechanical Properties, Fatigue Resistance and Residual Stress of Austenitic Stainless Steels AISI 304L. Materials 2023, 16, 2638.

- Weng, Z.; Gu, K.; Wang, K.; Liu, X.; Wang, J. The Reinforcement Role of Deep Cryogenic Treatment on the Strength and Toughness of Alloy Structural Steel. Mater. Sci. Eng. A 2020, 772, 138698.
- 33. Korade, D.; Ramana, K.V.; Jagtap, K. Wear and Fatigue Behaviour of Deep Cryogenically Treated H21 Tool Steel. Trans. Indian Inst. Met. 2020, 73, 843–851.
- Bensely, A.; Shyamala, L.; Harish, S.; Mohan Lal, D.; Nagarajan, G.; Junik, K.; Rajadurai, A. Fatigue Behaviour and Fracture Mechanism of Cryogenically Treated En 353 Steel. Mater. Des. 2009, 30, 2955–2962.
- 35. Jovicevic-Klug, M.; Jovicevic-Klug, P.; McCord, J.; Podgornik, B. Investigation of Microstructural Attributes of Steel Surfaces through Magneto-Optical Kerr Effect. J. Mater. Res. Technol. 2021, 11, 1245–1259.
- Jovičević-Klug, P.; Jovičević-Klug, M.; Podgornik, B. Unravelling the Role of Nitrogen in Surface Chemistry and Oxidation Evolution of Deep Cryogenic Treated High-Alloyed Ferrous Alloy. Coatings 2022, 12, 213.
- Jovičević-Klug, M.; Jovičević-Klug, P.; Kranjec, T.; Podgornik, B. Cross-Effect of Surface Finishing and Deep Cryogenic Treatment on Corrosion Resistance of AISI M35 Steel. J. Mater. Res. Technol. 2021, 14, 2365–2381.
- Jovičević-Klug, P.; Kranjec, T.; Jovičević-Klug, M.; Kosec, T.; Podgornik, B. Influence of the Deep Cryogenic Treatment on AISI 52100 and AISI D3 Steel's Corrosion Resistance. Materials 2021, 14, 6357.
- 39. Senthilkumar, D.; Bracke, J.; Slootsman, N. Corrosion and Elastic Behaviour of Cryogenically Treated En 19 Steel. Corros. Manag. 2014, 117, 16–21.
- 40. Wang, W.; Srinivasan, V.; Siva, S.; Albert, B.; Lal, M.; Alfantazi, A. Corrosion Behavior of Deep Cryogenically Treated AISI 420 and AISI 52100 Steel. Corrosion 2014, 70, 708–720.
- 41. Ramesh, S.; Bhuvaneswari, B.; Palani, G.S.; Lal, D.M.; Iyer, N.R. Effects on Corrosion Resistance of Rebar Subjected to Deep Cryogenic Treatment. J. Mech. Sci. Technol. 2017, 31, 123–132.
- 42. Ma, S.; Su, R.; Li, G.; Qu, Y.; Li, R. Effect of Deep Cryogenic Treatment on Corrosion Resistance of AA7075-RRA. J. Phys. Chem. Solids 2022, 167, 110747.
- 43. Su, R.; Ma, S.; Wang, K.; Li, G.; Qu, Y.; Li, R. Effect of Cyclic Deep Cryogenic Treatment on Corrosion Resistance of 7075 Alloy. Met. Mater. Int. 2022, 28, 862–870.
- 44. Garrison, T.C. Process for Improving the Corrosion Resistance of Metals. CN1795278A, 24 May 2004.
- 45. Gunes, I.; Uzun, M.; Cetin, A.; Aslantas, K.; Cicek, A. Evaluation of Wear Performance of Cryogenically Treated Vanadis 4 Extra Tool Steel. Kov. Mater. 2016, 54, 195–204.

- Koneshlou, M.; Meshinchi, A.K.; Khomamizadeh, F. Effect of Cryogenic Tratment on Microstucture, Mechanical and Wear Behaviors of AISI H13 Hot Work Tool Steel. Cryogenics 2011, 51, 55–61.
- 47. Senthilkumar, D.; Rajendran, I. Optimization of Deep Cryogenic Treatment to Reduce Wear Loss of 4140 Steel. Mater. Manuf. Process. 2011, 27, 567–572.
- 48. Jovičević-Klug, P.; Jenko, M.; Jovičević-Klug, M.; Šetina Batič, B.; Kovač, J.; Podgornik, B. Effect of Deep Cryogenic Treatment on Surface Chemistry and Microstructure of Selected High-Speed Steels. Appl. Surf. Sci. 2021, 548, 149257.
- 49. Cryogenic Treatment Applications Find Potential in the Energy Sector. Available online: https://www.cryogenicsociety.org/index.php? option=com_dailyplanetblog&view=entry&year=2023&month=05&day=02&id=188:cryogenictreatment-applications-find-potential-in-the-energy-sector (accessed on 20 July 2023).
- 50. Industrial Heating. Deep Cryogenic Treatment for Marine and Oil-and-Gas Applications. 3 December 2018. Available online: https://www.industrialheating.com/articles/94598-deep-cryogenic-treatment-for-marine-and-oil-and-gas-applications (accessed on 20 July 2023).
- Darwin, J.D.; Mohan Lal, D.; Nagarajan, G. Optimization of Cryogenic Treatment to Maximize the Wear Resistance of 18% Cr Martensitic Stainless Steel by Taguchi Method. J. Mater. Process Technol. 2008, 195, 241–247.
- 52. Kumar, M.C.; Vijayakumar, P.; Narayan, B. Optimization of Cryogenic Treatment Parameters to Maximise the Tool Wear of HSS Tools by Taguchi Method. Int. J. Mod. Eng. Res. 2012, 2, 3051–3055.
- 53. Baloji, D.; Anil, K.; Satyanarayana, K.; Ul Haq, A.; Singh, S.K.; Naik, M.T. Evaluation and Optimization of Material Properties of ASS316L at Sub-Zero Temperature Using Taguchi Robust Design. Mater. Today Proc. 2019, 18, 4475–4481.
- 54. Lance, J.W.; Jones, H.M. Material Treatment by Cryogenic Cooling. U.S. Patent No. 3,891,477, 9 September 1971.
- 55. Jin, F.; Wu, L.; Xiong, C.; Wei, J.; Wen, X. A Kind of Cryogenic Treating Process of Cast Aluminium Alloy Piston Piece. CN103498117B, 29 September 2013.
- 56. De Carvalho Eduardo, A.; Atem De Carvalho, R. Special Steels; Cryogenic Process for the Production Thereof; Use of Special Steels in a Saline and/or High-Pressure Environment. WO2014008564A1, 9 July 2013.
- 57. Jin, F.; Zhou, Z.; Wei, J.; Xiong, C.; Wu, L. High-Speed Steel Cryogenic Treatment Process. CN103525997A, 29 September 2013.

- 58. Pang, B.; Wang, B.; Zhao, X. High-Efficiency Energy-Saving Apparatus Used for Cryogenic Treatment. CN103589840A, 26 November 2013.
- 59. Kamody, D.J. Process for the Cryogenic Treatment of Metal Containing Materials. US5875636A, 1 October 1997.
- 60. Li, Z.; Wang, Y.; Wang, J.; Zhang, Y. Effect of Cryogenic Heat Treatment and Heat Treatment on the Influence of Mechanical, Energy, and Wear Properties of 316L Stainless Steel by Selective Laser Melting. JOM 2022, 74, 3855–3868.
- 61. Prieto, G.; Ipiña, J.E.P.; Tuckart, W.R. Cryogenic Treatments on AISI 420 Stainless Steel: Microstructure and Mechanical Properties. Mater. Sci. Eng. A 2014, 605, 236–243.
- 62. Zhirafar, S.; Rezaeian, A.; Pugh, M. Effect of Cryogenic Treatment on the Mechanical Properties of 4340 Steel. J. Mater. Process. Technol. 2007, 186, 298–303.
- 63. Baldissera, P.; Delprete, C. Effects of Deep Cryogenic Treatment on Static Mechanical Properties of 18NiCrMo5 Carburized Steel. Mater. Des. 2009, 30, 1435–1440.
- Jovičević-Klug, M.; Rezar, R.; Jovičević-Klug, P.; Podgornik, B. Influence of Deep Cryogenic Treatment on Natural and Artificial Aging of Al-Mg-Si Alloy EN AW 6026. J. Alloys Compd. 2022, 899, 163323.
- 65. Nageswara Rao, P.; Jayaganthan, R. Effects of Warm Rolling and Ageing after Cryogenic Rolling on Mechanical Properties and Microstructure of Al 6061 Alloy. Mater. Des. 2012, 39, 226–233.
- Shahsavari, A.; Karimzadeh, F.; Rezaeian, A.; Heydari, H. Significant Increase in Tensile Strength and Hardness in 2024 Aluminum Alloy by Cryogenic Rolling. Procedia Mater. Sci. 2015, 11, 84– 88.
- Aamir, A.; Lei, P.; Lixiang, D.; Zengmin, Z. Effects of Deep Cryogenic Treatment, Cryogenic and Annealing Temperatures on Mechanical Properties and Corrosion Resistance of AA5083 Aluminium Alloy. Int. J. Microstruct. Mater. Prop. 2016, 11, 339–358.
- Gu, K.; Zhang, H.; Zhao, B.; Wang, J.; Zhou, Y.; Li, Z. Effect of Cryogenic Treatment and Aging Treatment on the Tensile Properties and Microstructure of Ti-6AI-4V Alloy. Mater. Sci. Eng. A 2013, 584, 170–176.
- 69. Vinothkumar, T.S.; Kandaswamy, D.; Prabhakaran, G.; Rajadurai, A. Effect of Dry Cryogenic Treatment on Vickers Hardness and Wear Resistance of New Martensitic Shape Memory Nickel-Titanium Alloy. Eur. J. Dent. 2015, 9, 513–517.
- 70. Anil Kumar, B.K.; Ananthaprasad, M.G.; Gopalakrishna, K. Action of Cryogenic Chill on Mechanical Properties of Nickel Alloy Metal Matrix Composites. In Proceedings of the International Conference on Advances in Materials and Manufacturing Applications, Bangalore, India, 14–16 July 2016; pp. 1–11.

- Khedekar, D.; Gogte, C.L. Development of the Cryogenic Processing Cycle for Age Hardenable AA7075 Aluminium Alloy and Optimization of the Process for Surface Quality Using Gray Relational Analysis. Mater. Today Proc. 2018, 5, 4995–5003.
- 72. Yuanchun, H.; Li, Y.; Ren, X.; Xiao, Z. Effect of Deep Cryogenic Treatment on Aging Processes of Al–Mg–Si Alloy. Phys. Met. Metallogr. 2019, 120, 914–918.
- 73. Adin, M.Ş. Performances of Cryo-Treated and Untreated Cutting Tools in Machining of AA7075 Aerospace Aluminium Alloy. Eur. Mech. Sci. 2023, 7, 70–81.
- 74. Vendra, S.S.L.; Goel, S.; Kumar, N.; Jayaganthan, R. A Study on Fracture Toughness and Strain Rate Sensitivity of Severely Deformed AI 6063 Alloys Processed by Multiaxial Forging and Rolling at Cryogenic Temperature. Mater. Sci. Eng. A 2017, 686, 82–92.
- Sonia, P.; Verma, V.; Saxena, K.K.; Kishore, N.; Rana, R.S. Effect of Cryogenic Treatment on Mechanical Properties and Microstructure of Aluminium 6082 Alloy. Mater. Today Proc. 2020, 26, 2248–2253.
- 76. Özbek, N.A.; Çİçek, A.; Gülesİn, M.; Özbek, O. Application of Deep Cryogenic Treatment to Uncoated Tungsten Carbide Inserts in the Turning of AISI 304 Stainless Steel. Met. Mater. Trans. A Phys. Met. Mater. Sci. 2016, 47, 6270–6280.
- 77. Çiçek, A.; Kıvak, T.; Ekici, E. Optimization of Drilling Parameters Using Taguchi Technique and Response Surface Methodology (RSM) in Drilling of AISI 304 Steel with Cryogenically Treated HSS Drills. J. Intell. Manuf. 2015, 26, 295–305.
- Ramos, L.B.; Simoni, L.; Mielczarski, R.G.; Vega, M.R.O.; Schroeder, R.M.; De Fraga Malfatti, C. Tribocorrosion and Electrochemical Behavior of DIN 1.4110 Martensitic Stainless Steels After Cryogenic Heat Treatment. Mater. Res. 2017, 20, 460–468.
- 79. Ben Fredj, N.; Sidhom, H. Effects of the Cryogenic Cooling on the Fatigue Strength of the AISI 304 Stainless Steel Ground Components. Cryogenics 2006, 46, 439–448.
- 80. Nalbant, M.; Yildiz, Y. Effect of Cryogenic Cooling in Milling Process of AISI 304 Stainless Steel. Trans. Nonferrous Met. Soc. China 2011, 21, 72–79.
- Hong, S.Y.; Broomer, M.; Hong, S.Y.; Broomer, M. Economical and Ecological Cryogenic Machining of AISI 304 Austenitic Stainless Steel. Clean Technol. Environ. Policy 2000, 2, 157– 166.
- 82. Dhananchezian, M.; Pradeep Kumar, M.; Sornakumar, T. Cryogenic Turning of AISI 304 Stainless Steel with Modified Tungsten Carbide Tool Inserts. Mater. Manuf. Process. 2011, 26, 781–785.
- 83. Johan Singh, P.; Guha, B.; Achar, D.R.G. Fatigue Life Improvement of AISI 304L Cruciform Welded Joints by Cryogenic Treatment. Eng. Fail. Anal. 2003, 10, 1–12.

- 84. Singh, P.J.; Mannan, S.L.; Jayakumar, T.; Achar, D.R.G. Fatigue Life Extension of Notches in AISI 304L Weldments Using Deep Cryogenic Treatment. Eng. Fail. Anal. 2005, 12, 263–271.
- 85. Oh, D.; Song, S.; Kim, N.; Kim, M. Effect of Cryogenic Temperature on Low-Cycle Fatigue Behavior of AISI 304L Welded Joint. Metals 2018, 8, 657.
- 86. Read, D.T.; Reed, R.P. Fracture and Strength Properties of Selected Austenitic Stainless Steels at Cryogenic Temperatures. Cryogenics 1981, 21, 415–417.
- 87. Manimaran, G.; Pradeep Kumar, M.; Venkatasamy, R. Influence of Cryogenic Cooling on Surface Grinding of Stainless Steel 316. Cryogenics 2014, 59, 76–83.
- Kennedy, F.E.; Ye, Y.; Baker, I.; White, R.R.; Barry, R.L.; Tang, A.Y.; Song, M. Development of a New Cryogenic Tribotester and Its Application to the Study of Cryogenic Wear of AISI 316 Stainless Steel. Wear 2022, 496–497, 204309.
- 89. Bhaskar, L.; Raj, D.S. Evaluation of the Effect of Cryogenic Treatment of HSS Drills at Different Holding Time in Drilling AISI 316-SS. Eng. Res. Express 2020, 2, 025005.
- 90. Norberto López de Lacalle, L.; Gandarias, A.; López de Lacalle, L.N.; Aizpitarte, X.; Lamikiz, A. High Performance Drilling of Austenitic Stainless Steels. Int. J. Mach. Mater. 2008, 3, 1–17.
- 91. Uhlář, R.; Hlaváč, L.; Gembalová, L.; Jonšta, P.; Zuchnický, O. Abrasive Water Jet Cutting of the Steels Samples Cooled by Liquid Nitrogen. Appl. Mech. Mater. 2013, 308, 7–12.
- Çiçek, A.; Uygur, I.; Kvak, T.; Altan Zbek, N. Machinability of AISI 316 Austenitic Stainless Steel with Cryogenically Treated M35 High-Speed Steel Twist Drills. J. Manuf. Sci. Eng. 2012, 134, 061003.
- Kumar, M.; Singh Sidhu, H.; Singh Sidhu, B. Influence of Ultra-Low Temperature Treatments on the Slurry Erosion Performance of Stainless Steel-316L. In Advances in Mechanical and Materials Technology; Lecture Notes in Mechanical Engineering; Springer: Singapore, 2022; pp. 1273– 1286.
- Gao, Q.; Jiang, X.; Sun, H.; Zhang, Y.; Fang, Y.; Mo, D.; Li, X. Performance and Microstructure of TC4/Nb/Cu/316L Welded Joints Subjected to Cryogenic Treatment. Mater. Lett. 2022, 321, 132453.
- 95. Sugavaneswaran, M.; Kulkarni, A. Effect of Cryogenic Treatment on the Wear Behavior of Additive Manufactured 316L Stainless Steel. Tribol. Ind. 2019, 41, 33–42.
- 96. Wang, C.; Lin, X.; Wang, L.; Zhang, S.; Huang, W. Cryogenic Mechanical Properties of 316L Stainless Steel Fabricated by Selective Laser Melting. Mater. Sci. Eng. A 2021, 815, 141317.
- 97. Kosaraju, S.; Singh, S.K.; Buddi, T.; Kalluri, A.; Ul Haq, A. Evaluation and Characterisation of ASS316L at Sub-Zero Temperature. Adv. Mater. Process. Technol. 2020, 6, 445–455.

- Kvackaj, T.; Rozsypalova, A.; Kocisko, R.; Bidulska, J.; Petrousek, P.; Vlado, M.; Pokorny, I.; Sas, J.; Weiss, K.P.; Duchek, M.; et al. Influence of Processing Conditions on Properties of AISI 316LN Steel Grade. J. Mater. Eng. Perform. 2020, 29, 1509–1514.
- Salehi, M.; Eskandari, M.; Yeganeh, M. Characterizations of the Microstructure and Texture of 321 Austenitic Stainless Steel After Cryo-Rolling and Annealing Treatments. J. Mater. Eng. Perform. 2023, 32, 816–834.
- 100. Aletdinov, A.; Mironov, S.; Korznikova, G.; Konkova, T.; Zaripova, R.; Myshlyaev, M.; Semiatin, S.L. EBSD Investigation of Microstructure Evolution during Cryogenic Rolling of Type 321 Metastable Austenitic Steel. Mater. Sci. Eng. A 2019, 745, 460–473.
- Aurich, J.C.; Mayer, P.; Kirsch, B.; Eifler, D.; Smaga, M.; Skorupski, R. Characterization of Deformation Induced Surface Hardening during Cryogenic Turning of AISI 347. CIRP Ann. 2014, 63, 65–68.
- 102. Mayer, P.; Skorupski, R.; Smaga, M.; Eifler, D.; Aurich, J.C. Deformation Induced Surface Hardening When Turning Metastable Austenitic Steel AISI 347 with Different Cryogenic Cooling Strategies. Procedia CIRP 2014, 14, 101–106.
- 103. Laksanasittiphan, S.; Tuchinda, K.; Manonukul, A.; Suranuntchai, S. Use of Deep Cryogenic Treatment to Reduce Particle Contamination Induced Problem in Hard Disk Drive. Key Eng. Mater. 2017, 730, 265–271.
- 104. Prieto, G.; Tuckart, W.R. Influence of Cryogenic Treatments on the Wear Behavior of AISI 420 Martensitic Stainless Steel. J. Mater. Eng. Perform. 2017, 26, 5262–5271.
- 105. Ramesh, S.; Bhuvaneshwari, B.; Palani, G.S.; Mohan Lal, D.; Mondal, K.; Gupta, R.K. Enhancing the Corrosion Resistance Performance of Structural Steel via a Novel Deep Cryogenic Treatment Process. Vacuum 2019, 159, 468–475.
- 106. Makalesi, A.; Şenel, S.; Koçar, O.; Kocaman, E.; Özdamar, O.; Bülent, Z.; Üniversitesi, E.; Fakültesi, M.; Bölümü, M.M. AISI 430 Çeliklerin Derin Kroyonejik İşlem Sonrası Mekanik ve Mikroyapısal Özelliklerinin İncelenmesi. Eur. J. Sci. Technol. 2021, 32, 1000–1005.
- 107. ŞİRİN, Ş.; AKINCIOĞLU, S. Investigation of Friction Performance and Surface Integrity of Cryogenically Treated AISI 430 Ferritic Stainless Steel. Int. Adv. Res. Eng. J. 2021, 5, 194–201.
- Yıldız, E.; Altan Özbek, N.; Ankara Hidrolik Mak San Tic Ltd.; Şti, H. Effect of cryogenic treatment and tempering temperature on mechanical and microstructural properties of aisi 431 steel. Int. J. 3D Print. Technol. Digit. Ind. 2022, 6, 74–82.
- 109. Tembwa, E.N. Softening Response of As-Normalized and Cryogenic-Soaked P91 Martensitic Steels p y g P91 Martensitic Steels. Master's Thesis, University of Johannesburg, Johannesburg, South Africa, 2018.

- 110. Zhao, Z.; Yu, M.; Han, C.; Yang, Z.; Teng, P.; Zhong, J.; Li, S.; Liu, J. Effects of Carbide Evolution on SCC Behaviors of 10Cr13Co13Mo5NiW1VE Martensitic Stainless Steel. Available online: https://papers.ssrn.com/sol3/papers.cfm?abstract_id=4400821 (accessed on 2 October 2023).
- 111. Zhang, H.; Ji, X.; Ma, D.; Tong, M.; Wang, T.; Xu, B.; Sun, M.; Li, D. Effect of Aging Temperature on the Austenite Reversion and Mechanical Properties of a Fe–10Cr–10Ni Cryogenic Maraging Steel. J. Mater. Res. Technol. 2021, 11, 98–111.
- 112. Dhananchezian, M.; Priyan, M.R.; Rajashekar, G.; Narayanan, S.S. Study the Effect of Cryogenic Cooling On Machinability Characteristics During Turning Duplex Stainless Steel 2205. Mater. Today Proc. 2018, 5, 12062–12070.
- 113. Koppula, S.; Rajkumar, A.; Krishna, S.H.; Prudhvi, R.S.; Aparna, S.; Subbiah, R. Improving the Mechanical Properties of AISI 2205 Duplex Stainless Steel by Cryogenic Treatment Process. E3S Web Conf. 2020, 184, 01019.
- 114. Narayanan, D.; Jagadeesha, T. Process Capability Improvement Using Internally Cooled Cutting Tool Insert in Cryogenic Machining of Super Duplex Stainless Steel 2507. In Innovative Product Design and Intelligent Manufacturing Systems; Lecture Notes in Mechanical Engineering; Springer: Singapore, 2020; pp. 323–330.
- 115. Narayanan, D.; Salunkhe, V.G.; Dhinakaran, V.; Jagadeesha, T. Experimental Evaluation of Cutting Process Parameters in Cryogenic Machining of Duplex Stainless Steel. In Advances in Industrial Automation and Smart Manufacturing; Lecture Notes in Mechanical Engineering; Springer: Singapore, 2021; Volume 23, pp. 505–516.
- 116. Kanagaraju, T.; Boopathy, S.R.; Gowthaman, B. Effect of Cryogenic and Wet Coolant Performance on Drilling of Super Duplex Stainless Steel (2507). Mater. Express 2020, 10, 81–93.
- 117. Sastry, C.C.; Abeens, M.; Pradeep, N.; Manickam, M.A.M. Microstructural Analysis, Radiography, Tool Wear Characterization, Induced Residual Stress and Corrosion Behavior of Conventional and Cryogenic Trepanning of DSS 2507. J. Mech. Sci. Technol. 2020, 34, 2535–2547.
- 118. Pradeep Samuel, A.; Arul, S. Effect of Cryogenic Treatment on the Mechanical Properties of Low Carbon Steel IS 2062. Mater. Today Proc. 2018, 5, 25065–25074.
- 119. Thornton, R.; Slatter, T.; Lewis, R. Effects of Deep Cryogenic Treatment on the Wear Development of H13A Tungsten Carbide Inserts When Machining AISI 1045 Steel. Prod. Eng. 2014, 8, 355–364.
- 120. Govindaraju, N.; Shakeel Ahmed, L.; Pradeep Kumar, M. Experimental Investigations on Cryogenic Cooling in the Drilling of AISI 1045 Steel. Mater. Manuf. Process. 2014, 29, 1417– 1421.
- 121. Dilip Jerold, B.; Pradeep Kumar, M. Experimental Investigation of Turning AISI 1045 Steel Using Cryogenic Carbon Dioxide as the Cutting Fluid. J. Manuf. Process. 2011, 13, 113–119.

- 122. Mahendran, R.; Rajkumar, P.; Nirmal Raj, L.; Karthikeyan, S.; Rajeshkumar, L. Effect of Deep Cryogenic Treatment on Tool Life of Multilayer Coated Carbide Inserts by Shoulder Milling of EN8 Steel. J. Braz. Soc. Mech. Sci. Eng. 2021, 43, 378.
- 123. Karnan, B.; Kuppusamy, A.; Latchoumi, T.P.; Banerjee, A.; Sinha, A.; Biswas, A.; Subramanian, A.K. Multi-Response Optimization of Turning Parameters for Cryogenically Treated and Tempered WC–Co Inserts. J. Inst. Eng. India Ser. D 2022, 103, 263–274.
- 124. Senthilkumar, D. Deep Cryogenic Treatment of En 31 and En 8 Steel for the Development of Wear Resistance. Adv. Mater. Process. Technol. 2021, 8, 1769–1776.
- 125. Senthilkumar, D. Effect of Deep Cryogenic Treatment on Residual Stress and Mechanical Behaviour of Induction Hardened En 8 Steel. Adv. Mater. Process. Technol. 2016, 2, 427–436.
- 126. Arunkarthikeyan, K.; Balamurugan, K. Performance Improvement of Cryo Treated Insert on Turning Studies of AISI 1018 Steel Using Multi Objective Optimization. In Proceedings of the International Conference on Computational Intelligence for Smart Power System and Sustainable Energy, CISPSSE 2020, Keonjhar, India, 29–31 July 2020.
- 127. Wigley, D.A. The Metallurgical Structure and Mechanical Properties at Low Temperature of Nitronic 40 with Particular Reference to Its Use in the Construction of Models for Cryogenic Wind Tunnels; National Aeronautics and Space Administration: Hampton, VA, USA, 1982.
- 128. Gaddam, S.; Haridas, R.S.; Sanabria, C.; Tammana, D.; Berman, D.; Mishra, R.S. Friction Stir Welding of SS 316 LN and Nitronic 50 Jacket Sections for Application in Superconducting Fusion Magnet Systems. Mater. Des. 2022, 221, 110949.
- 129. Sastry, C.C.; Hariharan, P.; Pradeep Kumar, M.; Muthu Manickam, M.A. Experimental Investigation on Boring of HSLA ASTM A36 Steel under Dry, Wet, and Cryogenic Environments. Mater. Manuf. Process. 2019, 34, 1352–1379.
- 130. Y Chow, J.G.; Klamut, C.J. Properties of Cast C£-8 Stainless-Steel Weldments at Cryogenic Temperatures; Brookhaven National Lab.: Upton, NY, USA, 1981.
- 131. Thornton, R.; Slatter, T.; Jones, A.H.; Lewis, R. The Effects of Cryogenic Processing on the Wear Resistance of Grey Cast Iron Brake Discs. Wear 2011, 271, 2386–2395.
- Franco Steier, V.; Kalombo Badibanga, R.; Roberto Moreira Da Silva, C.; Magalhães Nogueira, M.; Araújo, J.A. Effect of Chromium Nitride Coatings and Cryogenic Treatments on Wear and Fretting Fatigue Resistance of Aluminum. Electr. Power Syst. Res. 2014, 116, 322–329.
- 133. Kara, F.; Çiçek, A. Multiple Regression and ANN Models for Surface Quality of Cryogenically-Treated AISI 52100 Bearing Steel Micro Machining of Ti6Al4V and Inconel 718 View Project Improvement of Machining Precesses View Project. Artic. J. Balk. Tribol. Assoc. 2013, 19, 570– 584.

- 134. Gunes, I.; Cicek, A.; Aslantas, K.; Kara, F. Effect of Deep Cryogenic Treatment on Wear Resistance of AISI 52100 Bearing Steel. Trans. Indian Inst. Met. 2014, 67, 909–917.
- 135. Villa, M.; Pantleon, K.; Somers, M.A.J. Enhanced Carbide Precipitation during Tempering of Sub-Zero Celsius Treated AISI 52100 Bearing Steel. In Proceedings of the Heat Treat & Surface Engineering Conference & Expo, Chennai, India, May 16–18 2013; pp. 1–7.
- 136. Hong, S.Y.; Ding, Y. Micro-Temperature Manipulation in Cryogenic Machining of Low Carbon Steel. J. Mater. Process Technol. 2001, 116, 22–30.
- Jamali, A.R.; Khan, W.; Chandio, A.D.; Anwer, Z.; Jokhio, M.H.; Karachi, P. Effect of Cryogenic Treatment on Mechanical Properties of AISI 4340 and AISI 4140 Steel. J. Eng. Technol. 2019, 38, 2413–7219.
- 138. Lisiecki, A.; Ślizak, D.; Kukofka, A. Laser Cladding of Co-Based Metallic at Cryogenic Conditions. J. Achiev. Mater. Manuf. Eng. 2019, 95, 20–31.
- Keseler, H.; Westermann, I.; Kandukuri, S.Y.; Nøkleby, J.O.; Holmedal, B. Permanent Effect of a Cryogenic Spill on Fracture Properties of Structural Steels. IOP Conf. Ser. Mater. Sci. Eng. 2015, 102, 012004.
- 140. Abdin, A.; Feyzabi, K.; Hellman, O.; Nordström, H.; Rasa, D.; Thaung Tolförs, G.; Öqvist, P.-O. Methods to Create Compressive Stress in High Strength Steel Components; Ångströmlaboratoriet: Uppsala, Sweden, 2018.
- 141. Walters, C.L.; Alvaro, A.; Maljaars, J. The Effect of Low Temperatures on the Fatigue Crack Growth of S460 Structural Steel. Int. J. Fatigue 2016, 82, 110–118.
- 142. Wang, C.; Yi, Y.; Huang, S.; Dong, F.; He, H.; Huang, K.; Jia, Y. Experimental and Theoretical Investigation on the Forming Limit of 2024-O Aluminum Alloy Sheet at Cryogenic Temperatures. Met. Mater. Int. 2021, 27, 5199–5211.
- 143. Fiedler, T.; Al-Sahlani, K.; Linul, P.A.; Linul, E. Mechanical Properties of A356 and ZA27 Metallic Syntactic Foams at Cryogenic Temperature. J. Alloys Compd. 2020, 813, 152181.
- 144. Sagar, S.R.; Srikanth, K.M.; Jayasimha, R. Effect of Cryogenic Treatment and Heat Treatment on Mechanical and Tribological Properties of A356 Reinforced with SiC. Mater. Today Proc. 2021, 45, 184–190.
- 145. Zhao, Z.; Hong, S.Y. Cooling Strategies for Cryogenic Machining from a Materials Viewpoint. J. Mater. Eng. Perform. 1992, 1, 669–678.
- 146. Jovičević-Klug, M.; Jovičević-Klug, P.; Sever, T.; Feizpour, D.; Podgornik, B. Extraordinary Nanocrystalline Pb Whisker Growth from Bi-Mg-Pb Pools in Aluminum Alloy 6026 Moderated through Oriented Attachment. Nanomaterials 2021, 11, 1842.

- 147. Jovičević-Klug, M.; Tegg, L.; Jovičević-Klug, P.; Dražić, G.; Almásy, L.; Lim, B.; Cairney, J.M.; Podgornik, B. Multiscale Modification of Aluminum Alloys with Deep Cryogenic Treatment for Advanced Properties. J. Mater. Res. Technol. 2022, 21, 3062–3073.
- 148. Jovičević-Klug, M.; Verbovšek, T.; Jovičević-Klug, P.; Batič, B.Š.; Ambrožič, B.; Dražić, G.; Podgornik, B. Revealing the Pb Whisker Growth Mechanism from Al-Alloy Surface and Morphological Dependency on Material Stress and Growth Environment. Materials 2022, 15, 2574.
- 149. Wang, X.; Fan, X.; Chen, X.; Yuan, S. Forming Limit of 6061 Aluminum Alloy Tube at Cryogenic Temperatures. J. Mater. Process. Technol. 2022, 306, 117649.
- 150. Wang, X.; Fan, X.; Chen, X.; Yuan, S. Cryogenic Deformation Behavior of 6061 Aluminum Alloy Tube under Biaxial Tension Condition. J. Mater. Process. Technol. 2022, 303, 117532.
- 151. Bouzada, F.; Cabeza, M.; Merino, P.; Trillo, S. Effect of Deep Cryogenic Treatment on the Microstructure of an Aerospace Aluminum Alloy. Adv. Mat. Res. 2012, 445, 965–970.
- Mohan, K.; Suresh, J.A.; Ramu, P.; Jayaganthan, R. Microstructure and Mechanical Behavior of AI 7075-T6 Subjected to Shallow Cryogenic Treatment. J. Mater. Eng. Perform. 2016, 25, 2185– 2194.
- 153. Siyi, M.; Su, R.; Wang, K.; Yang, Y.; Qu, Y.; Li, R. Effect of Deep Cryogenic Treatment on Wear and Corrosion Resistance of an Al–Zn–Mg–Cu Alloy. Russ. J. Non-Ferr. Met. 2021, 62, 89–96.
- 154. Wei, L.; Wang, D.; Li, H.; Xie, D.; Ye, F.; Song, R.; Zheng, G.; Wu, S. Effects of Cryogenic Treatment on the Microstructure and Residual Stress of 7075 Aluminum Alloy. Metals 2018, 8, 273.
- 155. Zhang, P.; Liu, Z.; Liu, J.; Yu, J.; Mai, Q.; Yue, X. Effect of Aging plus Cryogenic Treatment on the Machinability of 7075 Aluminum Alloy. Vacuum 2023, 208, 111692.
- 156. Deshpande, Y.V.; Andhare, A.B.; Padole, P.M. How Cryogenic Techniques Help in Machining of Nickel Alloys? A Review. Mach. Sci. Technol. 2018, 22, 543–584.
- 157. Baig, A.; Jaffery, S.H.I.; Khan, M.A.; Alruqi, M. Statistical Analysis of Surface Roughness, Burr Formation and Tool Wear in High Speed Micro Milling of Inconel 600 Alloy under Cryogenic, Wet and Dry Conditions. Micromachines 2022, 14, 13.
- 158. Satyanarayana, K.; Krishna, B.R.; Bhargavi, M.; Vasuki, R.E.; Kiran, K.R. Taguchi Optimization in Machining Inconel 600 with WEDM Process Using Cryogenically Treated Brass Wire. E3S Web Conf. 2021, 309, 01110.
- Mandal, P.K.; Michael Saji, A.; Kurian Lalu, A.; Krishnan, A.; Nair, A.S.; Jacob, M.M. Microstructural Study and Mechanical Properties of TIG Welded Inconel 617 Superalloy. Mater. Today Proc. 2022, 62, 3561–3568.

- Akgün, M.; Demir, H. Optimization of Cutting Parameters Affecting Surface Roughness in Turning of Inconel 625 Superalloy by Cryogenically Treated Tungsten Carbide Inserts. SN Appl. Sci. 2021, 3, 277.
- 161. Yıldırım, Ç.V. Experimental Comparison of the Performance of Nanofluids, Cryogenic and Hybrid Cooling in Turning of Inconel 625. Tribol. Int. 2019, 137, 366–378.
- 162. Anburaj, R.; Pradeep Kumar, M. Experimental Studies on Cryogenic CO2 Face Milling of Inconel 625 Superalloy. Mater. Manuf. Process. 2020, 36, 814–826.
- 163. Makhesana, M.A.; Patel, K.M.; Khanna, N. Analysis of Vegetable Oil-Based Nano-Lubricant Technique for Improving Machinability of Inconel 690. J. Manuf. Process. 2022, 77, 708–721.
- 164. Jovičevič Klug, P.; Jovičević Klug, M.; Podgornik, B. Potential in Deep Cryogenic Treatment of Non-Ferrous Alloys. In Proceedings of the European Cryogenics Days 2021, Virtual Conference, 4 November 2021; Cryogenics Society of Europe: Darmstadt, Germany, 2021.
- 165. Palanisamy, A.; Jeyaprakash, N.; Sivabharathi, V.; Sivasankaran, S. Effects of Dry Turning Parameters of Incoloy 800H Superalloy Using Taguchi-Based Grey Relational Analysis and Modeling by Response Surface Methodology. Proc. Inst. Mech. Eng. Part C J. Mech. Eng. Sci. 2022, 236, 607–623.
- 166. Palanisamy, A.; Selvaraj, T.; Sivasankaran, S. Optimization of Turning Parameters of Machining Incoloy 800H Superalloy Using Cryogenically Treated Multilayer CVD-Coated Tool. Arab. J. Sci. Eng. 2018, 43, 4977–4990.
- 167. Palanisamy, A.; Selvaraj, T. Optimization of Turning Parameters for Surface Integrity Properties on Incoloy 800 h Superalloy Using Cryogenically Treated Multi-Layer Cvd Coated Tool. Surf. Rev. Lett. 2019, 26, 1850139.
- 168. Dhananchezian, M. Study the Machinability Characteristics of Nicked Based Hastelloy C-276 under Cryogenic Cooling. Measurement 2019, 136, 694–702.
- 169. Nas, E.; Kara, F. Optimization of EDM Machinability of Hastelloy C22 Super Alloys. Machines 2022, 10, 1131.
- 170. Akincioğlu, S.; Gökkaya, H.; Akincioğlu, G.; Karataş, M.A. Taguchi Optimization of Surface Roughness in the Turning of Hastelloy C22 Super Alloy Using Cryogenically Treated Ceramic Inserts. Proc. Inst. Mech. Eng. Part C J. Mech. Eng. Sci. 2020, 234, 3826–3836.
- 171. Ekambaram, P. Study of Mechanical and Metallurgical Properties of Hastelloy X at Cryogenic Condition. J. Mater. Res. Technol. 2019, 8, 6413–6419.
- 172. Wu, Y.; Yuan, X.; Wen, X.; Jiao, M. Body-Centered Cubic High-Entropy Alloys. In Materials Horizons: From Nature to Nanomaterials; Springer: Singapore, 2022; pp. 3–34.

- 173. Hu, W.; Dong, Z.; Wang, H.; Ahamad, T.; Ma, Z. Microstructure Refinement and Mechanical Properties Improvement in the W-Y2O3 Alloys via Optimized Freeze-Drying. Int. J. Refract. Met. Hard Mater. 2021, 95, 105453.
- 174. Yildiz, Y.; Sundaram, M.M.; Rajurkar, K.P.; Nalbant, M. The Effects of Cold and Cryogenic Treatments on the Machinability of Beryllium-Copper Alloy in Electro Discharge Machinability. In Proceedings of the 44th CIRP Conference on Manufacturing Systems, Madison, WI, USA, 1–3 June 2011.
- 175. Bagherzadeh, A.; Kuram, E.; Budak, E. Experimental Evaluation of Eco-Friendly Hybrid Cooling Methods in Slot Milling of Titanium Alloy. J. Clean. Prod. 2021, 289, 125817.
- 176. Uygur, I.; Gerengi, H.; Arslan, Y.; Kurtay, M. The Effects of Cryogenic Treatment on the Corrosion of AISI D3 Steel. Mater. Res. 2015, 18, 569–574.
- 177. Shinde, T.; Pruncu, C.; Dhokey, N.B.; Parau, A.C.; Vladescu, A. Effect of Deep Cryogenic Treatment on Corrosion Behavior of AISI H13 Die Steel. Materials 2021, 14, 7863.
- 178. Wang, Y.M.; Liang, Y.; Zhai, Y.D.; Zhang, Y.S.; Sun, H.; Liu, Z.G.; Su, G.Q. Study on the Role of Cryogenic Treatment on Corrosion and Wear Behaviors of High Manganese Austenitic Steel. J. Mater. Res. Technol. 2023, 24, 5271–5285.
- 179. Akhbarizadeh, A.; Amini, K.; Javadpour, S. Effects of Applying an External Magnetic Field during the Deep Cryogenic Heat Treatment on the Corrosion Resistance and Wear Behavior of 1.2080 Tool Steel. Mater. Des. 2012, 41, 114–123.
- 180. Wang, L.; Dong, C.; Cao, Y.; Liang, J.; Xiao, K.; Li, X. Co-Enhancing the Mechanical Property and Corrosion Resistance of Selective Laser Melted High-Strength Stainless Steel via Cryogenic Treatment. J. Mater. Eng. Perform. 2020, 29, 7052–7062.
- 181. Baldissera, P.; Delprete, C. Deep Cryogenic Treatment of AISI 302 Stainless Steel: Part II— Fatigue and Corrosion. Mater. Des. 2010, 31, 4731–4737.
- 182. Cai, Y.; Luo, Z.; Zeng, Y. Influence of Deep Cryogenic Treatment on the Microstructure and Properties of AISI304 Austenitic Stainless Steel A-TIG Weld. Sci. Technol. Weld. Join. 2016, 22, 236–243.
- 183. He, X.; Lü, X.-Y.; Wu, Z.-W.; Li, S.-H.; Yong, Q.-L.; Liang, J.-X.; Su, J.; Zhou, L.-X.; Li, J. M23C6 Precipitation and Si Segregation Promoted by Deep Cryogenic Treatment Aggravating Pitting Corrosion of Supermartensitic Stainless Steel. J. Iron Steel Res. Int. 2021, 28, 629–640.
- 184. Cabeza, M.; Feijoo, I.; Merino, P.; Trillo, S. Effect of the Deep Cryogenic Treatment on the Stress Corrosion Cracking Behaviour of AA 2017-T4 Aluminium Alloy. Mater. Corros. 2016, 67, 504–512.

Retrieved from https://encyclopedia.pub/entry/history/show/115284