

Contributor: Lidia Ester Santibáñez-Velásquez

valorization

 $\frac{1}{4}$

elements such as iron through magnetic concentration and copper through bioleaching [7][9][10]. This reprocessing of mine tailings by different technologies is being explored to make mining operations more sustainable [11]. Acid leaching is widely used in mineral extraction and the recycling of valuable metals [12]. Sulfuric acid is the best-known and most conventionally used leaching agent; however, some studies recommend hydrochloric acid since the presence of chloride ions is advantageous for copper extraction [9][13][14]. In addition, many studies are focused on copper recovery from slags. Dimitrijević et al. worked with hydrochloric acid concentration below 2 M and combined it with hydrogen peroxide on copper slag samples [15]. Chen et al. performed a similar study using, also with copper slag, an 11 M concentration of hydrochloric acid at temperatures above 80 °C [13].

Chilean researches have carried out the characterization of an iron-rich tailing and the extraction of metals through leaching[16]. They obtained the tailing sample from a tailing dam placed in the north of Chile. Specifically, the sample was taken from the wall of the tailing dam using the trial pits technique. Their results showed that 80% of the sample is approximately below an ASTM 60 mesh, corresponding to 250 µm, meaning that the particle size distribution is fine. The tailing particles are irregular, and the composition is based on silicates and iron oxides. The composition was mainly quartz, magnetite, orthoclase, and albite. They determined that the tailing contains a total iron grade of 19%, which is a high concentration of iron. They focused on some interesting elements such as copper, aluminum, calcium and magnesium. They found that if the tailing is submitted to acid treatment with hydrochloric acid (HCl), a liquid solution and an insoluble solid are generated. Both phases (liquid and solid) represent an opportunity to produce valuable secondary species [17][18]. Regarding the acid solution, it is rich in a variety of metals, specially iron. As for the insoluble solid, the samples had an irregular morphology composed mainly of silica, having mainly orthoclase, quartz, and albite.

2. Mineral extraction

Mineral extraction brings with it the generation of waste, such as tailings and slags. It is important to find new ways to treat these wastes and extract as many valuable species as possible. The variability of elements in each sample makes leaching a complex process. Hydrochloric acid leaching is an alternative when it is desired to extract more than one element at a time. The tailings of northern Chile contain an important amount of iron and other valuable species, such as copper and aluminum, which can be extracted through leaching with hydrochloric acid. The most relevant condition in this process is the acid concentration, due to its effect on the extraction of metals. Conditions can be selected according to the element that wants to be obtained, e.g., if a high iron extraction is wanted, a high acid concentration should be applied, while on the contrary, if a high extraction of aluminum is wanted, a low acid concentration should be used. The variables time and temperature do not show a relevant influence on the iron concentration, so it can be considered that it presents a constant behavior. Within the ranges studied, the conditions of 9 M acid concentration, 16 h reaction time, and a temperature of 25 °C were selected as the optimum leaching parameters. This process differs from traditional leaching by using hydrochloric acid instead of sulfuric acid; in addition, the raw material is a residue from a metallurgical process instead of mined ore. This proves that valuable elements such as iron, copper, and aluminum, along with calcium and magnesium, can be extracted from copper tailings for further valorization. The silicates obtained in the insoluble portion show low iron concentrations

and could be used in other applications such as additives in the construction industry. It is important that these processes are circular, finding uses for waste such as tailings and also for the by-products of the tailing leaching. Environmental care is fundamental, so the production of by-products that are harmful to ecosystems must be avoided.

References

1. Aznar-Sánchez, J.A.; García-Gómez, J.J.; Velasco-Muñoz, J.F. Mining Waste and Its Sustainable Management: Advances in Worldwide Research. *Minerals* 2018, 8, 284.
2. Reichl, C.; Schatz, M.; Zsak, G. World Mining Data. *Miner. Prod.* 2017, 32, 1–261.
3. Cortés, S.; Soto, E.E.; Ordóñez, J.I. Recovery of Copper from Leached Tailing Solutions by Biosorption. *Minerals* 2020, 10, 158.
4. Upadhyay, A.; Laing, T.; Kumar, V.; Dora, M. Exploring barriers and drivers to the implementation of circular economy practices in the mining industry. *Resour. Policy* 2021, 72, 102037.
5. Kinnunen, P.; Kaksonen, A.H. Towards circular economy in mining: Opportunities and bottlenecks for tailings valorization. *J. Clean. Prod.* 2019, 228, 153–160.
6. Araya, N.; Kraslawski, A.; Cisternas, L.A. Towards mine tailings valorization: Recovery of critical materials from Chilean mine tailings. *J. Clean. Prod.* 2020, 263, 121555.
7. Valderrama, L.; Santander, M.; Zazzali, B.; Carmona, M. Concentración Magnética Aplicada a Relaves de cobre. *HOLOS* 2014, 6, 37–44.
8. Lacassie, J.P.; Vivallo, W.; Díaz, A.; Ruiz-del-Solar, J. Geoquímica de yacimientos metálicos y de sedimentos, de las regiones de Atacama y Coquimbo, norte de Chile. In *Proceedings of the XIV Congreso Geológico Chileno*, La Serena, Chile, 4–8 October 2015; pp. 429–432.
9. Ristović, I.; Štyriaková, D.; Štyriaková, I.; Šuba, J.; Širadović, E. Bioleaching Process for Copper Extraction from Waste in Alkaline and Acid Medium. *Minerals* 2022, 12, 100.
10. Vargas, F. Copper Tailings as Supplementary Cementitious Material: Activation, Leaching and Environmental Behaviour; Pontificia Universidad Católica de Chile: Santiago de Chile, Chile, 2020.
11. Godirilwe, L.L.; Haga, K.; Altansukh, B.; Takasaki, Y.; Ishiyama, D.; Trifunovic, V.; Avramovic, L.; Jonovic, R.; Stevanovic, Z.; Shibayama, A. Copper Recovery and Reduction of Environmental Loading from Mine Tailings by High-Pressure Leaching and SX-EW Process. *Metals* 2021, 11, 1335.
12. Wang, J.; Zhang, Y.; Yu, L.; Cui, K.; Fu, T.; Mao, H. Effective separation and recovery of valuable metals from waste Ni-based batteries: A comprehensive review. *Chem. Eng. J.* 2022, 439,

135767.

13. Chen, M.; Han, Z.; Wang, L. Recovery of valuable metals from copper slag by hydrometallurgy. *Adv. Mater. Res.* 2011, 402, 35–40.
14. Goryachev, A.; Svetlov, A.; Kompanchenko, A.; Makarov, D. Sulfuric Acid Granulation of Copper—Nickel Ore Tailings: Leaching of Copper and Nickel in the Presence of Sulfide Oxidation Activators. *Minerals* 2022, 12, 129.
15. Dimitrijević, M.; Urošević, D.; Milić, S.; Sokić, M.; Marković, R. Dissolution of copper from smelting slag by leaching in chloride media. *J. Min. Metall. Sect. B Metall.* 2017, 53, 407–412.
16. Santibáñez-Velásquez, L.E.; Guzmán, A.; Morel, M.J.; Extraction of Iron and Other Metals from Copper Tailings through Leaching. *Metals* **2022**, 12, 1-11, <https://doi.org/10.3390/met12111924>.
17. Adrianto, L.R.; Pfister, S. Prospective environmental assessment of reprocessing and valorization alternatives for sulfidic copper tailings. *Resour. Conserv. Recycl.* 2022, 186, 106567.
18. Leiva, E.; Cayazzo, M.; Dávila, L.; Torres, M.; Ledezma, C. Acid Mine Drainage Dynamics from a Paste Tailing Deposit: Effect of Sulfate Content on the Consistency and Chemical Stability after Storage. *Metals* 2021, 11, 860.

Retrieved from <https://www.encyclopedia.pub/entry/history/show/85122>