

Ni-Based Catalysts Supported on Mg-Al Mixed Oxides

Subjects: [Chemistry](#), [Applied](#)

Contributor: Soroosh Saeedi , Xuan Trung Nguyen , Filippo Bossola , Claudio Evangelisti , Vladimiro Dal Santo

Ni-based catalysts supported on Mg-Al mixed oxides (Mg(Al)O) have been intensively investigated as catalysts for CH₄ reforming processes (i.e., steam reforming (SMR) and dry reforming (DRM)), which are pivotal actors in the expanding H₂ economy.

hydrogen

nickel catalysts

magnesium aluminum mixed oxide

Mg(Al)O

1. Introduction

To overcome the identified challenges in catalytic reforming systems, the selection of the catalyst support plays a crucial role during the catalyst development [1][2][3]. In addition to coke limiting ability, reforming catalysts must also meet stringent requirements due to the harsh conditions required of the processes (high temperature, high pressure, and presence of steam) [4][5]. Common oxide supports are Al₂O₃, MgO, and their corresponding mixed oxides [4]. Because of its high surface area, thermal and chemical stability, and strong interaction with Ni, Al₂O₃ is one of the most studied supports [6][7]. Indeed, commercially available catalysts for traditional steam reforming (SMR) are mainly constituted by Ni supported on Al₂O₃ [8]. MgO support is also widely studied, particularly in dry reforming (DRM), because its high basicity is beneficial for adsorbing CO₂, which in turn enhances the reforming activity and the coke removal rate [9][10]. Moreover, the ability of MgO to form a strongly interacting solid solution with NiO improves the catalyst stability and resistance to sintering [11][12].

As for the active metallic constituents, bimetallic systems are attracting considerable research interest thanks to the possible promotional effect of the second (or third) metal on the processes and/or the presence of synergetic effects between the metals [13][14][15]. Particularly for Ni-based catalysts, noble, alkaline, and rare earth metal promoters are the subjects of many studies and demonstrate promising improvements. Among those, the addition of small amounts of noble metals to Ni catalysts is beneficial while remaining cost competitive [16]. The addition of Pt, Ru, and Pd improves reducibility, may provoke an auto-activation of the catalyst, and reduces the coke formation [16]. On the other hand, the addition of Group 11 metals (Au, Ag) reduces the Ni activity but extends the catalyst's lifetime by inhibiting the coke formation [17].

In addition to the selection of the active metal, support, and promoters, the way the catalyst is prepared also plays an important role in determining its morphological and structural features and, as a result, its catalytic performance [17][18][19]. This is particularly true when preparing Mg-Al mixed oxides, which can form several crystal phases and can have different morphological characteristics [20][21]. Hence, a thorough understanding of each parameter in

traditional synthesis procedures as well as the exploration of innovative preparation approaches are both highly desirable to improve homo- and bimetallic Ni catalysts supported on Mg(Al)O for SMR and DRM.

Metal–support interaction is arguably one of the most critical aspects impacting both the activity and the stability of heterogeneous catalysts, especially when used in high-temperature processes. The interaction of Ni with the support is a somewhat textbook example of the tradeoffs to be considered when preparing a heterogeneous catalyst. If, on the one hand, a weak interaction is good for the catalytic activity because it does not impair the Ni reducibility, it may be insufficient to stabilize the nanoparticles against sintering [22][23]. It is also true, however, that it is hard to obtain small Ni nanoparticles, and thus a high number of catalytically active sites with Ni interacting too weakly with the support can be found. In other words, a strong interaction with the support helps suppress the overgrowth of the particles, thereby enhancing their stability at high reaction temperatures, but could also lead to Ni nanoparticles that are hard to reduce, which may limit the availability of metallic Ni [19][24].

2. Ni-Support Interaction in Ni(M)/Mg(Al)O Catalysts

Ni-based catalysts are generally prepared as NiO followed by reduction, but the final form of the catalyst is heavily influenced by the composition of the Mg(Al)O support because Ni interacts very differently with Al and Mg oxides.

NiO is known to form a stable spinel nickel aluminate with Al_2O_3 after heat treatment, denoted as NiAl_2O_4 [25]. In Ni-Al-O systems, three phases of Ni- Al_2O_3 can be observed: “free” NiO particles, NiO weakly interacting with Al_2O_3 , and NiAl_2O_4 spinel. The order is based on the strength of interaction between Ni and Al. Temperature-programmed reduction (TPR) can be used to identify the phases of Ni in Al_2O_3 . Due to the difference in bond strength, each phase displays reduction features in a specific temperature range. Reduction peaks occurring between 300 and 350 °C are originated by the reduction of “free” NiO to metallic Ni, whilst weakly interacting NiO- Al_2O_3 is reduced around 500–600 °C. The reduction of Ni^{2+} present in the spinel phase (NiAl_2O_4) can only be observed at temperatures higher than 800 °C. The formation of such three phases depends largely on calcination temperature, Ni loading, and the preparation method. Generally, high calcination temperatures favor the formation of spinel phases with stronger interaction between Ni and Al_2O_3 [26][27].

With MgO, NiO can form an ideal NiO-MgO solid solution in the whole range of concentrations due to the similar ionic radii of Ni^{2+} (69 pm) and Mg^{2+} (72 pm) [28]. In the solid solution, the interaction of Ni with MgO is particularly strong, resulting in a Ni phase much harder to be reduced. Conventionally, the reduction of NiO-MgO occurs above 800 °C with long reduction times.

In addition to the interactions between Ni and each oxide component, the mixed oxide itself can also form the MgAl_2O_4 spinel phase during the catalyst synthesis [29][30], which provides high surface area, good thermal stability, and strong interaction with Ni [19].

Another important aspect of Mg(Al)O systems is the ability to form hydrotalcite. Hydrotalcite is a double-layered lamellar hydroxide (LDH) of Mg and Al with the formula $\text{Mg}_6\text{Al}_2(\text{OH})_{16}\text{CO}_3 \cdot 4\text{H}_2\text{O}$ [31]. It is demonstrated that

materials derived from hydrotalcites are promising for various catalytic processes including CH₄ reforming [32][33].

3. Monometallic Ni/Mg(Al)O Catalysts for SMR and DRM

3.1. Synthesis of Ni/Mg(Al)O Catalysts by Conventional Approaches

3.1.1. Effect of Ni Loading and Composition Ratio

Ni loading and composition ratio play an important role in the characteristics of the catalysts: High Ni loadings may imply higher activity, but they may result in larger particles, which promote coke formation [34][35][36][37][38].

The study by Guo et al. showed that a catalyst with a low Ni content is not stable in DRM, while the conversion is positively correlated with Ni content only up to 15 wt.% [39]. As expected, above that loading, the coke formation becomes severe. A similar trend of coke deposition was found by Alipour et al. while studying impregnated Ni/Mg(Al)O catalysts obtained by wet impregnation [40]. They showed that after calcination, NiO segregated when above the 15 wt.% of Ni loading. The amount of carbon deposited scaled with the Ni content, but the reforming activity did not. Catalysts prepared via co-precipitation showed a similar behavior [41].

Qi et al. used Ni/Mg(Al)O prepared by the co-precipitation technique and tested them in SMR in comparison with wet impregnated catalysts with varied divalent/trivalent cation molar ratios (Ni+Mg)/Al in the precursors [42]. They reported that the optimal (Ni+Mg)/Al molar ratio in the LDH precursor for SMR is three. The resulting catalyst exhibited the best activity because of its high surface area and high Ni dispersion upon reduction.

3.1.2. Effect of Heat Treatment

Both calcination and reduction conditions have a major impact on the physicochemical properties of the resulting catalyst. As stated earlier, higher calcination temperatures favor the formation of stable phases, such as spinel NiAl₂O₄ or NiO-MgO solid solution. A high calcination temperature can enhance the stability and interaction between components but can also decrease the surface area, thus causing a collapse of the pores, and particle sintering [43][44][45][46]. On the contrary, low reduction temperatures may not guarantee the generation of sufficient active species. Hence, various studies have been devoted to the influence of thermal pretreatments on the final structure of the catalysts.

The calcination temperature was studied on NiO-MgO systems for DRM [47][48]. At low calcination temperatures, the material contained weakly interacting NiO species, while at 800 °C NiO bonds strongly with MgO in the form of a solid solution. The strong interaction increases the strength of CO₂ absorption at low reaction temperatures, thus enhancing the activity and stability of the catalyst. The effect of Mg precursors and heat treatment was also studied by Ruckenstein and Hu [49].

3.2. Synthesis of Ni/Mg(Al)O Catalysts by Advanced Methods

Besides the more common methods mentioned above, other approaches aimed at obtaining strictly controlled morphological, structural, and textural properties of both the metal active phase.

Among them, the sol-gel method has been extensively investigated [50][51][52][53]. The catalysts obtained via this approach are typically characterized by high surface area, narrow size distribution, high thermal resistance, and homogeneous composition of the mixed oxides when compared to conventional synthesis methods [54][55]. González et al. utilized LDHs prepared in this way as precursors for DRM [56]. Upon mild thermal treatment, the hydrotalcite collapsed and formed nanosphere structures of mixed NiO and Mg(Ni)AlO periclase without the formation of NiAl₂O₄. The catalyst with 15 wt.% Ni and calcined at 650 °C showed the best activity and low carbon formation in DRM.

Another attractive synthesis approach is the aerogel method. This approach enables the synthesis of exceptionally high surface area and thermally stable materials [57]. Suh et al. used aerogel Al₂O₃ as supports for DRM [58]. The high surface area Al₂O₃ was prepared by supercritical CO₂ drying of alcogels. The aerogel-based Ni/Al₂O₃ catalysts showed high activity and enhanced stability against coking compared to the impregnated ones. The scholars assigned such improvements to the high surface area and uniform distribution of the active sites. The follow-up paper investigated the metal loading on this aerogel catalyst, again highlighting that too a high metal content resulted in large particle sizes, which in turn promote coke formation [37].

4. Bimetallic Ni-M/Mg(Al)O Catalysts for Reforming Reactions

4.1. Bimetallic Ni-M/Mg(Al)O Catalysts for SMR

Bimetallic catalysts are a promising area of research because they have improved properties compared to their parent metals, resulting in some cases in catalysts with higher selectivity, activity, and stability. Precious metals with high reforming activity and low coking tendency have been studied as promoters for Ni-based catalysts [59][60][61][62][63][64]. Among different synthesis methods reported for CH₄ reforming catalysts (i.e., self-combustion, ion exchange, sol-gel, microemulsion, precipitation, wet impregnation, and colloidal), precipitation and impregnation methods are the most common ones [65][66][67][68][69].

The role of Pt as a promoter in Ni/Mg(Al)O catalysts has been investigated in different synthetic ways both for metal deposition and support preparation. Foletto et al. reported a catalyst synthesized by the sequential impregnation method while using the sol-gel method via alkoxide hydrolysis to synthesize the Mg(Al)O support [70]. XRD analyses revealed that as the calcination temperature of the support increased, the size of the crystallites rose exponentially, and the formation of the spinel phase occurred at temperatures higher than 600 °C. The formation of the pure spinel phase and a higher resistance to sintering were observed for calcination temperatures exceeding 700 °C. The catalytic activity of the catalyst as a function of different Pt content showed that 0.1 wt.% Pt is optimal compared to catalysts at higher Pt loadings. According to TPR results, Ni reduction peaks shifted to

lower temperatures for small amounts of Pt (0.05–0.1 wt.%), while no significant changes were observed when increasing the Pt content.

4.2. Bimetallic Ni-M/Mg(Al)O Catalysts for DRM

The presence of a metallic phase is necessary for the dissociative adsorption of CH₄ and for the generation of H₂ as well as chemisorbed carbon species during DRM. Some bimetallic systems are also capable of lowering the activation energy of the rate-limiting step [71][72]. A kinetic study by Niu et al. revealed that the addition of Pt to Ni reduces the activation energy for CH₄ dissociation and lowers moderately the CO₂ dissociation barrier energy, resulting in higher catalytic activity [73]. Re and Ru have been also described as active sites for CO₂ activation, which, due to their electron-rich properties, can donate electrons to the CO₂ antibonding orbitals and facilitate the reaction by weakening the C-O bond [74].

In another impregnation synthesis process, Pt was loaded on a Ni/Mg(Al)O catalyst using glow discharge plasma pretreatment after impregnation and before calcination [75]. Such treatment was useful to improve the Ni dispersion but inhibited its reduction. The addition of Pt helped in this sense and in fact the bimetallic, plasma-treated Pt-Ni/Mg(Al)O catalyst demonstrated a higher conversion of both the reactant and a higher H₂ yield. An improved resistance toward coke formation was also reported by the scholars. The presence of Pt resulted in smaller Ni NPs in the fresh materials, while the plasma treatment was critical to prevent sintering. It is worth noting the filamentous carbon formations on the spent Ni/Mg(Al)O catalyst, which on the contrary cannot be seen on the spent P-Ni-Pt/Mg(Al)O catalyst. The scholars suggest that this was due to the presence of Pt more than the plasma treatment, and specifically to an altered dissociative adsorption capacity of CH₄ [76][77].

In general, many alloying effects of Ni-based catalysts with base metals and Ni-based catalysts with noble metals have been reported in DRM and SMR to improve the dispersion and reducibility of the supported metal, modify the catalytic performance such as activity and selectivity, and improve the resistance to carbon deposition, sulfur poisoning, sintering, and so on.

References

1. Roussi re, T.; Schulz, L.; Schelkle, K.M.; Wasserschaff, G.; Milanov, A.; Schwab, E.; Deutschmann, O.; Jentys, A.; Lercher, J.; Schunk, S.A. Structure–Activity Relationships of Nickel–Hexaaluminates in Reforming Reactions Part II: Activity and Stability of Nanostructured Nickel–Hexaaluminate-Based Catalysts in the Dry Reforming of Methane. *ChemCatChem* 2014, 6, 1447–1452.
2. Ginsburg, J.M.; Pi a, J.; El Solh, T.; de Lasa, H.I. Coke Formation over a Nickel Catalyst under Methane Dry Reforming Conditions: Thermodynamic and Kinetic Models. *Ind. Eng. Chem. Res.* 2005, 44, 4846–4854.

3. Titus, J.; Roussi re, T.; Wasserschaff, G.; Schunk, S.; Milanov, A.; Schwab, E.; Wagner, G.; Oeckler, O.; Gl aser, R. Dry Reforming of Methane with Carbon Dioxide over NiO–MgO–ZrO₂. *Catal. Today* 2016, 270, 68–75.
4. Rostrup-Nielsen, J.; Christiansen, L.J. Concepts in Syngas Manufacture. *Catal. Sci. Ser.* 2011, 10, 392.
5. Aramouni, N.A.K.; Touma, J.G.; Tarboush, B.A.; Zeaiter, J.; Ahmad, M.N. Catalyst Design for Dry Reforming of Methane: Analysis Review. *Renew. Sustain. Energy Rev.* 2018, 82, 2570–2585.
6. Van Hook, J.P. Methane-Steam Reforming. *Catal. Rev.* 1980, 21, 1–51.
7. Hu, Y.H. Advances in Catalysts for CO₂ Reforming of Methane. In *Advances in CO₂ Conversion and Utilization*; American Chemical Society: Washington, DC, USA, 2010; pp. 155–174.
8. Lee, S. *Methane and Its Derivatives*; CRC Press: Boca Raton, FL, USA, 2017.
9. Hu, Y.H.; Ruckenstein, E. Binary MgO-Based Solid Solution Catalysts for Methane Conversion to Syngas. *Catal. Rev.* 2002, 44, 423–453.
10. Fan, M.-S.; Abdullah, A.Z.; Bhatia, S. Catalytic Technology for Carbon Dioxide Reforming of Methane to Synthesis Gas. *ChemCatChem* 2009, 1, 192–208.
11. Muraza, O.; Galadima, A. A Review on Coke Management during Dry Reforming of Methane. *Int. J. Energy Res.* 2015, 39, 1196–1216.
12. Arora, S.; Prasad, R. An Overview on Dry Reforming of Methane: Strategies to Reduce Carbonaceous Deactivation of Catalysts. *RSC Adv.* 2016, 6, 108668–108688.
13. De, S.; Zhang, J.; Luque, R.; Yan, N. Ni-Based Bimetallic Heterogeneous Catalysts for Energy and Environmental Applications. *Energy Environ. Sci.* 2016, 9, 3314–3347.
14. Alonso, D.M.; Wettstein, S.G.; Dumesic, J.A. Bimetallic Catalysts for Upgrading of Biomass to Fuels and Chemicals. *Chem. Soc. Rev.* 2012, 41, 8075–8098.
15. Dal Santo, V.; Gallo, A.; Naldoni, A.; Guidotti, M.; Psaro, R. Bimetallic Heterogeneous Catalysts for Hydrogen Production. *Catal. Today* 2012, 197, 190–205.
16. Li, D.; Nakagawa, Y.; Tomishige, K. Methane Reforming to Synthesis Gas over Ni Catalysts Modified with Noble Metals. *Appl. Catal. A Gen.* 2011, 408, 1–24.
17. Usman, M.; Daud, W.W.; Abbas, H.F. Dry Reforming of Methane: Influence of Process Parameters—A Review. *Renew. Sustain. Energy Rev.* 2015, 45, 710–744.
18. Puxley, D.C.; Kitchener, I.J.; Komodromos, C.; Parkyns, N.D. The Effect Of Preparation Method Upon The Structures, Stability And Metal/Support Interactions In Nickel/Alumina Catalysts. In *Studies in Surface Science and Catalysis*; Poncelet, G., Grange, P., Jacobs, P.A., Eds.; Elsevier: Amsterdam, The Netherlands, 1983; Volume 16, pp. 237–271.

19. Azancot, L.; Bobadilla, L.F.; Santos, J.L.; Córdoba, J.M.; Centeno, M.A.; Odriozola, J.A. Influence of the Preparation Method in the Metal-Support Interaction and Reducibility of Ni-Mg-Al Based Catalysts for Methane Steam Reforming. *Int. J. Hydrogen Energy* 2019, 44, 19827–19840.
20. Kwon, D.; Kang, J.Y.; An, S.; Yang, I.; Jung, J.C. Tuning the Base Properties of Mg–Al Hydrotalcite Catalysts Using Their Memory Effect. *J. Energy Chem.* 2020, 46, 229–236.
21. Bossola, F.; Evangelisti, C.; Allieta, M.; Psaro, R.; Recchia, S.; Dal Santo, V. Well-Formed, Size-Controlled Ruthenium Nanoparticles Active and Stable for Acetic Acid Steam Reforming. *Appl. Catal. B Environ.* 2016, 181, 599–611.
22. Adamu, S.; Bawah, A.-R.; Muraza, O.; Malaibari, Z.; Hossain, M.M. Effects of Metal Support Interaction on Dry Reforming of Methane over Ni/Ce-Al₂O₃ Catalysts. *Can. J. Chem. Eng.* 2020, 98, 2425–2434.
23. Kumar, R.; Kumar, K.; Pant, K.K.; Choudary, N.V. Tuning the Metal-Support Interaction of Methane Tri-Reforming Catalysts for Industrial Flue Gas Utilization. *Int. J. Hydrogen Energy* 2020, 45, 1911–1929.
24. Özdemir, H.; Öksüzömer, M.A.F.; Gürkaynak, M.A. Effect of the Calcination Temperature on Ni/MgAl₂O₄ Catalyst Structure and Catalytic Properties for Partial Oxidation of Methane. *Fuel* 2014, 116, 63–70.
25. Li, C.; Chen, Y.-W. Temperature-Programmed-Reduction Studies of Nickel Oxide/Alumina Catalysts: Effects of the Preparation Method. *Thermochim. Acta* 1995, 256, 457–465.
26. Rynkowski, J.M.; Paryjczak, T.; Lenik, M. On the Nature of Oxidic Nickel Phases in NiO/γ-Al₂O₃ Catalysts. *Appl. Catal. A Gen.* 1993, 106, 73–82.
27. Zhang, C.; Hu, X.; Zhang, Z.; Zhang, L.; Dong, D.; Gao, G.; Westerhof, R.; Syed-Hassan, S.S.A. Steam Reforming of Acetic Acid over Ni/Al₂O₃ Catalyst: Correlation of Calcination Temperature with the Interaction of Nickel and Alumina. *Fuel* 2018, 227, 307–324.
28. Kuzmin, A.; Mironova, N. Composition Dependence of the Lattice Parameter in Solid Solutions. *J. Phys. Matter* 1998, 10, 7937–7944.
29. Gac, W. Acid–Base Properties of Ni–MgO–Al₂O₃ Materials. *Appl. Surf. Sci.* 2011, 257, 2875–2880.
30. Coleman, L.J.I.; Epling, W.; Hudgins, R.R.; Croiset, E. Ni/Mg–Al Mixed Oxide Catalyst for the Steam Reforming of Ethanol. *Appl. Catal. A Gen.* 2009, 363, 52–63.
31. Williams, G.R.; O'Hare, D. Towards Understanding, Control and Application of Layered Double Hydroxide Chemistry. *J. Mater. Chem.* 2006, 16, 3065–3074.
32. Cavani, F.; Trifirò, F.; Vaccari, A. Hydrotalcite-Type Anionic Clays: Preparation, Properties and Applications. *Catal. Today* 1991, 11, 173–301.

33. Sikander, U.; Sufian, S.; Salam, M.A. A Review of Hydrotalcite Based Catalysts for Hydrogen Production Systems. *Int. J. Hydrogen Energy* 2017, 42, 19851–19868.
34. Touahra, F.; Sehailia, M.; Ketir, W.; Bachari, K.; Chebout, R.; Trari, M.; Cherifi, O.; Halliche, D. Effect of the Ni/Al Ratio of Hydrotalcite-Type Catalysts on Their Performance in the Methane Dry Reforming Process. *Appl. Petrochem. Res.* 2016, 6, 1–13.
35. Li, L.; Zhang, L.; Zhang, Y.; Li, J. Effect of Ni Loadings on the Catalytic Properties of Ni/MgO(111) Catalyst for the Reforming of Methane with Carbon Dioxide. *J. Fuel Chem. Technol.* 2015, 43, 315–322.
36. Wang, Y.; Wang, H.; Dam, A.H.; Xiao, L.; Qi, Y.; Niu, J.; Yang, J.; Zhu, Y.-A.; Holmen, A.; Chen, D. Understanding Effects of Ni Particle Size on Steam Methane Reforming Activity by Combined Experimental and Theoretical Analysis. *Catal. Today* 2019, 355, 139–147.
37. Kim, J.-H.; Suh, D.J.; Park, T.-J.; Kim, K.-L. Effect of Metal Particle Size on Coking during CO₂ Reforming of CH₄ over Ni–Alumina Aerogel Catalysts. *Appl. Catal. A Gen.* 2000, 197, 191–200.
38. Vogt, C.; Kranenborg, J.; Monai, M.; Weckhuysen, B.M. Structure Sensitivity in Steam and Dry Methane Reforming over Nickel: Activity and Carbon Formation. *ACS Catal.* 2020, 10, 1428–1438.
39. Guo, J.; Lou, H.; Zhao, H.; Chai, D.; Zheng, X. Dry Reforming of Methane over Nickel Catalysts Supported on Magnesium Aluminate Spinel. *Appl. Catal. A Gen.* 2004, 273, 75–82.
40. Alipour, Z.; Rezaei, M.; Meshkani, F. Effect of Ni Loadings on the Activity and Coke Formation of MgO-Modified Ni/Al₂O₃ Nanocatalyst in Dry Reforming of Methane. *J. Energy Chem.* 2014, 23, 633–638.
41. Akbari, E.; Alavi, S.M.; Rezaei, M. Synthesis Gas Production over Highly Active and Stable Nanostructured Ni-MgO-Al₂O₃ Catalysts in Dry Reforming of Methane: Effects of Ni Contents. *Fuel* 2017, 194, 171–179.
42. Qi, Y.; Cheng, Z.; Zhou, Z. Steam Reforming of Methane over Ni Catalysts Prepared from Hydrotalcite-Type Precursors: Catalytic Activity and Reaction Kinetics. *Chin. J. Chem. Eng.* 2015, 23, 76–85.
43. Munnik, P.; de Jongh, P.E.; de Jong, K.P. Recent Developments in the Synthesis of Supported Catalysts. *Chem. Rev.* 2015, 115, 6687–6718.
44. Roh, H.-S.; Eum, I.-H.; Jeong, D.-W.; Yi, B.E.; Na, J.-G.; Ko, C.H. The Effect of Calcination Temperature on the Performance of Ni/MgO–Al₂O₃ Catalysts for Decarboxylation of Oleic Acid. *Catal. Today* 2011, 164, 457–460.
45. Smoláková, L.; Kout, M.; Koudelková, E.; Čapek, L. Effect of Calcination Temperature on the Structure and Catalytic Performance of the Ni/Al₂O₃ and Ni–Ce/Al₂O₃ Catalysts in Oxidative

- Dehydrogenation of Ethane. *Ind. Eng. Chem. Res.* 2015, 54, 12730–12740.
46. Khan, A.I.; O'Hare, D. Intercalation Chemistry of Layered Double Hydroxides: Recent Developments and Applications. *J. Mater. Chem.* 2002, 12, 3191–3198.
 47. Feng, J.; Ding, Y.; Guo, Y.; Li, X.; Li, W. Calcination Temperature Effect on the Adsorption and Hydrogenated Dissociation of CO₂ over the NiO/MgO Catalyst. *Fuel* 2013, 109, 110–115.
 48. Millet, M.-M.; Tarasov, A.V.; Girgsdies, F.; Algara-Siller, G.; Schlögl, R.; Frei, E. Highly Dispersed NiO/NixMg_{1-x}O Catalysts Derived from Solid Solutions: How Metal and Support Control the CO₂ Hydrogenation. *ACS Catal.* 2019, 9, 8534–8546.
 49. Ruckenstein, E.; Hang Hu, Y. The Effect of Precursor and Preparation Conditions of MgO on the CO₂ Reforming of CH₄ over NiO/MgO Catalysts. *Appl. Catal. A Gen.* 1997, 154, 185–205.
 50. Ward, D.A.; Ko, E.I. Preparing Catalytic Materials by the Sol-Gel Method. *Ind. Eng. Chem. Res.* 1995, 34, 421–433.
 51. Frenzer, G.; Maier, W.F. Amorphous Porous Mixed Oxides: Sol-Gel Ways to a Highly Versatile Class of Materials and Catalysts. *Annu. Rev. Mater. Res.* 2006, 36, 281–331.
 52. Othman, M.R.; Helwani, Z.; Martunus; Fernando, W.J.N. Synthetic Hydrotalcites from Different Routes and Their Application as Catalysts and Gas Adsorbents: A Review. *Appl. Organomet. Chem.* 2009, 23, 335–346.
 53. Miller, J.B.; Ko, E.I. Control of Mixed Oxide Textural and Acidic Properties by the Sol-Gel Method. *Catal. Today* 1997, 35, 269–292.
 54. Otero Areán, C.; Peñarroya Mentruit, M.; López López, A.J.; Parra, J.B. High Surface Area Nickel Aluminate Spinel Prepared by a Sol–Gel Method. *Colloids Surf. A Physicochem. Eng. Asp.* 2001, 180, 253–258.
 55. Li, H.; Xu, H.; Wang, J. Methane Reforming with CO₂ to Syngas over CeO₂-Promoted Ni/Al₂O₃-ZrO₂ Catalysts Prepared via a Direct Sol-Gel Process. *J. Nat. Gas Chem.* 2011, 20, 1–8.
 56. González, A.R.; Asencios, Y.J.O.; Assaf, E.M.; Assaf, J.M. Dry Reforming of Methane on Ni–Mg–Al Nano-Spheroid Oxide Catalysts Prepared by the Sol–Gel Method from Hydrotalcite-like Precursors. *Appl. Surf. Sci.* 2013, 280, 876–887.
 57. Schimmoeller, B.; Pratsinis, S.E.; Baiker, A. Flame Aerosol Synthesis of Metal Oxide Catalysts with Unprecedented Structural and Catalytic Properties. *ChemCatChem* 2011, 3, 1234–1256.
 58. Suh, D.J.; Park, T.-J.; Kim, J.-H.; Kim, K.-L. Nickel–Alumina Aerogel Catalysts Prepared by Fast Sol–Gel Synthesis. *J. Non-Cryst. Solids* 1998, 225, 168–172.
 59. Hou, Z.; Yashima, T. Small Amounts of Rh-Promoted Ni Catalysts for Methane Reforming with CO₂. *Catal. Lett.* 2003, 89, 193–197.

60. Fei, J.; Hou, Z.; Zheng, X.; Yashima, T. Doped Ni Catalysts for Methane Reforming with CO₂. *Catal. Lett.* 2004, 98, 241–246.
61. Crisafulli, C.; Scirè, S.; Minicò, S.; Solarino, L. Ni–Ru Bimetallic Catalysts for the CO₂ Reforming of Methane. *Appl. Catal. A Gen.* 2002, 225, 1–9.
62. Tomishige, K.; Kanazawa, S.; Sato, M.; Ikushima, K.; Kunimori, K. Catalyst Design of Pt-Modified Ni/Al₂O₃ Catalyst with Flat Temperature Profile in Methane Reforming with CO₂ and O₂. *Catal. Lett.* 2002, 84, 69–74.
63. Dias, J.A.C.; Assaf, J.M. Autothermal Reforming of Methane over Ni/γ-Al₂O₃ Catalysts: The Enhancement Effect of Small Quantities of Noble Metals. *J. Power Sources* 2004, 130, 106–110.
64. Dias, J.A.C.; Assaf, J.M. Autoreduction of Promoted Ni/γ-Al₂O₃ during Autothermal Reforming of Methane. *J. Power Sources* 2005, 139, 176–181.
65. Daza, C.E.; Gallego, J.; Mondragón, F.; Moreno, S.; Molina, R. High Stability of Ce-Promoted Ni/Mg–Al Catalysts Derived from Hydrotalcites in Dry Reforming of Methane. *Fuel* 2010, 89, 592–603.
66. Laosiripojana, N.; Sutthisripok, W.; Assabumrungrat, S. Synthesis Gas Production from Dry Reforming of Methane over CeO₂ Doped Ni/Al₂O₃: Influence of the Doping Ceria on the Resistance toward Carbon Formation. *Chem. Eng. J.* 2005, 112, 13–22.
67. Abd Ghani, N.A.; Azapour, A.; Syed Muhammad, A.F.; Abdullah, B. Dry Reforming of Methane for Hydrogen Production over NiCo Catalysts: Effect of NbZr Promoters. *Int. J. Hydrogen Energy* 2019, 44, 20881–20888.
68. Navarro, M.V.; Plou, J.; López, J.M.; Grasa, G.; Murillo, R. Effect of Oxidation-Reduction Cycles on Steam-Methane Reforming Kinetics over a Nickel-Based Catalyst. *Int. J. Hydrogen Energy* 2019, 44, 12617–12627.
69. Álvarez, M.A.; Bobadilla, L.F.; Garcilaso, V.; Centeno, M.A.; Odriozola, J.A. CO₂ Reforming of Methane over Ni-Ru Supported Catalysts: On the Nature of Active Sites by Operando DRIFTS Study. *J. CO₂ Util.* 2018, 24, 509–515.
70. Foletto, E.L.; Alves, R.W.; Jahn, S.L. Preparation of Ni/Pt Catalysts Supported on Spinel (MgAl₂O₄) for Methane Reforming. *J. Power Sources* 2006, 161, 531–534.
71. Ko, J.; Kim, B.-K.; Han, J.W. Density Functional Theory Study for Catalytic Activation and Dissociation of CO₂ on Bimetallic Alloy Surfaces. *J. Phys. Chem. C* 2016, 120, 3438–3447.
72. Zhang, J.; Wang, H.; Dalai, A.K. Effects of Metal Content on Activity and Stability of Ni-Co Bimetallic Catalysts for CO₂ Reforming of CH₄. *Appl. Catal. A Gen.* 2008, 339, 121–129.
73. Niu, J.; Wang, Y.; Liland, E.S.; Regli, K.S.; Yang, J.; Rout, K.R.; Luo, J.; Rønning, M.; Ran, J.; Chen, D. Unraveling Enhanced Activity, Selectivity, and Coke Resistance of Pt–Ni Bimetallic

- Clusters in Dry Reforming. *ACS Catal.* 2021, 11, 2398–2411.
74. Álvarez Moreno, A.; Ramirez-Reina, T.; Ivanova, S.; Roger, A.-C.; Centeno, M.Á.; Odriozola, J.A. Bimetallic Ni–Ru and Ni–Re Catalysts for Dry Reforming of Methane: Understanding the Synergies of the Selected Promoters. *Front. Chem.* 2021, 9, 694976.
75. Yu, X.; Zhang, F.; Wang, N.; Hao, S.; Chu, W. Plasma-Treated Bimetallic Ni–Pt Catalysts Derived from Hydrotalcites for the Carbon Dioxide Reforming of Methane. *Catal. Lett.* 2014, 144, 293–300.
76. Osaki, T.; Mori, T. Role of Potassium in Carbon-Free CO₂ Reforming of Methane on K-Promoted Ni/Al₂O₃ Catalysts. *J. Catal.* 2001, 204, 89–97.
77. García-Diéguez, M.; Pieta, I.S.; Herrera, M.C.; Larrubia, M.A.; Alemany, L.J. Nanostructured Pt- and Ni-Based Catalysts for CO₂-Reforming of Methane. *J. Catal.* 2010, 270, 136–145.
-

Retrieved from <https://encyclopedia.pub/entry/history/show/98657>