# Nickel-Titanium Rotary Instruments in Endodontics

Subjects: Dentistry, Oral Surgery & Medicine | Engineering, Mechanical | Instruments & Instrumentation Contributor: Alessio Zanza

Since the introduction of Nickel-Titanium alloy as the material of choice for the manufacturing of endodontic rotary instruments, the success rate of the root canal therapies has been significantly increased. This success mainly arises from the properties of the Nickel-Titanium alloy: the biocompatibility, the superelasticity and the shape memory effect. Those characteristics have led to a reduction in time of endodontic treatments, a simplification of instrumentation procedures and an increase of predictability and effectiveness of endodontic treatments. Nevertheless, the intracanal separation of Nickel-Titanium rotary instruments is still a major concern of endodontists, with a consequent possible reduction in the outcome rate. As thoroughly demonstrated, the two main causes of intracanal separation of endodontic instruments are the cyclic fatigue and the torsional loads. As results, in order to reduce the percentage of intracanal separation researches and manufacturers have been focused on the parameters that directly or indirectly influence mechanical properties of endodontic rotary instruments. This entry describes the current state of the art regarding the Nickel-Titanium alloy in endodontics, the mechanical behavior of endodontic rotary instruments and the relative stresses acting on them during intracanal instrumentation, highlighting the limitation of the current literature.

endodontics

endodontic rotary instruments

Nickel-Titanium alloy

root canal treatment

## 1. Introduction

The history of Endodontics is characterized by two eras, divided each other by the introduction of Nickel-Titanium (NiTi) alloy as the most eligible material for the manufacturing of endodontic rotary instruments. Its introduction, in fact, has thoroughly changed the instrumentation procedures of endodontic root canal systems, so as to be considered as a technological revolution which established the beginning of the modern endodontics. The exact moment of this passage corresponds to the publishment by Walia et al. of the article titled "An initial investigation of the bending and torsional properties of Nitinol root canal files", in which for the first time the Authors proposed the NiTi alloy as a material for the manufacturing of endodontic instruments, considering the great success that this alloy was having in orthodontics [1].

## 2. Advantages in Using NiTi Rotary Instruments

**Reduction in time of endodontic treatments**: Instrumentation technique with manual SS files requires a larger number of tools and longer operating times. Instead, the increased cutting efficiency of NiTi rotary instruments and

the use of increased taper instruments allow clinicians to improve these parameters of endodontic treatment  $\frac{[2][3][4]}{2}$ .

**Simplification of instrumentation procedures:** The special properties of the NiTi instruments have made it possible to considerably simplify the instrumentation technique compared to the traditional procedural steps carried out through the use of SS files <sup>[3][5][6]</sup>. Thanks to the better mechanical characteristics of rotary instruments than manual ones, it's possible to shape the root canals respecting their original trajectories not altering their original anatomy <sup>[7][8]</sup>.

**Increase of predictability and effectiveness of endodontic treatments:** The superelasticity of NiTi alloy ensures the use of endodontic instruments with an increased taper without an excessive risk of fracture due to bending or cyclic fatigue, improving the process of root canal shaping and therefore of root canal filling <sup>[9]</sup>. For all these reasons, the success rates of endodontic treatments performed with NiTi rotary instruments is significantly greater than those performed with SS manual instruments <sup>[10]</sup>[11][12][13][14].

## 3. Nickel-Titanium Alloy

The mechanical responses of the NiTi alloy under certain load can be represented through a stress/deformation graph (**Figure 1**). The stress and strain curve could be divided by three vertical line (A, B and C in **Figure 1**) that individuate on the graph three different areas according to the crystallographic organization of the NiTi alloy: the austenitic region in which the alloy is composed by austenite; the austenitic/martensitic region (also called R-phase) in which there is a partially transformation of austenite in martensite, according to the application of stress; the martensite region in which the total amount of austenite is transformed in martensite above certain loads <sup>[15][16]</sup>. Below certain load, the transformation induced by mechanical stress is totally reversible (elastic deformation) as a direct consequence of the superelasticiy, however if a yield strength is exceeded the deformation becomes irreversible (plastic deformation) and the endodontic instrument is permanently damaged <sup>[17]</sup>.

The mechanical responses of the NiTi alloy under certain load can be represented through a stress/deformation graph (**Figure 1**). The stress and strain curve could be divided by three vertical line (A, B and C in **Figure 1**) that individuate on the graph three different areas according to the crystallographic organization of the NiTi alloy: the austenitic region in which the alloy is composed by austenite; the austenitic/martensitic region (also called R-phase) in which there is a partially transformation of austenite in martensite, according to the application of stress; the martensite region in which the total amount of austenite is transformed in martensite above certain loads <sup>[15][16]</sup>. Below certain load, the transformation induced by mechanical stress is totally reversible (elastic deformation) as a direct consequence of the superelasticiy, however if a yield strength is exceeded the deformation becomes irreversible (plastic deformation) and the endodontic instrument is permanently damaged <sup>[17]</sup>.



**Figure 1.** Schematic representation of the stress and strain curve showing the crystallographic transformation according to the induced stress.

# 4. Evaluation of Mechanical Properties of NiTi Endodontic Rotary Instruments

#### 4.1. Cyclic Fatigue Resistance

The cyclic fatigue accumulation is an unavoidable consequence of tension–compression strain cycles to which the instrument is subjected in the point of maximum curvature (**Figure 2**) <sup>[18]</sup>. As a result, the risk of fracture due to flexural fatigue can never be zeroed, but only limited, until these instruments are used in continuous or alternating rotation in curved canals.



**Figure 2.** SEM image of fractured surface of a F2 EdgeTaper Platinum (Albuquerque, NM, USA) in a transversal view at ×600 magnification after cyclic fatigue testing. Dimples and microvoids visibly spread on the fractured surface constitute a typical feature of ductile fracture, which origins from the external part of the instruments with visible crack (evidenced by yellow arrows).

With the aim of reducing the probability of intracanal failure arising from cyclic or flexural fatigue, the manufacturers and researchers have increasingly focused on the determination of those parameters that are directly or indirectly involved in the determination of cyclic fatigue resistance and flexibility of endodontic rotary instruments. In a general view, those parameters could be divided into three groups: the anatomy-related factors, the instrument-related factors and the factors related to the instrumentation technique and strategy.

The first group is composed by those factors that characterize the anatomy of the root canal system. Pruett et al. in 1997 proposed a new method for the evaluation of the complexity of the root canal anatomy, adding to the Schneider's method another parameter: the radius of curvature of the root canal <sup>[18]</sup>. It has been demonstrated that in case of the same degrees of curvature, a smaller radius of curvature greatly reduces the resistance to cyclic fatigue of endodontic instruments. Accordingly, increasing the curvature angle and reducing the radius of curvature, endodontic instruments will be subjected to greater flexural stress, reducing their ability to withstand cyclic fatigue

<sup>[18]</sup>. Thus, in order to prevent cyclic fatigue failure, the knowledge of the root canal anatomy is a fundamental prerogative <sup>[19][20]</sup>.

Regarding the instrument-related factors, two parameters in particular must be mentioned: the heat-treatments, as described above, and the metal mass or the volume per millimeters (Vol per mm) <sup>[21][22][23]</sup>. Grande et al. have stated that there is a statistically significant relationship between the Vol per mm and the cyclic fatigue resistance of endodontic instruments, and that instruments with similar Vol per mm, and then mass, at the point of maximum stress show similar cyclic fatigue resistance. This innovative parameter, according to the Authors, allows to group in a single parameter all those geometric characteristics that, until then, were thought to have a crucial role in the determination of the cyclic fatigue resistance such as the number of blades, the size of the instrument, the taper and the inner core area <sup>[24]</sup>.

The factors related to the instrumentation technique and the strategy used are mainly related to the access cavity design, the choice of the setting of speed and the motion used (continuous or reciprocating motion). As stated by Pedullà et al. a conservative access cavity could lead to an angled insertion of endodontic instruments inside the root canal system and the consequent decrease of their cyclic fatigue resistance arising from the increase of the flexural stress derived from their angulation of insertion <sup>[25]</sup>. As regards the use of endodontic instruments, it has been demonstrated that reducing the rotational speed, the time before fracture increases due to the lower number of cycles carried out in the same given time period, however, the rotational speed per se does not affect the number of rotations to fracture <sup>[26]</sup>. Finally, it has been demonstrated that the use of reciprocating movements (alternating clockwise and counterclockwise rotation movements) significantly reduces the cyclic fatigue of the instruments, increasing their resistance <sup>[27][28]</sup>.

#### 4.2. Torsional Resistance

Torsional failure occurs when an apical part of the endodontic instrument, more frequently the tip, operating in continuous or alternating rotation, remains blocked in the dentinal wall and its coronal portion continues to rotate, causing its fracture (**Figure 3**)<sup>[29]</sup>.



**Figure 3.** SEM image of fractured surface of a F-One #20 (Fanta Dental, Shanghai, China) in a transversal view at ×800 magnification after torsional testing. The typical features of fracture arising from excessive torsional load, showing concentric circular abrasion marks and fibrous dimples near the center of rotation are evidenced by the round-shaped circumferential line.

Even the parameters that influence the torsional resistance of NiTi endodontic rotary instruments could be divided in the same three groups evidenced in reference to the cyclic fatigue resistance <sup>[30]</sup>.

The anatomy related factors include all the characteristics of the tooth that contribute to the generation of torsional stresses such as: the diameter of the canal, the radius and degrees of curvature, the hardness of the dentin and the length of the canal [31][32][33].

Otherwise, in the third group there are all those factors that characterize the clinical approach to endodontic therapy such as: the extension of the access cavity, the coronal preflaring, the glide path, the use of high and low torque engines, the instrumentation technique (crown-down, step back, simultaneous instrumentation technique, etc.), the amplitude and intensity of the pecking-motion and the type of motion used (reciprocating or continuous motion) <sup>[34][35][36][37][38][39][40]</sup>. Contrarily to the cyclic fatigue resistance, a constricted access cavity improves the torsional resistance of endodontic instruments <sup>[41]</sup>. In fact, it has been stated that increasing the bending moment

acting on an endodontic instrument, as it happens during the angled insertion of the instruments in the conservative access cavity, the torsional resistance increases <sup>[41][42]</sup>. In other words, according to Di Nardo et al., constricted access cavity could impose a coronal curvature to NiTi instruments, increasing the bending moment acting on them <sup>[41]</sup>. An increased bending moment, according to Seracchiani et al. is able to increase the torsional resistance of NiTi instruments since the two parameters are strictly correlated as discussed in the next subparagraph <sup>[42]</sup>.

Finally, the second group consists of all those structural factors that characterize an endodontic instrument, such as the cross-sectional design, the type of the alloy and its crystallography phase, the manufacturing processes, the pitch, the helix and the rake angle, the length of the instrument and the taper [30][36][43][44][45]. As many studies have shown, the design of the cross-section is one of the most important parameters that can significantly determine the torsional stiffness of a NiTi endodontic instrument, since it thoroughly influences its mechanical properties [43][46][47]. Berutti et al. have been demonstrated that different cross-sectional designs allow a different distribution of torsional stresses; the more stresses are uniformly spread along the instrument, the more its torsional stiffness increases [48]. Nevertheless, the actual relationship between the cross-sectional design of the instrument and its torsional stiffness seemed to be unclear and, specifically, it was unclear which aspect of the instrument cross-section played a major role in determining the resistance of the instruments to torsional stresses. Recently, Zanza et al. identified the key factor in determining the torsional resistance of NiTi endodontic rotary instruments. Based on their study, the parameter that showed the most significant correlation with torsional resistance is the polar moment of inertia <sup>[49]</sup>. According to this, the Authors stated that the mass and area are not so crucial in terms of absolute value, but instead, it is relevant how they are distributed in relation to the center of rotation. Thus, the more the mass and the area are spread far from the pivot center, the more the polar moment of inertia is and the more the torsional resistance is [49].

#### 4.3. Combined Torsional and Flexural Stresses

Recently, greater attention has been focused on understanding the interaction between bending and torsional stress in order to better comprise the mechanical phenomena behind the root canal instrumentation <sup>[42][50]</sup>. In fact, the NiTi endodontic rotary instruments during shaping procedure are always subjected to both flexural and torsional stresses and surely further studies are needed to eviscerate their reciprocal influence in a more detail <sup>[51]</sup>.

Seracchiani et al. concluded that in static situation flexural stresses significantly influence the torsional resistance of instruments with a blocked tip. This is due to the fact that the torque, in case of curved canal, is not only caused by torsional moment, but also by flexural loads <sup>[42]</sup>. Thus, it can be stated that increasing the curvature degrees of root canal the torsional resistance of instruments increases.

On the contrary, Iacono et al. with the aim of investigating the influence of torsional loads on cyclic fatigue of NiTi endodontic instruments proposed a novel testing device <sup>[50]</sup>. The device is a usual cyclic fatigue testing device with a standardized load on the apical 5 mm providing a uniform real-time load. The Authors concluded that an increase

of apical torsional load led to a decrease of cyclic fatigue resistance <sup>[50]</sup>. However, even if the above-mentioned research add novelty to the current knowledge, the influence of torsional loads on cyclic fatigue in the point of maximum curvature, where the bending moment acts, is still unknow. Therefore, further research should be conducted on this theme.

Another limitation on this topic is the static condition used in the methodology of the published research. In fact, in order to comprise in a more detail the reciprocal relationship between cyclic fatigue and torsional resistance, a dynamic evaluation of these phenomena is mandatory <sup>[53]</sup>.

#### 4.4. Bending Ability

The flexibility of NiTi endodontic rotary instruments is defined as the ability to be bent without being irreversibly deformed and still retaining their original form <sup>[54]</sup>. As previously stated by several studies, the enhanced flexibility in comparison to SS manual instruments arises from the NiTi alloy superelasticity and the ability to start a stress-induced transformation of the parent  $\beta$ -phase, characterized by the reversible transition of austenite to martensite <sup>[54][55][56]</sup>. Moreover, the increased bending ability of NiTi alloy is highlighted by the NiTi Young's modulus (modulus of elasticity), an intrinsic characteristic of the alloy, that is lower than the stainless-steel one <sup>[1]</sup>.

As demonstrated, an increased flexibility of NiTi endodontic instruments allows a more suitable canal enlargement since the instrument is more able to follow the curved anatomy of root canals and to maintain a central position within the canal <sup>[1][57][58][59][60]</sup>. Flexibility is influenced by several factors, among those the most important is undoubtedly the heat-treatment that allows instrument to be martensitic at ambient or intracanal temperature <sup>[61]</sup>. However, there are other factors related to the bending ability of NiTi instruments, such as the alloys chemical composition, the geometric design such as cross-section, inner core area, taper and pitch <sup>[16][62][63]</sup>.

According to the bending test assessed by ISO 3630-1, the flexibility of an endodontic instrument is evaluated by clamping 3 mm of its tip in a chuck and applying an angular deflection of 45°. The force generated to bend the instrument is registered as the bending resistance, thus, low bending results are indicative of the high material flexibility <sup>[64]</sup>.

Recently, Miccoli et al. proposed a new bending test device able to evaluate the flexibility of NiTi instruments at different length from the tip (i.e., 3, 6 and 9 mm), providing a more representative description of the bending ability of NiTi instruments <sup>[65]</sup>.

The main limitation of bending tests is always the staticity of the evaluation. In fact, those tests do not take into account the dynamicity of instrumentation procedures, not considering the rotation of NiTi instruments at high speed, thus, the clinical relevance of these static tests has been considered low by many researchers, since clinical usage can be affected by several other factors <sup>[66]</sup>. Despite this, static bending tests with static torsional and cyclic fatigue tests remain a good manner to establish the basic mechanical properties of NiTi instruments, that should be implemented with dynamic investigations such as the evaluation of centering ability, canal transportation,

shaping ability and cutting efficiency, so a reliable evaluation of the performance of different NiTi instruments can be performed through a multimethod approach <sup>[66]</sup>.

## 5. Centering Ability, Canal Transportation and Shaping Ability

The main goal of shaping procedure is undoubtedly the mechanical removal of vital and/or necrotic tissues form the root canal system, simultaneously allowing the creation of an adequate space for the chemical disinfection and obturation <sup>[67]</sup>. According to this, root canal instrumentation could be considered as the most crucial phase during root canal treatment, in which clinicians must avoid any procedural error in order to not compromise the outcome of the endodontic treatment <sup>[68][69]</sup>. As stated by Gorni et al. the alteration of the root canal morphology is one of the most significant parameters in determining the outcome of endodontic retreatments, since inferior cleansing can be performed specifically aimed at the anatomical irregularities created by previous treatment <sup>[70]</sup>. Regarding this, the most common procedural errors during root canal treatments could be synthetized in: ledges, strip perforations, excessive thinning of canal walls, and canal transportation <sup>[1][71][72]</sup>.

Considering the above-mentioned reasons, the preservation of the original root canal morphology is one of the most important features that characterized endodontic instruments. In fact, during the evaluation of the performance of NiTi rotary instruments the shaping ability should be considered.

The two main popular and thoroughly validated methods used to evaluate these factors are the Micro-Computed Tomography (CT) and the SEM analysis, singularly used or in combination, that allow a precise calculation of the interested measurement trough the aid of digital software <sup>[73][74]</sup>. In our opinion Micro-CT imaging should be preferred because it is non-destructive 3-dimensional analysis and gives high-resolution images to precisely evaluate the untouched area, volume changes, and transportation in comparison to SEM analysis that requires the split of the teeth <sup>[73]</sup>. However, the SEM analysis could be used to evaluate debris and smear layer removal since it allows their direct measurement without using complex software for the voxel interpretation of Micro-CT images, nevertheless, also those measurements have some limitation, such as the bi-dimensional analysis of debris and smear layer, that does not allow measurement of the thickness of both parameters analyzed <sup>[75][76][77]</sup>.

The most widely used centering ability and canal transportation evaluation method is the superimposition of root canal anatomy images before and after instrumentation <sup>[8]</sup>[73][78][79]</sup>. The differences reside in the acquisition method used. Obviously the most accurate is the Micro-CT, followed by the CBCT and bi-dimensional radiograph. During Micro-Ct analysis, scans of each specimen before and after shaping procedures are overlapped using algorithms, allowing a consistent location of various dimensional measurements, such as the measurement of transportation across different (pre- and post-shaping) CT scans <sup>[80]</sup>.

Despite the recent advances and innovations in kinematics and metallurgical and mechanical characteristics, none of the NiTi instrument systems are capable of shaping root canals to the ideal form, leaving a certain percentage of untouched canal [81][82][83].

#### References

- 1. Walia, H.M.; Brantley, W.A.; Gerstein, H. An initial investigation of the bending and torsional properties of Nitinol root canal files. J. Endod. 1988, 14, 346–351.
- Weiger, R.; Brückner, M.; ElAyouti, A.; Löst, C. Preparation of curved root canals with rotary FlexMaster instruments compared to Lightspeed instruments and NiTi hand files. Int. Endod. J. 2003, 36, 483–490.
- Vaudt, J.; Bitter, K.; Neumann, K.; Kielbassa, A.M. Ex vivo study on root canal instrumentation of two rotary nickel-titanium systems in comparison to stainless steel hand instruments. Int. Endod. J. 2009, 42, 22–33.
- 4. Govindaraju, L.; Jeevanandan, G.; Subramanian, E. Clinical Evaluation of Quality of Obturation and Instrumentation Time using Two Modified Rotary File Systems with Manual Instrumentation in Primary Teeth. J. Clin. Diagn. Res. 2017, 11, Zc55–Zc58.
- 5. Sadeghi, S. Shaping ability of NiTi rotary versus stainless steel hand instruments in simulated curved canals. Med. Oral Patol. Oral Cir. Bucal. 2011, 16, e454–e458.
- Htun, P.H.; Ebihara, A.; Maki, K.; Kimura, S.; Nishijo, M.; Tokita, D.; Okiji, T. Comparison of torque, force generation and canal shaping ability between manual and nickel-titanium glide path instruments in rotary and optimum glide path motion. Odontology 2020, 108, 188–193.
- 7. Kandaswamy, D.; Venkateshbabu, N.; Porkodi, I.; Pradeep, G. Canal-centering ability: An endodontic challenge. J. Conserv. Dent. 2009, 12, 3–9.
- Gergi, R.; Rjeily, J.A.; Sader, J.; Naaman, A. Comparison of canal transportation and centering ability of twisted files, Pathfile-ProTaper system, and stainless steel hand K-files by using computed tomography. J. Endod. 2010, 36, 904–907.
- Donfrancesco, O.; Del Giudice, A.; Zanza, A.; Relucenti, M.; Petracchiola, S.; Gambarini, G.; Testarelli, L.; Seracchiani, M. SEM Evaluation of Endosequence BC Sealer Hiflow in Different Environmental Conditions. J. Compos. Sci. 2021, 5, 99.
- 10. Namazikhah, M.S.; Mokhlis, H.R.; Alasmakh, K. Comparison between a hand stainless-steel K file and a rotary NiTi 0.04 taper. J. Calif Dent. Assoc. 2000, 28, 421–426.
- Taşdemir, T.; Aydemir, H.; Inan, U.; Unal, O. Canal preparation with Hero 642 rotary Ni-Ti instruments compared with stainless steel hand K-file assessed using computed tomography. Int. Endod. J. 2005, 38, 402–408.
- 12. Cheung, G.S.; Liu, C.S. A retrospective study of endodontic treatment outcome between nickeltitanium rotary and stainless steel hand filing techniques. J. Endod. 2009, 35, 938–943.

- Del Fabbro, M.; Afrashtehfar, K.I.; Corbella, S.; El-Kabbaney, A.; Perondi, I.; Taschieri, S. In Vivo and In Vitro Effectiveness of Rotary Nickel-Titanium vs Manual Stainless Steel Instruments for Root Canal Therapy: Systematic Review and Meta-analysis. J. Evid. Based Dent. Pract. 2018, 18, 59–69.
- 14. Makanjuola, J.O.; Umesi, D.C.; Oderinu, O.H. Treatment outcome of manual versus rotary techniques in single-visit endodontics for patients in a Nigerian Teaching Hospital: A randomized clinical trial. J. West Afr. Coll. Surg. 2018, 8, 44–75.
- 15. Thompson, S.A. An overview of nickel-titanium alloys used in dentistry. Int. Endod. J. 2000, 33, 297–310.
- 16. Zhou, H.; Peng, B.; Zheng, Y.-F. An overview of the mechanical properties of nickel–titanium endodontic instruments. Endodontic Topics. 2013, 29, 42–54.
- 17. Hamilton, R.F.; Sehitoglu, H.; Chumlyakov, Y.; Maier, H.J. Stress dependence of the hysteresis in single crystal NiTi alloys. Acta Materialia 2004, 52, 3383–3402.
- 18. Pruett, J.P.; Clement, D.J.; Carnes, D.L. Cyclic fatigue testing of nickel-titanium endodontic instruments. J. Endod. 1997, 23, 77–85.
- Leonardi Dutra, K.; Haas, L.; Porporatti, A.L.; Flores-Mir, C.; Nascimento Santos, J.; Mezzomo, L.A.; Corrêa, M.; Canto, G.D.L. Diagnostic Accuracy of Cone-beam Computed Tomography and Conventional Radiography on Apical Periodontitis: A Systematic Review and Meta-analysis. J. Endod. 2016, 42, 356–364.
- 20. Reda, R.; Zanza, A.; Mazzoni, A.; Cicconetti, A.; Testarelli, L.; Di Nardo, D. An update of the possible applications of magnetic resonance imaging (Mri) in dentistry: A literature review. J. Imaging 2021, 7, 75.
- Di Nardo, D.; Gambarini, G.; Seracchiani, M.; Mazzoni, A.; Zanza, A.; Giudice, A.; D'Angelo, M.; Testarelli, L. Influence of different cross-section on cyclic fatigue resistance of two nickel-titanium rotary instruments with same heat treatment: An in vitro study. Saudi Endod. J. 2020, 10, 221– 225.
- 22. Seracchiani, M.; Miccoli, G.; Reda, R.; Zanza, A.; Obino, F.V.; Bhandi, S.; Gambarini, G.; Testarelli, L. A comprehensive in vitro comparison of mechanical properties of two rotary endodontic instruments. World J. Dent. 2020, 11, 185–188.
- Bhandi, S.; Seracchiani, M.; Donfrancesco, O.; Reda, R.; Mazzoni, A.; Nottola, S.; Familiari, G. Nickel-Titanium Rotary Instruments: An In Vitro Comparison (Torsional Resistance of Two Heattreated Reciprocating Files). J. Contemp. Dent. Pract. 2021, 22, 361–364.
- 24. Grande, N.M.; Plotino, G.; Pecci, R.; Bedini, R.; Malagnino, V.A.; Somma, F. Cyclic fatigue resistance and three-dimensional analysis of instruments from two nickel-titanium rotary systems. Int. Endod. J. 2006, 39, 755–763.

- 25. Pedullà, E.; La Rosa, G.R.M.; Virgillito, C.; Rapisarda, E.; Kim, H.C.; Generali, L. Cyclic Fatigue Resistance of Nickel-titanium Rotary Instruments according to the Angle of File Access and Radius of Root Canal. J. Endod. 2020, 46, 431–436.
- 26. Kitchens, G.G., Jr.; Liewehr, F.R.; Moon, P.C. The effect of operational speed on the fracture of nickel-titanium rotary instruments. J. Endod. 2007, 33, 52–54.
- Pedullà, E.; Grande, N.M.; Plotino, G.; Gambarini, G.; Rapisarda, E. Influence of continuous or reciprocating motion on cyclic fatigue resistance of 4 different nickel-titanium rotary instruments. J. Endod. 2013, 39, 258–261.
- Pedullà, E.; Corsentino, G.; Ambu, E.; Rovai, F.; Campedelli, F.; Rapisarda, S.; Rapisarda, E.; Grandini, S.; La Rosa, G.R. Influence of continuous rotation or reciprocation of Optimum Torque Reverse motion on cyclic fatigue resistance of nickel-titanium rotary instruments. Int. Endod. J. 2018, 51, 522–528.
- 29. Sattapan, B.; Nervo, G.J.; Palamara, J.E.; Messer, H.H. Defects in rotary nickel-titanium files after clinical use. J. Endod. 2000, 26, 161–165.
- Gambarini, G.; Seracchiani, M.; Zanza, A.; Miccoli, G.; Del Giudice, A.; Testarelli, L. Influence of shaft length on torsional behavior of endodontic nickel–titanium instruments. Odontology 2020, 109, 568–573.
- Peters, O.A.; Peters, C.I.; Schönenberger, K.; Barbakow, F. ProTaper rotary root canal preparation: Assessment of torque and force in relation to canal anatomy. Int. Endod. J. 2003, 36, 93–99.
- 32. Boessler, C.; Peters, O.A.; Zehnder, M. Impact of lubricant parameters on rotary instrument torque and force. J. Endod. 2007, 33, 280–283.
- Gambarini, G.; Seracchiani, M.; Piasecki, L.; Valenti Obino, F.; Galli, M.; Di Nardo, D.; Testarelli, L. Measurement of torque generated during intracanal instrumentation in vivo. Int. Endod. J. 2019, 52, 737–745.
- Roland, D.D.; Andelin, W.E.; Browning, D.F.; Hsu, G.H.; Torabinejad, M. The effect of preflaring on the rates of separation for 0.04 taper nickel titanium rotary instruments. J. Endod. 2002, 28, 543– 545.
- 35. Yared, G.; Sleiman, P. Failure of ProFile instruments used with air, high torque control, and low torque control motors. Oral Surg. Oral Med. Oral Pathol. Oral Radiol. Endod. 2002, 93, 92–96.
- 36. Parashos, P.; Messer, H.H. Rotary NiTi instrument fracture and its consequences. J. Endod. 2006, 32, 1031–1043.
- 37. Ha, J.H.; Park, S.S. Influence of glide path on the screw-in effect and torque of nickel-titanium rotary files in simulated resin root canals. Restor. Dent. Endod. 2012, 37, 215–219.

- Tokita, D.; Ebihara, A.; Nishijo, M.; Miyara, K.; Okiji, T. Dynamic Torque and Vertical Force Analysis during Nickel-titanium Rotary Root Canal Preparation with Different Modes of Reciprocal Rotation. J. Endod. 2017, 43, 1706–1710.
- 39. Kwak, S.W.; Ha, J.H.; Cheung, G.S.; Kim, H.C.; Kim, S.K. Effect of the Glide Path Establishment on the Torque Generation to the Files during Instrumentation: An In Vitro Measurement. J. Endod. 2018, 44, 496–500.
- 40. Kimura, S.; Ebihara, A.; Maki, K.; Nishijo, M.; Tokita, D.; Okiji, T. Effect of Optimum Torque Reverse Motion on Torque and Force Generation during Root Canal Instrumentation with Crowndown and Single-length Techniques. J. Endod. 2020, 46, 232–237.
- Di Nardo, D.; Zanza, A.; Seracchiani, M.; Donfrancesco, O.; Gambarini, G.; Testarelli, L. Angle of Insertion and Torsional Resistance of Nickel–Titanium Rotary Instruments. Materials 2021, 14, 3744.
- 42. Seracchiani, M.; Miccoli, G.; Di Nardo, D.; Zanza, A.; Cantore, M.; Gambarini, G.; Testarelli, L. Effect of Flexural Stress on Torsional Resistance of NiTi Instruments. J. Endod. 2021, 47, 472– 476.
- 43. Baek, S.H.; Lee, C.J.; Versluis, A.; Kim, B.M.; Lee, W.; Kim, H.C. Comparison of torsional stiffness of nickel-titanium rotary files with different geometric characteristics. J. Endod. 2011, 37, 1283–1286.
- 44. Vivan, R.R.; Alcalde, M.P.; Candeiro, G.; Gavini, G.; Caldeira, C.L.; Duarte, M.A.H. Torsional fatigue strength of reciprocating and rotary pathfinding instruments manufactured from different NiTi alloys. Braz. Oral Res. 2019, 33, e097.
- 45. Gambarini, G.; Cicconetti, A.; Nardo, D.D.; Miccoli, G.; Zanza, A.; Testarelli, L.; Seracchiani, M. Influence of different heat treatments on torsional and cyclic fatigue resistance of nickel-titanium rotary files: A comparative study. Appl. Sci. 2020, 10, 5604.
- 46. Camps, J.J.; Pertot, W.J.; Levallois, B. Relationship between file size and stiffness of nickel titanium instruments. Endod. Dent. Traumatol. 1995, 11, 270–273.
- 47. Kim, H.C.; Kim, H.J.; Lee, C.J.; Kim, B.M.; Park, J.K.; Versluis, A. Mechanical response of nickeltitanium instruments with different cross-sectional designs during shaping of simulated curved canals. Int. Endod. J. 2009, 42, 593–602.
- 48. Berutti, E.; Chiandussi, G.; Gaviglio, I.; Ibba, A. Comparative analysis of torsional and bending stresses in two mathematical models of nickel-titanium rotary instruments: ProTaper versus ProFile. J. Endod. 2003, 29, 15–19.
- 49. Zanza, A.; Seracchiani, M.; Di Nardo, D.; Reda, R.; Gambarini, G.; Testarelli, L. A Paradigm Shift for Torsional Stiffness of Nickel-Titanium Rotary Instruments: A Finite Element Analysis. J. Endod. 2021, 47, 1149–1156.

- 50. Iacono, F.; Pirani, C.; Gatto, M.R.; Prati, C.; Peters, O. Combining apical torsional load and cyclic fatigue resistance of NiTi instruments: New approach to determine the effective lifespan of rotary instruments. Aust. Endod. J. 2021. online ahead of print.
- Santos, C.B.; Simões-Carvalho, M.; Perez, R.; Vieira, V.T.L.; Antunes, H.S.; Cavalcante, D.F.; De-Deus, G.; Silva, E.J.N.L. Torsional fatigue resistance of R-Pilot and WaveOne Gold Glider NiTi glide path reciprocating systems. Int. Endod. J. 2019, 52, 874–879.
- 52. Zanza, A.; Seracchiani, M.; Reda, R.; Di Nardo, D.; Gambarini, G.; Testarelli, L. Role of the Crystallographic Phase of NiTi Rotary Instruments in Determining Their Torsional Resistance during Different Bending Conditions. Materials 2021, 14, 6324.
- 53. Gambarini, G.; Miccoli, G.; D'Angelo, M.; Seracchiani, M.; Obino, F.V.; Reda, R.; Testarelli, L. The relevance of operative torque and torsional resistance of nickel-titanium rotary instruments: A preliminary clinical investigation. Saudi Endod. J. 2020, 10, 260–264.
- 54. Viana, A.C.; Chaves Craveiro de Melo, M.; Guiomar de Azevedo Bahia, M.; Lopes Buono, V.T. Relationship between flexibility and physical, chemical, and geometric characteristics of rotary nickel-titanium instruments. Oral Surg. Oral Med. Oral Pathol. Oral Radiol. Endod. 2010, 110, 527–533.
- 55. Bahia, M.G.A.; Martins, R.C.; Gonzalez, B.M.; Buono, V.T.L. Physical and mechanical characterization and the influence of cyclic loading on the behaviour of nickel-titanium wires employed in the manufacture of rotary endodontic instruments. Int. Endod. J. 2005, 38, 795–801.
- Hamdy, T.M.; Galal, M.; Ismail, A.G.; Abdelraouf, R.M. Evaluation of Flexibility, Microstructure and Elemental Analysis of Some Contemporary Nickel-Titanium Rotary Instruments. Open Access Maced J. Med. Sci. 2019, 7, 3647–3654.
- 57. Glossen, C.R.; Haller, R.H.; Dove, S.B.; del Rio, C.E. A comparison of root canal preparations using Ni-Ti hand, Ni-Ti engine-driven, and K-Flex endodontic instruments. J. Endod. 1995, 21, 146–151.
- 58. Park, H. A comparison of Greater Taper files, ProFiles, and stainless steel files to shape curved root canals. Oral Surg. Oral Med. Oral Pathol. Oral Radiol. Endod. 2001, 91, 715–718.
- 59. de Arruda Santos, L.; López, J.B.; de Las Casas, E.B.; de Azevedo Bahia, M.G.; Buono, V.T. Mechanical behavior of three nickel-titanium rotary files: A comparison of numerical simulation with bending and torsion tests. Mater. Sci. Eng. C Mater. Biol. Appl. 2014, 37, 258–263.
- Razcha, C.; Zacharopoulos, A.; Anestis, D.; Mikrogeorgis, G.; Zacharakis, G.; Lyroudia, K. Micro-Computed Tomographic Evaluation of Canal Transportation and Centering Ability of 4 Heat-Treated Nickel-Titanium Systems. J. Endod. 2020, 46, 675–681.
- 61. Zupanc, J.; Vahdat-Pajouh, N.; Schäfer, E. New thermomechanically treated NiTi alloys—A review. Int. Endod. J. 2018, 51, 1088–1103.

- 62. Yahata, Y.; Yoneyama, T.; Hayashi, Y.; Ebihara, A.; Doi, H.; Hanawa, T.; Suda, H. Effect of heat treatment on transformation temperatures and bending properties of nickel-titanium endodontic instruments. Int. Endod. J. 2009, 42, 621–626.
- Hou, X.; Yahata, Y.; Hayashi, Y.; Ebihara, A.; Hanawa, T.; Suda, H. Phase transformation behaviour and bending property of twisted nickel-titanium endodontic instruments. Int. Endod. J. 2011, 44, 253–258.
- Testarelli, L.; Plotino, G.; Al-Sudani, D.; Vincenzi, V.; Giansiracusa, A.; Grande, N.M.; Gambarini, G. Bending properties of a new nickel-titanium alloy with a lower percent by weight of nickel. J. Endod. 2011, 37, 1293–1295.
- 65. Miccoli, G.; Cicconetti, A.; Gambarini, G.; Del Giudice, A.; Ripanti, F.; Di Nardo, D.; Testarelli, L.; Seracchiani, M. A New Device to Test the Bending Resistance of Mechanical Endodontic Instruments. Appl. Sci. 2020, 10, 7215.
- Silva, E.; Martins, J.N.R.; Lima, C.O.; Vieira, V.T.L.; Braz Fernandes, F.M.; De-Deus, G.; Versiani, M.A. Mechanical Tests, Metallurgical Characterization, and Shaping Ability of Nickel-Titanium Rotary Instruments: A Multimethod Research. J. Endod. 2020, 46, 1485–1494.
- 67. Chugal, N.; Mallya, S.M.; Kahler, B.; Lin, L.M. Endodontic Treatment Outcomes. Dent. Clin. North Am. 2017, 61, 59–80.
- Ng, Y.L.; Mann, V.; Rahbaran, S.; Lewsey, J.; Gulabivala, K. Outcome of primary root canal treatment: Systematic review of the literature—Part 1. Effects of study characteristics on probability of success. Int. Endod. J. 2007, 40, 921–939.
- Ng, Y.L.; Mann, V.; Rahbaran, S.; Lewsey, J.; Gulabivala, K. Outcome of primary root canal treatment: Systematic review of the literature—Part 2. Influence of clinical factors. Int. Endod. J. 2008, 41, 6–31.
- 70. Gorni, F.G.; Gagliani, M.M. The outcome of endodontic retreatment: A 2-yr follow-up. J. Endod. 2004, 30, 1–4.
- 71. Lin, L.M.; Rosenberg, P.A.; Lin, J. Do procedural errors cause endodontic treatment failure? J. Am. Dent. Assoc. 2005, 136, 187–193.
- Song, M.; Kim, H.C.; Lee, W.; Kim, E. Analysis of the cause of failure in nonsurgical endodontic treatment by microscopic inspection during endodontic microsurgery. J. Endod. 2011, 37, 1516– 1519.
- 73. Sousa-Neto, M.D.; Silva-Sousa, Y.C.; Mazzi-Chaves, J.F.; Carvalho, K.K.T.; Barbosa, A.F.S.; Versiani, M.A.; Jacobs, R.; Leoni, G. Root canal preparation using micro-computed tomography analysis: A literature review. Braz. Oral Res. 2018, 32, e66.

- 74. Htun, P.H.; Ebihara, A.; Maki, K.; Kimura, S.; Nishijo, M.; Okiji, T. Cleaning and Shaping Ability of Gentlefile, HyFlex, EDM, and ProTaper Next Instruments: A Combined Micro-computed Tomographic and Scanning Electron Microscopic Study. J. Endod. 2020, 46, 973–979.
- Hülsmann, M.; Rümmelin, C.; Schäfers, F. Root canal cleanliness after preparation with different endodontic handpieces and hand instruments: A comparative SEM investigation. J. Endod. 1997, 23, 301–306.
- Garip, Y.; Sazak, H.; Gunday, M.; Hatipoglu, S. Evaluation of smear layer removal after use of a canal brush: An SEM study. Oral Surg. Oral Med. Oral Pathol. Oral Radiol. Endod. 2010, 110, e62–e66.
- 77. Plotino, G.; Özyürek, T.; Grande, N.M.; Gündoğar, M. Influence of size and taper of basic root canal preparation on root canal cleanliness: A scanning electron microscopy study. Int. Endod. J. 2019, 52, 343–351.
- 78. Gambill, J.M.; Alder, M.; del Rio, C.E. Comparison of nickel-titanium and stainless steel hand-file instrumentation using computed tomography. J. Endod. 1996, 22, 369–375.
- 79. Poly, A.; AlMalki, F.; Marques, F.; Karabucak, B. Canal transportation and centering ratio after preparation in severely curved canals: Analysis by micro-computed tomography and double-digital radiography. Clin. Oral Investig. 2019, 23, 4255–4262.
- Kabil, E.; Katić, M.; Anić, I.; Bago, I. Micro-computed Evaluation of Canal Transportation and Centering Ability of 5 Rotary and Reciprocating Systems with Different Metallurgical Properties and Surface Treatments in Curved Root Canals. J. Endod. 2021, 47, 477–484.
- 81. Schneider, S.W. A comparison of canal preparations in straight and curved root canals. Oral Surg. Oral Med. Oral Pathol. 1971, 32, 271–275.
- 82. Setzer, F.C.; Kwon, T.K.; Karabucak, B. Comparison of apical transportation between two rotary file systems and two hybrid rotary instrumentation sequences. J. Endod. 2010, 36, 1226–1229.
- 83. Zhao, D.; Shen, Y.; Peng, B.; Haapasalo, M. Micro-computed tomography evaluation of the preparation of mesiobuccal root canals in maxillary first molars with Hyflex, CM Twisted Files, and K3 instruments. J. Endod. 2013, 39, 385–388.

Retrieved from https://encyclopedia.pub/entry/history/show/44013