# Layered Oxide Cathodes

Subjects: Chemistry, Inorganic & Nuclear Contributor: Julia Yang

Layered intercalation compounds are the dominant cathode materials for rechargeable Li-ion batteries. In this review, we discuss the topology of the layered structure and explain how the structure (1) sets the voltage slope trends among various alkali ions, (2) is critically limited to certain transition metals due to their electronic structure, and (3) controls the alkali diffusion mechanism.

Keywords: layered oxide cathodes ; alkali-alkali interactions ; electronic structure ; Li diffusion

### 1. Introduction to the O3 Structure

Rechargeable Li-ion batteries have enabled a wireless revolution and are currently the dominant technology used to power electric vehicles and provide resilience to a grid powered by renewables. Research in the 1970s to create superconductors by modifying the carrier density of chalcogenides through intercalation <sup>[1]</sup> transitioned into energy storage when Whittingham demonstrated in 1976 a rechargeable battery using the layered TiS<sub>2</sub> cathode and Li metal anode <sup>[2]</sup>. Soon thereafter, Mizushima, Jones, Wiseman, and Goodenough demonstrated that a much higher voltage could be achieved by reversible Li de-intercalation from layered LiCoO<sub>2</sub> <sup>[3]</sup>, energizing generations of rechargeable battery research. In this short review we revisit our work in understanding a few basic relationships between the structure, electronic structure, and properties of layered cathode materials.

A layered rocksalt cathode oxide adopts the general formula  $A_xMO_2$  (A: alkali cation, M: metal cation, O: oxygen anion). The O anions form a face-centered cubic (FCC) framework with octahedral and tetrahedral sites. These two environments are face sharing and form a topologically connected network. When fully alkaliated such that  $x \sim 1$ , the compound consists of  $AO_2$  and  $MO_2$  edge-sharing octahedra. The layered structure, illustrated in Figure 1, is aptly named because  $AO_2/MO_2$  octahedra form alternating (111) planes of the FCC oxygen lattice when fully lithiated. The A and M cations alternate in the abc repeat unit of the oxygen framework to form  $a-b_c-a_b-c_-$ , stacking where the minus sign "–" indicates the location of M and the underscore "\_" gives the position of the A ions. Because the oxygen stacking has a repeat unit of three and the metal layering repeats every two layers, periodicity is achieved after six oxygen layers. Under the structural classification by Delmas et al. for layered cathode oxides <sup>[4]</sup>, the layered rocksalt cathode structure is commonly referred to as O3: O for the octahedral alkali ion environment (not to be confused with O for oxygen) and 3 for the number of  $MO_2$  slabs in a repeat unit. The O3 structure is equivalent to the structure of  $\alpha$ -NaFeO<sub>2</sub> and the cation ordering is also known in metallic alloys as L1<sub>1</sub> (CuPt prototype) <sup>[5]</sup>.



**Figure 1.** Representative O3 structure showing the abc stacking sequence of oxygen ions (red), thus creating various coordination environments for the alkali ion A (green) and metal ion M (blue). In an O3 repeat unit, M and A are coordinated below and above by oxygen layers. The beginning of another repeat unit with a-M-b stacking is in gray.

It is now well understood that the ordering of AO<sub>2</sub> and MO<sub>2</sub> in alternating layers is not the most favored cation ordering from an electrostatic perspective. Instead, the layered structure finds its stability in the size difference of A and M <sup>[G][Z]</sup> as it allows A-O and M-O bond distances to relax independently of each other. This independent A-O and M-O bond accommodation explains how a larger A cation, such as Na<sup>+</sup>, can form the layered structure with a wide range of M radii <sup>[B]</sup>, whereas a smaller A, such as Li<sup>+</sup>, only forms stable O3 compounds with a limited range of smaller M radii, namely  $Co^{3+}$  <sup>[D]</sup>,  $V^{3+}$  <sup>[10]</sup>, Ni<sup>3+</sup> <sup>[11]</sup>, and  $Cr^{3+}$  <sup>[10]</sup>.

# 2. Evolution from LiCoO<sub>2</sub> to NMC

Today, O3 cathodes have evolved in several directions from LiCoO<sub>2</sub> <sup>[12]</sup> for use cases beyond portable electronics. Anticipating potential cost and resource problems with Co [13], research in the 1980s and 1990s mostly focused on substitutions of Co by Ni <sup>[14]</sup>. However, consideration of the low cost of Mn and the high stability of the Mn<sup>4+</sup> charge state led the community towards layered LiMnO2. Even though this structure is not the thermodynamically stable state of LiMnO<sub>2</sub><sup>[15]</sup>, Delmas <sup>[16]</sup> and Bruce <sup>[17]</sup> were able to synthesize it by ion exchange from the stable NaMnO<sub>2</sub>. Unfortunately, the high mobility of Mn<sup>3+</sup> [18] leads to a rapid transformation of the layered structure into the spinel structure upon cycling  $\frac{19}{10}$  because of its pronounced energetic preference at the Li<sub>0.5</sub>MnO<sub>2</sub> composition  $\frac{20}{20}$ . Attempts to stabilize layered LiMnO<sub>2</sub> with AI [21] or Cr [22][23] substitution were only partially successful and led to the formation of a phase intermediate between layered and spinel <sup>[24]</sup>. Then, in 2001, several key papers were published that would pave the way for the highly successful Ni-Mn-Co (NMC) cathode series: Ohzuku showed very high capacity and cyclability in Li(Ni1/3Mn1/3Co1/3)O2  $\frac{[25]}{2}$ , known as NMC-111, and in Li(Ni<sub>1/2</sub>Mn<sub>1/2</sub>)O<sub>2</sub>  $\frac{[26]}{2}$ ; Lu and Dahn published their work on the Li(Ni<sub>x</sub>Co<sub>1-2x</sub>Mn<sub>x</sub>)O<sub>2</sub>  $\frac{[27]}{2}$  and its Co-free Li-excess version Li(Ni<sub>x</sub>Li<sub>1/3-2/x</sub>Mn<sub>2/3-x/3</sub>)O<sub>2</sub> <sup>[28]</sup>. In these compounds Ni is valence +2 and Mn is +4 <sup>[29]</sup>, thereby stabilizing the layered material against Mn migration and providing double redox from Ni<sup>2+</sup>/Ni<sup>4+</sup>. At this point the NMC cathode series was born. Since then, Ni-rich NMC cathodes have become of great interest to both academia and industry because they deliver a capacity approaching 200 mAh/g and demonstrate high energy density, good rate capability, and moderate cost [30][31][32]

In this short article, we summarize some general and fundamental understanding we have gained in layered oxide cathodes, without delving into issues with very specific compositions. We focus on the roles of the alkali–alkali interaction, electronic structure, and alkali diffusion, and illustrate how these fundamental features conspire to control the electrochemical behavior of O3-structured layered oxides.

## 3. Alkali–Alkali Interactions, Alkali/Vacancy Ordering, and Voltage Slope

The voltage of a cathode compound is set by the chemical potential of its alkali ions [33] which itself is the derivative of the free energy with respect to alkali concentration. This thermodynamic connection between voltage and free energy creates a direct relation between the voltage profile, the alkali-alkali interactions, and phase transformations as functions of alkali content. While Na<sub>x</sub>MO<sub>2</sub> compounds show many changes in the stacking of the oxygen host layers when the Na content is changed, phase transitions in Li<sub>x</sub>MO<sub>2</sub> materials are mostly driven by the Li-vacancy configurational free energy, resulting from Li<sup>+</sup>-Li<sup>+</sup> interactions in the layer  $\frac{[20][34]}{2}$ . In layered compounds with a single transition metal, such as Li<sub>x</sub>CoO<sub>2</sub> and Li<sub>x</sub>NiO<sub>2</sub>, such phase transitions are easily observed as voltage plateaus and steps in the electrochemical chargedischarge profiles as shown in Figure 2a. For a first-order phase transformation, for example from Phase I to Phase II, the Gibbs phase rule dictates that the Li chemical potential should be constant, hence the voltage remains constant while one phase transforms into the other. Phases in which the alkali ions are well-ordered usually display a rapid voltage change as the alkali content is changed, reflecting the high energy cost of trying to create off-stoichiometry in ordered phases. This is in contrast to solid solutions which have smoother voltage profiles as a function of alkali concentration. For example, both theory <sup>[35]</sup> and experiments <sup>[36][37]</sup> indicate that in Li<sub>x</sub>CoO<sub>2</sub> a monoclinic phase appears with lithium and vacancies ordered in rows for x  $\approx 0.5$  [36]. In Li<sub>x</sub>NiO<sub>2</sub>, Li-vacancy ordering is responsible for stable phases at x  $\sim 0.8$ ,  $\sim 0.5$ , and  $\sim 0.25-0.3$  [38] [39][40]. When many transition metals are mixed, as in NMC cathodes, the Li<sup>+</sup>-Li<sup>+</sup> interaction remains present, but Livacancy ordering is suppressed by the electrostatic and elastic perturbations on the Li site caused by the distribution of the Ni, Mn and Co in the transition metal layers.



**Figure 2.** (a) Typical charge–discharge of intercalation-based cathode materials. A voltage step indicates new phase formation. (b) Charge–discharge comparison of O3-Li<sub>x</sub>CoO<sub>2</sub>, P2-Na<sub>x</sub>CoO<sub>2</sub>, and P2-K<sub>x</sub>CoO<sub>2</sub>  $^{[41][42][43]}$ . Voltage curves for P2-Na<sub>x</sub>CoO<sub>2</sub>, P2-K<sub>x</sub>CoO<sub>2</sub>, P2-K<sub>x</sub>CoO<sub>2</sub>, and O3-Li<sub>x</sub>CoO<sub>2</sub> are reproduced with permissions from  $^{[41][42][43]}$ . The voltage curve for P2-K<sub>x</sub>CoO<sub>2</sub> is licensed under CC BY-NC 4.0  $^{[42]}$ .

The Li<sup>+</sup>-Li<sup>+</sup> interaction is mostly electrostatic but is highly screened by the charge density on the oxygen ions, leading to a rather small effective interaction in layered Li<sub>x</sub>MO<sub>2</sub> compounds and small voltage slope. This is a critical feature of Li<sub>x</sub>MO<sub>2</sub> compounds that gives them high capacity in a relatively narrow voltage window compared to other alkali compounds, as explained below. The effective interaction between intercalating ions increases significantly when larger alkali ions (e.g., Na<sup>+</sup> and K<sup>+</sup>) are used in the layered structure <sup>[44][45][46]</sup>. These larger alkali ions increase the oxygen slab distance, reducing the oxygen charge density available for screening within the alkali layer <sup>[20][45][46]</sup>. The larger effective repulsion between the Na<sup>+</sup> or K<sup>+</sup> ions affects the phase transition and electrochemistry in a very significant way as shown in Figure 2b. For example, Na<sub>x</sub>CoO<sub>2</sub> has stronger Na-vacancy ordering and thus more pronounced voltage steps compared to Li<sub>x</sub>CoO<sub>2</sub>. This phenomenon <sup>[41][47]</sup> becomes even more significant in K<sub>x</sub>CoO<sub>2</sub> <sup>[48][42]</sup>. The effect of the intercalant's size on the phase transitions and voltage steps is not just limited to Co-containing compounds but is also generally applicable to other transition metal systems as described in a recent review <sup>[46]</sup>.

#### References

- 1. Gamble, F.R.; Osiecki, J.H.; Cais, M.; Pisharody, R.; Disalvo, F.J.; Geballe, T.H. Intercalation complexes of lewis bases and layered sulfides: A large class of new superconductors. Science 1971, 174, 493–497.
- 2. Whittingham, M.S. Electrical Energy Storage and Intercalation Chemistry. Science 1976, 192, 1126–1127.
- 3. Mizushima, K.; Jones, P.C.; Wiseman, P.J.; Goodenough, J.B. LixCoO2 (0 < x < −1): A new cathode material for batteries of high energy density. Mater. Res. Bull. 1980, 15, 783–789.
- Delmas, C.; Fouassier, C.; Hagenmuller, P. Structural classification and properties of the layered oxides. Physica B+C 1980, 99, 81–85.
- 5. Ceder, G.; Van der Ven, A.; Marianetti, C.; Morgan, D. First-principles alloy theory in oxides. Model. Simul. Mater. Sci. Eng. 2000, 8, 311–321.
- Wu, E.J.; Tepesch, P.D.; Ceder, G. Size and charge effects on the structural stability of LiMO2 (M = transition metal) compounds. Philos. Mag. B 1998, 77, 1039–1047.
- 7. Hewston, T.A.; Chamberland, B.L. A Survey of first-row ternary oxides LiMO2 (M = Sc-Cu). J. Phys. Chem. Solids 1987, 48, 97–108.
- 8. Kim, S.; Ma, X.; Ong, S.P.; Ceder, G. A comparison of destabilization mechanisms of the layered NaxMO2 and LixMO2 compounds upon alkali de-intercalation. Phys. Chem. Chem. Phys. 2012, 14, 15571–15578.
- 9. Orman, H.J.; Wiseman, P.J. Cobalt(III) lithium oxide, CoLiO2: Structure refinement by powder neutron diffraction. Acta Crystallogr. Sect. C 1984, 40, 12–14.
- 10. Rüdorff, W.; Becker, H. Notizen: Die Strukturen von LiVO2, NaVO2, LiCrO2 und NaCrO2. Z. Nat. B 1954, 9, 614-615.
- 11. Dyer, L.D.; Borie, B.S.; Smith, G.P. Alkali Metal-Nickel Oxides of the Type MNiO2. J. Am. Chem. Soc. 1954, 76, 1499– 1503.
- 12. Manthiram, A.; Goodenough, J.B. Layered lithium cobalt oxide cathodes. Nat. Energy 2021, 6, 323.
- 13. Fu, X.; Beatty, D.N.; Gaustad, G.G.; Ceder, G.; Roth, R.; Kirchain, R.E.; Olivetti, E.A. Perspectives on Cobalt Supply through 2030 in the Face of Changing Demand. Environ. Sci. Technol. 2020, 54, 2985–2993.
- 14. Delmas, C.; Saadoune, I. Electrochemical and physical properties of the LixNi1-yCoyO2 phases. Solid State Ion. 1992, 53–56, 370–375.

- 15. Ceder, G. The Stability of Orthorhombic and Monoclinic-Layered LiMnO2. Electrochem. Solid-State Lett. 1999, 2, 550.
- 16. Capitaine, F.; Gravereau, P.; Delmas, C. A new variety of LiMnO2 with a layered structure. Solid State Ion. 1996, 89, 197–202.
- 17. Armstrong, A.R.; Bruce, P.G. Synthesis of layered LiMnO2 as an electrode for rechargeable lithium batteries. Nature 1996, 381, 499–500.
- 18. Reed, J.; Ceder, G.; Van Der Ven, A. Layered-to-Spinel Phase Transition in LixMnO2. Electrochem. Solid-State Lett. 2001, 4, A78.
- Shao-Horn, Y.; Hackney, S.A.; Armstrong, A.R.; Bruce, P.G.; Gitzendanner, R.; Johnson, C.S.; Thackeray, M.M. Structural Characterization of Layered LiMnO2 Electrodes by Electron Diffraction and Lattice Imaging. J. Electrochem. Soc. 1999, 146, 2404–2412.
- 20. Ceder, G.; Van der Ven, A. Phase diagrams of lithium transition metal oxides: Investigations from first principles. Electrochim. Acta 1999, 45, 131–150.
- 21. Jang, Y.; Huang, B.; Wang, H.; Sadoway, D.R.; Ceder, G.; Chiang, Y.; Liu, H.; Tamura, H. LiAlyCo1 yO2 (R-3m) Intercalation Cathode for Rechargeable Lithium Batteries. J. Electrochem. Soc. 1999, 146, 862–868.
- 22. Dahn, J.R.; Zheng, T.; Thomas, C.L. Structure and Electrochemistry of Li2CrxMn2-xO4 for  $1.0 \le x \le 1.5$ . J. Electrochem. Soc. 1998, 145, 851–859.
- Davidson, I.J.; McMillan, R.S.; Murray, J.J.; Greedan, J.E. Lithium-ion cell based on orthorhombic LiMnO2. J. Power Sources 1995, 54, 232–235.
- 24. Reed, J.S. Ab-Initio Study of Cathode Materials for Lithium Batteries. Ph.D. Thesis, Massachusetts Institute of Technology, Cambridge, MA, USA, 2003.
- Ohzuku, T.; Makimura, Y. Layered Lithium Insertion Material of LiCo1/3Ni1/3Mn1/3O2 for Lithium-Ion Batteries. Chem. Lett. 2001, 30, 642–643.
- Ohzuku, T.; Makimura, Y. Layered Lithium Insertion Material of LiNi1/2Mn1/2O2: A Possible Alternative to LiCoO2 for Advanced Lithium-Ion Batteries. Chem. Lett. 2001, 30, 744–745.
- 27. Lu, Z.; MacNeil, D.D.; Dahn, J.R. Layered Li[NixCo1-2xMnx]O2 Cathode Materials for Lithium-Ion Batteries. Electrochem. Solid-State Lett. 2001, 4, A200.
- 28. Lu, Z.; MacNeil, D.D.; Dahn, J.R. Layered Cathode Materials Li[NixLi1/3-2x/3Mn2/3-x/3]O2 for Lithium-Ion Batteries. Electrochem. Solid-State Lett. 2001, 4, A191.
- 29. Reed, J.; Ceder, G. Charge, Potential, and Phase Stability of Layered Li(Ni0.5Mn0.5)O2. Electrochem. Solid-State Lett. 2002, 5, A145.
- Manthiram, A.; Song, B.; Li, W. A perspective on nickel-rich layered oxide cathodes for lithium-ion batteries. Energy Storage Mater. 2017, 6, 125–139.
- 31. Kim, J.; Lee, H.; Cha, H.; Yoon, M.; Park, M.; Cho, J. Prospect and Reality of Ni-Rich Cathode for Commercialization. Adv. Energy Mater. 2018, 8, 1702028.
- 32. Zhu, L.; Bao, C.; Xie, L.; Yang, X.; Cao, X. Review of synthesis and structural optimization of LiNi1/3Co1/3Mn1/3O2 cathode materials for lithium-ion batteries applications. J. Alloys Compd. 2020, 831, 154864.
- Aydinol, M.K.; Ceder, G. First-Principles Prediction of Insertion Potentials in Li-Mn Oxides for Secondary Li Batteries. J. Electrochem. Soc. 1997, 144, 3832–3835.
- 34. Li, W.; Reimers, J.N.; Dahn, J.R. Lattice-gas-model approach to understanding the structures of lithium transition-metal oxides LiMO2. Phys. Rev. B 1994, 49, 826–831.
- 35. Van der Ven, A.; Aydinol, M.K.; Ceder, G.; Kresse, G.; Hafner, J. First-principles investigation of phase stability in LixCoO2. Phys. Rev. B 1998, 58, 2975–2987.
- Reimers, J.N.; Dahn, J.R. Electrochemical and In Situ X-ray Diffraction Studies of Lithium Intercalation in LixCoO2. J. Electrochem. Soc. 1992, 139, 2091–2097.
- Shao-Horn, Y.; Levasseur, S.; Weill, F.; Delmas, C. Probing Lithium and Vacancy Ordering in O3 Layered LixCoO2 (x ≈ 0.5). J. Electrochem. Soc. 2003, 150, A366.
- Li, W.; Reimers, J.N.; Dahn, J.R. In situ x-ray diffraction and electrochemical studies of Li1–xNiO2. Solid State Ion. 1993, 67, 123–130.
- Peres, J.P.; Weill, F.; Delmas, C. Lithium/vacancy ordering in the monoclinic LixNiO2 (0.50 ≤ x ≤ 0.75) solid solution. Solid State Ion. 1999, 116, 19–27.

- 40. Arai, H.; Okada, S.; Ohtsuka, H.; Ichimura, M.; Yamaki, J. Characterization and cathode performance of Li1–xNi1+xO2 prepared with the excess lithium method. Solid State Ion. 1995, 80, 261–269.
- 41. Berthelot, R.; Carlier, D.; Delmas, C. Electrochemical investigation of the P2–NaxCoO2 phase diagram. Nat. Mater. 2011, 10, 74–80.
- 42. Kim, H.; Kim, J.C.; Bo, S.-H.; Shi, T.; Kwon, D.-H.; Ceder, G. K-Ion Batteries Based on a P2-Type K0.6CoO2 Cathode. Adv. Energy Mater. 2017, 7, 1700098.
- 43. Sun, Y.-K.; Han, J.-M.; Myung, S.-T.; Lee, S.-W.; Amine, K. Significant improvement of high voltage cycling behavior AIF3-coated LiCoO2 cathode. Electrochem. Commun. 2006, 8, 821–826.
- 44. Kim, H.; Ji, H.; Wang, J.; Ceder, G. Next-Generation Cathode Materials for Non-aqueous Potassium-Ion Batteries. Trends Chem. 2019, 1, 682–692.
- Lee, W.; Kim, J.; Yun, S.; Choi, W.; Kim, H.; Yoon, W.-S. Multiscale factors in designing alkali-ion (Li, Na, and K) transition metal inorganic compounds for next-generation rechargeable batteries. Energy Environ. Sci. 2020, 13, 4406– 4449.
- 46. Tian, Y.; Zeng, G.; Rutt, A.; Shi, T.; Kim, H.; Wang, J.; Koettgen, J.; Sun, Y.; Ouyang, B.; Chen, T.; et al. Promises and Challenges of Next-Generation "Beyond Li-ion" Batteries for Electric Vehicles and Grid Decarbonization. Chem. Rev. 2021, 121, 1623–1669.
- 47. Xu, J.; Lee, D.A.E.H.O.E.; Meng, Y.S. Recent advances in sodium intercalation positive electrode materials for sodium ion batteries. Funct. Mater. Lett. 2013, 6, 1330001.
- 48. Hironaka, Y.; Kubota, K.; Komaba, S. P2- and P3-KxCoO2 as an electrochemical potassium intercalation host. Chem. Commun. 2017, 53, 3693–3696.

Retrieved from https://encyclopedia.pub/entry/history/show/25892