Silicon-Based Nanomaterials

Subjects: Nanoscience & Nanotechnology

Contributor: Marina Martínez-Carmona , María Vallet-Regí

Laser ablation is a technique by which a laser beam is focused on a substrate to remove part of the material from the irradiated surface. Under the right conditions, nanomaterials of the desired size and in the absence of additional substances are obtained. This green methodology applied to a silicon substrate produces silicon-based nanomaterials, which include the characteristic advantages of these materials and reduce the potential toxicity. The applicability of these nanomaterials for nanomedicine is incalculable. This review highlights the latest advances in the treatment of bacterial infection with silicon-based nanomaterials and points out the future challenges in this field.

laser ablation silicon silica nanoparticles nanomaterials bacteria infection biofilm

1. Definition

Nanomaterials have unique properties and characteristics derived from their shape and small size that are not present in bulk materials. If size and shape are decisive, the synthesis method used, which determines the above parameters, is equally important. Among the different nanomaterial's synthesis methods, we can find chemical methods (microemulsion, sol-gel, hydrothermal treatments, etc.), physical methods (evaporation-condensation, laser treatment, etc.) and biosynthesis. Among all of them, the use of laser ablation that allows obtaining non-toxic nanomaterials (absence of foreign compounds) with a controlled 3D size, has emerged in recent years as a simple and versatile alternative for the synthesis of a wide variety of nanomaterials with numerous applications. This manuscript reviews the latest advances in the use of laser ablation for the synthesis of silicon-based nanomaterials, highlighting its usefulness in the prevention of bacterial infection.

2. Antibacterial Effect of Silicon-Based Nanomaterials

Over time, bacteria are becoming more resistant to the use of antibiotics, which forces the investigation of new treatments for fighting bacterial infections. One of the alternatives that is gaining importance to solve this problem is the use of nanomaterials for drug delivery, reducing the dose and increasing the effectiveness of antibiotics. Recently, many studies have reported the value of silicon-based nanomaterial treatments at different stages of bacterial infection, from its early detection to its destruction once the biofilm has been formed (Figure 1).



Figure 1. Silicon-based nanomaterials used for the treatment of bacterial infection depending on the stage in which they operate. (**a**) Bacteria Detection. (**b**) Effect on Planktonic Bacteria. (**c**) Effect on Biofilm.

Among the possible stages for the treatment of bacterial infection (detection, action on planktonic bacteria, and action on the biofilm) that can be intervened, the use of silicon-based nanomaterials created by laser ablation, has preferably focused on the creation of anti-adherent surfaces to prevent the biofilm formation. Reason why the present manuscript focuses on describing its usefulness in this stage.

Smirnov et al. prepared silicon nanoparticles by means of the laser ablation of a solid silicon target in water and isopropyl alcohol media [1]. These nanoparticles formed a uniform surface coating onto a silicon wafer and their hydrophobicity and antifouling ability were tested. For studying the hydrophobicity, a drop of water was added on the top of the materials and the contact angle was measured. Silicon nanoparticles obtained in alcohol probed to have a greater hydrophobicity.
Regarding the antibacterial effect of the nanocoating, both of them presented stronger inhibitory effect on the *S. aureus* and *P. aeruginosa* biofilm formation compared to the non-ablated silicon sample. The authors attribute this antimicrobial effect to the generation of reactive oxygen species formed on the surface of Si nanoparticles during their production. Lately, an study in terms of productivity for nanosecond-laser plasma-mediated ablation regimes of these nanoparticles in water was performed [2].

Sometimes the laser ablation of the substrate does not lead to the formation of nanomaterials but to certain periodically aligned nanostructures that are called LIPSS (Laser-Induced Periodic Surface Structures). Controversy exists over the process by which these structures are formed. Some authors attribute them to a process of interference between the incident electromagnetic wave and that reflected and scattered by the material that gives rise to a pattern that affects only certain parts of the surface [3].

Others propose that it is the result of self-organization of the material surface during relaxation after application of the pulses [4]. Kudryashov et al. used picosecond IR-laser pulses to irradiate a Si wafer surface in liquid CS_2 to produce Si ripples nanosheet arrays via nanoplasmonic ablative self-organization [5]. The antifouling capacity of the material was tested by culturing the nanosheet with *Staphylococcus aureus* bacteria for 18 h. “Live/Dead Biofilm Viability Kit” was used to study the viability of bacteria, showing the absence of the biofilm and the death of almost all the bacteria. Contrary, the appearance of a biofilm was observed for both controls: smooth Si wafer and silica glass slide.

In addition to the usefulness of pure silicon-based nanomaterials in preventing bacterial infection, some articles have reported that their combination with other materials or small molecules (such as antibiotics) that have bactericidal properties improves its action against microorganisms. For instance, it was observed that the coating of Si ripples nanosheets with Se, TeO_2, Sb_2O_3, and Ag NPs nanoparticles, capable of damaging the bacterial DNA by the production of ROS, increased the antibacterial properties of the surfaces. Being the sample that combined Si nanoripples and TeO_2 the most effective for biofilm prevention [6].

The addition of antibiotics to the silicon-based nanostructures is another strategy to increase the antibacterial effect. For most of the materials the ablation temperature is lower than the decomposition temperature, however, for some polymers, biomolecules, proteins, antibiotics, etc. this standard is not followed. These materials are very sensitive to temperature and degrade easily.

In order to achieve a fine coating of these organic materials, a modification called matrix-assisted pulsed laser evaporation (MAPLE) is used. In MAPLE, the sensitive compound is dissolved or dispersed in an inert solvent and then frozen to form a solid substrate. During laser ablation, the volatile solvent absorbs most of the laser energy whereas the intact molecule of interest acquires enough kinetic energy to be transported and form a uniform film on the desired surface. This variation was used by Mihaiescu et al. to create magnetite/salicylic acid/silica shell/antibiotics thin films [7]. The authors reported that despite the differences found for both types of bacteria (*S. aureus and P. aeruginosa*), the thin films exhibited an inhibitory effect for the biofilm formation.

Although the application of these nanomaterials to prevent bacterial infection is the majority, an article was recently published highlighting their usefulness as a probe. Kögler et al. combined the ability of gold nanoparticles to enhance Raman scattering (surface-enhanced Raman scattering, SERS) with the silicon biocompatibility to create mobile SERS probes for bacteria detection [8]. Three types of gold nanoparticles with increasing concentrations of silicon (0%, 40%, and 70%) were synthesized. As the amount of silicon increased, the size of the particles and the capacity to serve as SERS probes (assessed by studying the enhancement of Rhodamine 6G as a model molecule) decreased. Gold 60% nanoparticles were selected as optimal and used to test their applicability as biosensors against two different bacteria species: *L. innocua and E. coli.* Raman spectra of *L. innocua* using only the patterned SERS substrate or combined with Au-60% NPs gave rise to similar peaks, however, the intensity of the signal for the combined detection was 4.4-times higher. When the experiment was carried out in the presence of *E. coli*, the autofluorescence of the bacteria was so high that it prevented their detection. However, the use of time-gating solved the autofluorescence problem and allowed to register a spectrum that in the presence of nanoparticles was more than one order of magnitude greater than only with the substrate and which revealed a variety of novel Raman lines.

3.Conclusions and Future Perspectives

The mechanisms of laser ablation for obtaining silicon-based nanomaterials is well documented, however, there is little information about their application for the treatment of bacterial infection. This implies that much remains to be discovered on this topic and therefore it is an interesting field to investigate. Most of the publications related to the

use of Silicon-based nanomaterials synthesized by laser ablation for the treatment of infection focus on the creation of non-stick surfaces. It would be of great scientific value to study the antibacterial effect that these nanomaterials have in the different stages of infection and to see if the same material can have a long-lasting efficient action. In the same way, a comparative study between silica and silicon nanomaterials would provide great information on the similarities and differences of both materials with respect to antibacterial activity, allowing the most suitable material to be chosen in each case. Furthermore, since silicon-based nanomaterials produced by laser ablation are of the same nature as silicon-derived nanomaterials synthesized by chemical and biogenic methods, it would be of great interest to synthesize equivalent materials by these three routes and compare their effects on various bacterial strains. These studies would shed light on whether the synthesis method itself has any effect on the antibacterial activity of nanomaterials.

References

1. N A Smirnov; Sergey Kudryashov; A A Nastulyavichus; A A Rudenko; I N Saraeva; E R Tolordava; S A Gonchukov; Yu M Romanova; A A Ionin; D A Zayarny; et al. Antibacterial properties of silicon nanoparticles. *Laser Physics Letters* **2018**, *15*, 105602, 10.1088/1612-202x/aad853.
2. Sergey Kudryashov; Alena A. Nastulyavichus; Anastasiya K. Ivanova; Nikita A. Smirnov; Roman A. Khmelnitskiy; Andrey A. Rudenko; Irina N. Saraeva; Etery R. Tolordava; Alexander Yu. Kharin; Irina N. Zavestovskaya; et al.Yulia M. RomanovaDmitry A. ZayarnyAndrey A. Ionin High-throughput laser generation of Si-nanoparticle based surface coatings for antibacterial applications. *Applied Surface Science* **2019**, *470*, 825-831, 10.1016/j.apsusc.2018.11.201.
3. Jörn Bonse; Sandra Hohm; Sabrina V. Kirner; Arkadi Rosenfeld; Jorg Kruger; Laser-Induced Periodic Surface Structures— A Scientific Evergreen. *IEEE Journal of Selected Topics in Quantum Electronics* **2016**, *23*, 1-1, 10.1109/jstqe.2016.2614183.
4. J Reif; Florenta Costache; Matthias Henyk; Stanislav V. Pandelov; Ripples revisited: non-classical morphology at the bottom of femtosecond laser ablation craters in transparent dielectrics. *Applied Surface Science* **2002**, *197*, 891-895, 10.1016/s0169-4332(02)00450-6.
5. Sergey Kudryashov; Luong V. Nguyen; Demid A. Kirilenko; Pavel N. Brunkov; Andrey A. Rudenko; Nikolay I. Busleev; Alexander L. Shakhmin; Alexander V. Semencha; Roman A. Khmelnitsky; Nikolay N. Melnik; et al.Irina N. SaraevaAlena A. NastulyavichusAndrey A. IoninEteri R. TolordavaYulia M. Romanova Large-Scale Laser Fabrication of Antifouling Silicon-Surface Nanosheet Arrays via Nanoplasmonic Ablative Self-Organization in Liquid CS2 Tracked by a Sulfur Dopant. *ACS Applied Nano Materials* **2018**, *1*, 2461-2468, 10.1021/acsanm.8b00392.
6. Irina N Saraeva; Eteri R Tolordava; Alyona A Nastulyavichus; Anastasiya K Ivanova; Sergey I Kudryashov; Andrey A Rudenko; Nikolay N Melnik; Dmitriy A Zayarny; Andrey A Ionin; Yulia M Romanova; et al.Sergey A Gonchukov A bacterial misericorde: laser-generated silicon nanorazors

with embedded biotoxic nanoparticles combat the formation of durable biofilms. *Laser Physics Letters* **2020**, *17*, 025601, 10.1088/1612-202x/ab5fca.

7. Dan Eduard Mihaiescu; R. Cristescu; G Dorcioman; C E Popescu; C Nita; G Socol; I N Mihailescu; Alexandra Elena Stoica; D Tamas; Monica Enculescu; et al.R F NegreaC GhicaC ChifiriucCoralia BleotuD B ChriseyMariana Chifiriuc Functionalized magnetite silica thin films fabricated by MAPLE with antibiofilm properties. *Biofabrication* **2012**, *5*, 015007, 10.1088/1758-5082/5/1/015007.
8. Martin Kogler; Yu. V. Ryabchikov; Sanna Uusitalo; Alexey Popov; Anton Popov; Gleb Tselikov; Anna-Liisa Välimaa; Ahmed Al-Kattan; Jussi Hiltunen; Riitta Laitinen; et al.Peter NeubauerIgor MeglinskiAndrei Kabashin Bare laser-synthesized Au-based nanoparticles as nondisturbing surface-enhanced Raman scattering probes for bacteria identification. *Journal of Biophotonics* **2018**, *11*, e201700225, 10.1002/jbio.201700225.

Retrieved from https://encyclopedia.pub/entry/history/show/3387