

Pillararenes Trimer for Self-Assembly

Subjects: Nanoscience & Nanotechnology

Contributor: Huacheng Zhang

Pillararenes trimer with particularly designed structural geometry and excellent capacity of recognizing guest molecules is a very efficient and attractive building block for the fabrication of advanced self-assembled materials. Pillararenes trimers could be prepared via both covalent and noncovalent bonds. The classic organic synthesis reactions such as click reaction, Palladium-catalyzed coupling reaction, amidation, esterification and aminolysis are employed to build covalent bonds and integrate three pieces of pillararenes subunits together into the “star-shaped” trimers and linear foldamers. Alternatively, pillararenes trimers could also be assembled in the form of host-guest inclusions and mechanically interlocked molecules via noncovalent interactions, and during those procedures, pillararenes units contribute the cavity for recognizing guest molecules and act as a “wheel” subunit, respectively. By fully utilizing the driving forces such as host-guest interactions, charge transfer, hydrophobic, hydrogen bonding, C—H \cdots π and π — π stacking interactions, pillararenes trimers-based supramolecular self-assemblies provide a possibility in the construction of multi-dimensional materials such as vesicular and tubular aggregates, layered networks, as well as frameworks. Interestingly, those assembled materials exhibit interesting external stimuli responsiveness to *e.g.*, variable concentrations, changed pH values, different temperature, as well as the addition/removal of competition guests and ions. Thus, they could further be used for diverse applications such as detection, sorption and separation of significant multi-analytes including metal cations, anions and amino acids.

Keywords: Pillararenes trimers ; Supramolecular interactions ; Self-assembly ; Synthesis ; Applications

1. Introduction


Self-assembly has attracted much more attention in fundamental researches of material science and interesting applications to practical engineering areas [1], *e.g.*, providing not only inspiring methodological strategy in processing, but also solid functional materials to balance morphologies and properties. Building ideal self-assembly begins from the molecular level [1], *i.e.*, designing the structural geometry of molecules, modifying them with proper functional moieties, introducing and choosing proper inter/intramolecular interactions, as well as controlling the behavior of assembled molecules. Thus, designing appropriate building blocks from the molecular level is very significant in the construction of multi-dimensional self-assembly [1].


Macrocycles is a kind of particular cyclic oligomers with the hollow cavity for recognizing guest molecules [1], providing a possibility to introduce more functional and sensitive moieties for the fabrication of building blocks, as well as controllable self-assembly through supramolecular interactions such as host-guest interactions [1]. Pillararenes is a rising star in macrocycles [1], due to its high synthesis yield and convenient modifications. Different from other macrocycles, pillararenes composed by repeated phenol subunits possesses the electron-rich cavity and more rigid chemical structures, leading to its unique physiochemical properties such as planar chirality, as well as recognition towards neutral and electron-deficient guests. Interestingly, functionalized pillararenes monomers and dimers have been used as the building blocks to construct self-assemblies such as vesicular and polymeric architectures with small guest molecules as the template, but their morphologies are still limited [1].

2. Influence and application


To enlarge the family of assemblies with controllable multi-dimensional morphologies such as two-dimensional materials, pillararenes trimers have been designed and have attracted much more attentions recently. Different from pillararenes monomers and dimers, pillararenes trimers integrate three pieces of pillararenes units together via a “core” bridge, contribute a planar geometry as building blocks for advanced self-assemblies, and generate unique physiochemical properties such as aggregation-induced absorption [1]. We briefly summarized the recent progress about pillararenes trimers (**PT1–PT10** according to the timeline, Table 1 and Scheme 1), their synthesis method, supramolecular interactions with *e.g.*, guest molecules (**G1–G9**, Scheme 2), driving forces for self-assembly, the fabrication of advanced self-

assembly, and current applications in the review [14]. We will try to find the issues and concerns in the development of pillararenes trimers and their advanced self-assembly. For example, pillararenes trimer could be prepared via both covalent and noncovalent bonds[2][3][4][5][6][7][8][9][10][11][12]. The selection of the synthesis strategy and functional precursors (Scheme 3 and Table 1) will become significant because it will further affect the molecular geometry including “star-shaped” molecules and linear foldamers, as well as driving forces for next-step self-assembly, e.g., by utilizing unoccupied pillararenes cavities via host-guest interactions or functional groups from modifications via other supramolecular interactions. In addition, the precise control over the self-assembly is always the key point during practical applications. Thus, we will analyze the sensitive supramolecular interactions of pillararenes trimers-based self-assemblies in details [14].






Scheme 1. Chemical structures of pillararenes trimers (**PT1–PT10**).



Scheme 2. Chemical structures of guest molecules (**G1–G9**).



Scheme 3. Chemical structures of precursors for the synthesis of pillararenes trimer, as well as other significant building blocks for the construction of assemblies (X1–X13).

Table 1. Comparison of various pillararenes trimer (PT1–PT10), guest molecules (G1–G9), precursors, and other significant building blocks (X1–X13) for self-assembly and external stimuli responsiveness.

Pillararenes Trimer	Guest	Precursor	Interactions	Assembly	External Stimuli	Applications	Ref
PT1	G1	X1	Host-guest interactions	Hollow spherical, tubular and layered assemblies	Concentration-dependent	Morphological control in comparison with X2	[12]
PT2	G2	-	Host-guest interactions	Supramolecular hyperbranched alternating polymers	K ⁺ (crown ether X3)	-	[13]

Pillararenes Trimer	Guest	Precursor	Interactions	Assembly	External Stimuli	Applications	Ref
PT3	-	X4	Hydrogen bonding, van der Waals forces, C-H \cdots π and π - π stacking interactions	Supramolecular polymer	Cations	Fluorescence detection and separation of Hg ²⁺	[^[4]]
PT4	G3/G4	X5	Host-guest interactions	Supramolecular polymer	-	-	[^[5]]
PT5	G5	X6	Hydrogen bonding, π - π stacking and host-guest interactions	Hyperbranched supramolecular polymer	Heat and acid/base	-	[^[6]]
PT6	-	X7/X8	π - π stacking interactions	(Metal ions coordinated) supramolecular organic frameworks	Fe ³⁺ /Hg ²⁺ /Cr ³⁺ and CN ⁻ /H ₂ PO ₄ ⁻	Fluorescence ultrasensitive detection	[^[7]]
PT7	G6	X9	Hydrogen bonding, C-H \cdots π and π - π stacking interactions	Supramolecular polymer network/supramolecular polymer framework	Metal cations/anions/amino acid	Fluorescence detection/adsorption capacity for cations	[^[8]]
PT8	G7	X10	-	-	Competitive complexation with Anions	Fluorescence detection of F ⁻ /AcO ⁻ /H ₂ PO ₄ ⁻	[^[9]]
PT9	G8	X11	Mechanical interlocked molecule	Dendrimer	-	-	[^[10]]
PT10	G9	X12	Mechanical interlocked molecule	Dendrimer	Dimethylsulfoxide and acetate anion	-	[^[11]]
X13 \supset G6	G6	X13	Hydrogen bonding, π - π stacking and host-guest interactions	Supramolecular polymer networks/gel	Heat/cooling, pH, competitive guests and mechanical	Dye sorption, ultrasensitive detection and separation of Fe ³⁺	[^[12]]

References

- Zhang, H.; Liu, Z.; Fu, H.; Pillararenes Trimer for Self-assembly. *Nanomaterials* **2020**, *10*, 651, .
- Zhang, H.; Nguyen, K. T.; Ma, X.; Yan, H.; Guo, J.; Zhu, L.; Zhao, Y.; Host-guest complexation driven dynamic supramolecular self-assembly. *Org. Biomol. Chem.* **2013**, *11*(13), 2070-2074, .
- Li, H.; Fan, X.; Shang, X.; Qi, M.; Zhang, H.; Tian, W.; A triple-monomer methodology to construct controllable supramolecular hyperbranched alternating polymers. *Polym. Chem.* **2016**, *7*, 4322-4325, .
- Jiang, X.-M.; Huang, X.-J.; Song, S.-S.; Ma, X.-Q.; Zhang, Y.-M.; Yao, H.; Tai-BaoWei; Lin, Q.; Tri-pillar[5]arene-based multi-stimuli-responsive supramolecular polymers for fluorescence detection and separation of Hg²⁺. *Polym. Chem.* **2018**, *9*, 4625-4630, .
- Liu, L.-Z.; Qin, X.; Duan, W.-G.; Huang, H.-F.; Zhang, W.-X.; Zhou, Q.-Q.; Huang, Y.; Aggregation-induced near-infrared absorption of a pillar[5]arene trimer by charge transfer interaction. *Dyes Pigm.* **2018**, *158*, 390-395, .
- Jiang, Y.-Q.; Wu, K.; Zhang, Q.; Li, K.-Q.; Li, Y.-Y.; Xin, P.-Y.; Zhang, W.-W.; Guo, H.-M.; A dual-responsive hyperbranched supramolecular polymer constructed by cooperative host-guest recognition and hydrogen-bond interactions. *Chem. Commun.* **2018**, *54*, 13821-13824, .
- Wei, T.-B.; Ma, X.-Q.; Fan, Y.-Q.; Jiang, X.-M.; Dong, H.-Q.; Yang, Q.-Y.; Zhang, Y.-F.; Yao, H.; Lin, Q.; Zhang, Y.-M.; et al. Aggregation-induced emission supramolecular organic framework (AIE SOF) gels constructed from tri-pillar[5]arene-

- based foldamer for ultrasensitive detection and separation of multi-analytes. *Soft Matter* **2019**, *15*, 6753-6758, .
8. Liu, J.; Fan, Y.-Q.; Song, S.-S.; Gong, G.-F.; Wang, J.; Guan, X.-W.; Yao, H.; Zhang, Y.-M.; Wei, T.-B.; Lin, Q.; et al. Aggregation-Induced Emission Supramolecular Organic Framework (AIE SOF) Gels Constructed from Supramolecular Polymer Networks Based on Tripodal Pillar[5]arene for Fluorescence Detection and Efficient Removal of Various Analytes. *ACS Sustainable Chem. Eng.* **2019**, *7*, 11999-12007, .
9. Khadieva, A.; Gorbachuk, V.; Shurpik, D.; Stoikov, I.; Synthesis of Tris-pillar[5]arene and Its Association with Phenothiazine Dye: Colorimetric Recognition of Anions. *Molecules* **2019**, *24*(9), 1807, .
10. Wang, W.; Chen, L. J.; Wang, X. Q.; Sun, B.; Li, X.; Zhang, Y.; Shi, J.; Yu, Y.; Zhang, L.; Liu, M.; et al. Organometallic rotaxane dendrimers with fourth-generation mechanically interlocked branches. *Proc. Natl. Acad. Sci.* **2015**, *112*(18), 5597-5601, .
11. Wang, X. Q.; Wang, W.; Li, W. J.; Chen, L. J.; Yao, R.; Yin, G. Q.; Wang, Y. X.; Zhang, Y.; Huang, J.; Tan, H.; et al. Dual stimuli-responsive rotaxane-branched dendrimers with reversible dimension modulation. *Nat. Commun.* **2018**, *9*(1), 3190, .
12. Guan, X.-W.; Lin, Q.; Zhang, Y.-M.; Wei, T.-B.; Wang, J.; Fan, Y.-Q.; Yao, H.; Pillar[5]arene-based spongy supramolecular polymer gel and its properties in multi-responsiveness, dye sorption, ultrasensitive detection and separation of Fe³⁺. *Soft Matter* **2019**, *15*, 3241-3247, .
-

Retrieved from <https://encyclopedia.pub/entry/history/show/7926>