

Chemical Rings

Subjects: Chemistry, Applied | Engineering, Chemical | Green & Sustainable Science & Technology

Contributor: Vincenzo Russo, Francesco Taddeo, Pasi Tolvaren

The epoxidized group, also known as the oxirane group, can be considered as one of the most crucial rings in chemistry. Due to the high ring strain and the polarization of the C–O bond in this three-membered ring, several reactions can be carried out. One can see such a functional group as a crucial intermediate in fuels, polymers, materials, fine chemistry, etc.

Keywords: heterogeneous catalyst ; enzymatic catalyst ; epoxidation ; epoxidized vegetable oils ; ethylene and propylene oxide

1. Introduction

Three-membered rings are fascinating chemical functional groups because they represent an excellent compromise between stability and reactivity. The oxirane ring, consisting of two carbons and one oxygen atom, is the most representative of these three-membered rings. The synthesis of this ring is most often performed by the oxidation of unsaturated groups. Another name for this reaction is epoxidation. This reaction can be undertaken in gas, liquid or liquid–liquid systems, where a catalyst plays an important role. An overview of common epoxidation methods and routes are shown in **Figure 1**.




Figure 1. Overview of common epoxidation methods and routes.

Epoxides are valuable chemical intermediates and can be used in different sectors such as surfactants, resins, fine chemicals or polymers. The interaction between carbon dioxide and epoxide [1] can produce other valuable intermediates: carbonates. According to some research groups [2][3], this reaction can contribute to valorize carbon dioxide. These carbonates are promising materials for the production of polymers such as polyurethanes [4][5].

2. Synthesis of Ethylene and Propylene Oxide

The attained products in the ethylene oxidation are ethylene oxide, acetaldehyde, CO₂ and H₂O [6], where CO₂ is thermodynamically more stable in respect to ethylene oxide and acetaldehyde [7].

In ethylene oxide production, silver is the heterogeneous catalyst which leads to a high selectivity towards the desired product [6][8]. However, this value depends on the diameter of Ag particles supported on α -Al₂O₃; more precisely the selectivity increases with the increasing of the particle diameter, as within an in-series mechanism, smaller particles lead

to higher reactivity, thus lower selectivity referred to the intermediate specie (e.g., epoxide) [6].

Different ways to produce propylene oxide exist and between them, the chlorohydrin process represents one of the most used as well as hydroperoxide process which produce tert-butyl alcohol and styrene as coproducts [9].

Another promising catalyst for its high selectivity in propylene oxidation is Cu; in the last period, copper-based catalysts are becoming more important as they can be used in several applications [10]. One of the reasons why their use is increasing is their cheapness as well as the high selectivity towards the propylene oxide, as mentioned before. For example, in the literature it is reported that in the presence of Cu/SiO₂ a propylene oxide selectivity of 53% was reached for a conversion of 0.25% [11].

3. Synthesis of Epoxidized Vegetable Oils

At the moment, the largest market share of vegetable oils account for palm oil (46%)—it is cultivated extensively since it is used both in cooking as well as in the rapidly growing biofuel industry [12]. Regardless of edible or not, epoxidized vegetable oils can be used as such as lubricants or modified further into cosmetic products, surfactants, paint ingredients, resins or biopolymers. This field of research has increased drastically during the last 15 years due to the concern of global warming and the mutual intention to reduce fossil-based, CO₂-polluting production processes. Vegetable oils can be chemically modified in numerous ways, such as transesterification, epoxidation, hydroxylation, carboxylation, halogenation, hydrogenation, and oxidation. However, their epoxidation has gained a lot of attention due to the high reactivity of the epoxide group [13].

Even though epoxidation has been known for over 100 years, it has not been widely used for modification of vegetable oils until there became a market need for renewable building blocks. Before the 1990s, there was not much research related to epoxidation of vegetable oils, see **Figure 2**. The classical Prilezhaev epoxidation has been studied by different aspects in several groups since then.




Figure 2. Number of publications per year with the search words vegetable oil epoxidation and oleic acid epoxidation, obtained from webofscience.com (some are overlapping).

There are approximately 30 review papers concerning vegetable oil epoxidation—the most recent dealing with a general overview of synthetic approaches [14], catalytic epoxidation and analysis of products [13], end-product related i.e., lubrication [15] or bio-resin [16], and process intensification-related i.e., microwave-assisted epoxidation [17]. Some reviews focus on the type of vegetable oil that is used, i.e., tall oil [18].

One drawback with the system is that it operates in several phases and therefore, the reaction velocity is limited by a slow mass transfer of the reactive species between the phases. Another drawback is that it works best with high-oleic acid (C18:1) vegetable oils, whereas the epoxidation of linoleic acid groups and higher unsaturation fatty acids, may sterically hinder the reaction [19].

4. Synthesis of Epichlorohydrin

The intermediate, DCH, could be directly produced from glycerol and hydrogen chloride without chlorine. Therefore, this type of reaction system has many advantages such as more resources, shorter technical processes, less investment, less consumption of water and energy, safer operation, fewer byproducts containing chloride, and is more environmentally

friendly.

For the reaction system with hydrogen chloride liquid, during the chlorination step, the high content of moisture brought by the liquid of hydrochloric acid into the reaction system could lead to a lower yield of dichlorohydrin through decelerating the reaction rate, prolonging the reaction time, and promoting the production of byproducts. Therefore, dehydration is the most critical procedure in this chlorination system. The reaction system with hydrogen chloride gas results in a high yield of dichlorohydrin with the advantages of increasing reaction rate and reducing reaction time. Also, hydrogen chloride gas could be produced by the reaction of sodium chloride with concentrated sulfuric acid or the reaction of phosphorus trichloride with hydrochloric acid.

Moreover, the yield of ECH will be low once the reaction system contains an excess of alkaline solution leading to the accelerated hydrolysis of ECH to glycerol. Thus, ECH should be collected immediately to avoid the formation of byproducts. Moreover, the epoxidation of DCH and the yield of ECH can be easily affected by factors including mole ratio, temperature, reaction time, the existence of mineral salt.

References

1. Cai, X.; Zheng, J.L.; Wärnå, J.; Salmi, T.; Taouk, B.; Leveneur, S. Influence of gas-liquid mass transfer on kinetic modelling: Carbonation of epoxidized vegetable oils. *Chem. Eng. J.* 2017, 313, 1168–1183.
2. Kiatkittipong, K.; Shukri, M.A.A.M.; Kiatkittipong, W.; Lim, J.W.; Show, P.L.; Lam, M.K.; Assabumrungrat, S. Green pathway in utilizing CO₂ via cycloaddition reaction with epoxide-A mini review. *Processes* 2020, 8, 548.
3. Subramanian, S.; Song, Y.; Kim, D.; Yavuz, C.T. Redox and Nonredox CO₂ Utilization: Dry Reforming of Methane and Catalytic Cyclic Carbonate Formation. *ACS Energy Lett.* 2020, 5, 1689–1700.
4. Pérez-Sena, W.Y.; Cai, X.; Kebir, N.; Vernières-Hassimi, L.; Serra, C.; Salmi, T.; Leveneur, S. Aminolysis of cyclic-carbonate vegetable oils as a non-isocyanate route for the synthesis of polyurethane: A kinetic and thermal study. *Chem. Eng. J.* 2018, 346, 271–280.
5. Guzmán Agudelo, A.F.; Pérez-Sena, W.Y.; Kebir, N.; Salmi, T.; Ríos, L.A.; Leveneur, S. Influence of steric effects on the kinetics of cyclic-carbonate vegetable oils aminolysis. *Chem. Eng. Sci.* 2020, 228.
6. Christopher, P.; Linic, S. Engineering selectivity in heterogeneous catalysis: Ag nanowires as selective ethylene epoxidation catalysts. *J. Am. Chem. Soc.* 2008, 130, 11264–11265.
7. Greiner, M.T.; Jones, T.E.; Klyushin, A.; Knop-Gericke, A.; Schlögl, R. Ethylene Epoxidation at the Phase Transition of Copper Oxides. *J. Am. Chem. Soc.* 2017, 139, 11825–11832.
8. Pu, T.; Tian, H.; Ford, M.E.; Rangarajan, S.; Wachs, I.E. Overview of Selective Oxidation of Ethylene to Ethylene Oxide by Ag Catalysts. *ACS Catal.* 2019, 9, 10727–10750.
9. Khatib, S.J.; Oyama, S.T. Direct Oxidation of Propylene to Propylene Oxide with Molecular Oxygen: A Review. *Catal. Rev. Sci. Eng.* 2015, 57, 306–344.
10. Song, Y.Y.; Wang, G.C. Theoretical Study of Propylene Epoxidation over Cu₂O(111) Surface: Activity of O₂-, O-, and O²⁻ Species. *J. Phys. Chem. C* 2018, 122, 21500–21513.
11. Vaughan, O.P.H.; Kyriakou, G.; MacLeod, N.; Tikhov, M.; Lambert, R.M. Copper as a selective catalyst for the epoxidation of propene. *J. Catal.* 2005, 236, 401–404.
12. Global Vegetable Oil Market Report: 2017–2030. 2021. Available online: <https://www.goldsteinresearch.com/report/global-vegetable-oil-market> (accessed on 21 June 2021).
13. Wai, P.T.; Jiang, P.; Shen, Y.; Zhang, P.; Gu, Q.; Leng, Y. Catalytic developments in the epoxidation of vegetable oils and the analysis methods of epoxidized products. *RSC Adv.* 2019, 9, 38119–38136.
14. Danov, S.M.; Kazantsev, O.A.; Esipovich, A.L.; Belousov, A.S.; Rogozhin, A.E.; Kanakov, E.A. Recent advances in the field of selective epoxidation of vegetable oils and their derivatives: A review and perspective. *Catal. Sci. Technol.* 2017, 7, 3659–3675.
15. Cecilia, J.A.; Plata, D.B.; Saboya, R.M.A.; de Luna, F.M.T.; Cavalcante, C.L.; Rodríguez-Castellón, E. An overview of the biolubricant production process: Challenges and future perspectives. *Processes* 2020, 8, 257.
16. Latif, R.F.E.A.; Abidin, Z.Z.; Cardona, F.; Awang Biak, D.R.; Abdan, K.; Tahir, P.M.; Ern, L.K. Bio-resin production through ethylene unsaturated carbon using vegetable oils. *Processes* 2020, 8, 48.
17. Zhang, J.; Hu, Y.; Zhang, F.; Lu, J.; Huang, J.; Liu, C.; Jia, P.; Hu, L.; An, R.; Zhou, Y. Recent Progress in Microwave-assisted Modification of Vegetable Oils or Their Derivatives. *Curr. Org. Chem.* 2020, 24, 870–884.

18. Vevere, L.; Fridrihsone, A.; Kirpluks, M.; Cabulis, U. A review of wood biomass-based fatty acids and rosin acids use in polymeric materials. *Polymers* 2020, 12, 2706.
19. Goud, V.V.; Patwardhan, A.V.; Pradhan, N.C. Kinetics of in situ epoxidation of natural unsaturated triglycerides catalyzed by acidic ion exchange resin. *Ind. Eng. Chem. Res.* 2007, 46, 3078–3085.

Retrieved from <https://encyclopedia.pub/entry/history/show/32030>