

Encyclopedia

Applications of Cyclodextrins Modified/Coated Metal–Organic Frameworks

Created by: Huacheng Zhang

Version received: 18 March 2020




The introduction of cyclodextrins (CDs) via noncovalent bonds could improve various physiochemical properties of metal–organic frameworks (MOFs) and expand their practical applications in aqueous solutions, for example, biocompatible CDs could improve the solubility of CDs-coated MOFs as a hybrid delivery system. And external-stimuli responsiveness of CDs-coated MOFs is key for widening applications in controlled drug releasing system, catalysis, detection, extraction and separation.

Table of Content [Hide]

Drug Delivery and Release System

CDs-modified MOFs provide an opportunity of combining diverse functions for the application in biomedicines such as improving biocompatibility and solubility of delivery systems, introducing particular functional groups for recognizing specific targeting receptors, escaping immune system, delivering various drugs and drug models, release drugs according to external stimuli as well as delaying the release for different requirements of medical treatments [1,2].

Different roles of CDs and MOFs in the hybrid materials (Scheme 1) contribute a lot to improving the functions of traditional bioactive materials, as well as drug delivery and release systems.



Scheme 1 Structural illustrations of **H1**—**H5** and **L1**.

The introduction of CDs can improve the biocompatibility and solubility of unmodified MOFs in H_2O , and CDs-modified MOFs is able to be used for specific targeting, due to the possession of recognition ability on the outer surface of MOFs and the escape from the immune system. For example, in order to evade the immune system and to add extra molecular recognition ability, tetraethylene glycol, PEG and mannose moieties can functionalize CDs first, and then modified CDs could further combine with MOFs, such as loading CDs on the outer surface of MIL-100(Fe) via the phosphate- Fe^{III} bonding [2,3] and leading to a significant decrease of macrophage uptake (Figure 1). Particularly, the tetraethylene glycol-bearing β -CDs phosphate (**H1**) modified MOFs exhibit remarkably enhanced binding affinity towards the specific mannose receptor, i.e., Concanavalin A, due to the possession of mannose moieties, reduced macrophage internalization and multivalent effects based on the scaffold of β -CDs.




Figure 1. Observations by confocal microscopy to evaluate the interaction between J774 macrophage and CDs-coated MOFs, indicating that hybrid materials have penetrated into macrophage and affected its functions. Cells were stained in green with calcein, the cell nucleus is in black, and the rhodamine-B-labeled hybrid materials exhibited red signals. The differences of images (**a,b,c**) of the same cells caused by three different heights above the glass slide including 2.3, 4.9 and 7.6 μm , respectively. Scale bar = 5 μm . Reproduced from Reference [2] with permission from the Nature Publishing Group, copyright 2015.

CDs-modified MOFs can be used for delivering and releasing drugs. In the first step, CDs mainly perform as a cap to stop the release of loaded drugs, for example, tetraethylene glycol functionalized β -CDs (**H2**) can further be coated on the outer surface of DOX-loaded MIL-100(Fe) without affecting the payload of the nanocomposite [3]. In the second step, removing CDs from hybrid materials will lead to the release of loaded drugs, and different CDs coated on the surface of inorganic materials have different performances, for example, the effect of releasing the tritium-labeled antiretroviral drug, AZT-PT by CDs-coated MOFs is estimated by scintillation counting [4], and reveals that polymeric β -CDs (such as **H3**) modified MOFs afford a better control of drug release over monomeric β -CDs (**H4** and **H5**) coated ones, due to the presence of nonmodified CDs moieties in the structure and interacting with drugs. Although it is known that AZT has interactions with native and primary face-modified β -CDs, polymeric β -CDs-modified MOFs can increase drug retention in 13%.

Particularly, the external stimuli-responsive release of drugs can be achieved by the employment of CDs-coated MOFs. For example, external stimuli-responsive molecules such as azobenzene can be introduced into the hybrid materials such as the water-stable, biocompatible and degradable Zr-MOF, then act as the switch tool to associate/disassociate with coated β -CDs in accordance with different light irradiation conditions and, finally, control the performance of thus obtained integrated hybrid organic–inorganic materials, which have already stored drug models such as rhodamine B [5]. Additionally, the “gatekeeper”, β -CDs, can also be removed to release cargos inside the UiO-68-azo-bearing Zr-MOFs upon the addition of competitive guests, e.g., the drug for Parkinson’s disease, amantadine [5]. Thus, this kind of β -CDs-coated Zr-MOFs might be used as a platform for on-command drug delivery systems (Figure 2).




Figure 2. (a) Schematic illustration of the controlled release system upon the addition of a competitive guest, amantadine, as well as exposure under UV irradiation. The *trans*-azobenzene and its *cis*-isomer are colored in green and cyan, respectively. (b) Changing points in the release profile of CDs capped UiO-68-azo-bearing Zr-MOFs. Reproduced from Reference [5] with permission from the American Association for the Advancement of Science, copyright 2016.

Additionally, the organic–inorganic hybrid material, β -CDs/ Fe_3O_4 @ SiO_2 @MIL-100(Fe) [6], can be used as a pH-responsive drug delivery system due to the possession of pH-sensitive β -CDs, which is unstable and easily hydrolyzed at lower pH solutions. It is found that the drug model, cephalexin is released by this system slower under physiological conditions than the acidic buffer solution, indicating that the release happens in a controlled manner. Furthermore, it is observed that increasing temperature enhanced the drug release percentage, due to the shrinking of temperature-

sensitive polymers inside hybrid materials (Figure 3). However, the coating of the organic layer onto the surface of $\text{Fe}_3\text{O}_4@\text{SiO}_2@\text{MIL-100}(\text{Fe})$ results in a decrease in magnetic responsivity, and the magnetic responsiveness of this hybrid material was not explored directly upon releasing drugs.




Figure 3. (a) The release of cephalexin at different pH at $T = 37^\circ\text{C}$, (b) the effect of temperature on the release of cephalexin at $\text{pH} = 1.2$, (c) the effect of temperature on the release of cephalexin at $\text{pH} = 7$ and (d) the effect of temperature on the release of cephalexin at $\text{pH} = 5$. Reproduced from Reference [6] from the Royal Society of Chemistry, copyright 2018.

CDs-modified MOFs can perform as efficient and robust drug delivery systems comprising potential for slow release. For example, β -CDs-modified Fe-MIL-88B-NH_2 [7] could store alendronate through both the pores of MOFs and the cavities of loaded β -CDs, increasing the drug loading amount. Interestingly, after loading alendronate, the β -CDs-modified Fe-MIL-88B-NH_2 can be encapsulated with hydroxyapatite, which is the main component of teeth texture and can further lower the drug release rate with bone-like structures by decreasing the demand dosage. It is still very curious about the role of CDs in this system, for example, it looks like both CDs and MOFs have the same roles in the construction of drug delivery systems here, and there is no control experiment about the delivery system without functionalizing CDs.

Catalysis and Detection Materials

The employment of CDs is a very good control strategy for tuning MOFs to apply in the catalysis area. For example, with the assistance of host–guest complex between β -CDs and **L1** as assembly agents, UiO-66-NH_2 loaded polypropylene performs well in catalytic degradation of dimethyl 4-nitrophenyl phosphate, a chemical warfare agent simulant, with a half-life of less than 5 min [8].

Additionally, the CDs-modified MOFs hybrid materials also reveal good catalytic behavior, due to the possession of the large surface area of MOFs as well as the synergistic effect between MOFs and CDs, for example, the nanocomposite, $\text{MOF-235}/\beta\text{-CDs}$ has catalytic activity for the hydrogen peroxide-luminol system, and can enhance the chemiluminescence response with more than 30-fold in comparison with that of hydrogen peroxide-luminol system (Figure 4) [9]. Thus, the catalytical performance of $\text{MOF-235}/\beta\text{-CDs}$ could be applied to sensitively detect H_2O_2 and glucose. It is further found that the limits of detection (LOD) for H_2O_2 and glucose in serum samples by $\text{MOF-235}/\beta\text{-CDs}$ hybrid materials are 0.5 and $1.0 \times 10^{-9} \text{ mol L}^{-1}$, respectively.




Figure 4. Proposed chemiluminescence (CL) mechanism of the luminol- H_2O_2 system by MOF-235/ $\beta\text{-CD}$ s hybrid materials. MOF-235 is generated by the coordination reaction between Fe^{III} and terephthalic acid (top left), and further functionalized with $\beta\text{-CD}$. The intermediate of luminol is supposed to be hosted by the cavity of $\beta\text{-CD}$ (right) during the oxidation reaction of glucose with glucose oxidase (GOx). Reproduced from Reference [9] with permission from Elsevier B.V. Copyright 2018.

Except for the above example for applying to detection fields, CDs-modified MOFs could further be used for extraction and separation. For example, the hybrid material M-MOF/ $\beta\text{-CD}$ s could perform as the solid phase extraction material and extract prochloraz and triazole fungicides from tomato and lettuce vegetables. As determined by HPLC–MS/MS, the LOD for those fungicides are $0.25\text{--}1.0 \times 10^{-6} \text{ g L}^{-1}$ at a signal-to-noise ratio of three with spiked recoveries of 74.13%–119.83% [10], indicating that analyte detection was not affected by differences in the standard curve diluent and experimental sample matrix.

References

1. Zhang, H.; Liu, Z.; Shen, J., Cyclodextrins Modified/Coated Metal–Organic Frameworks. *Materials* **2020**, *13*, (6), 1273.
2. Agostoni, V.; Horcajada, P.; Noiray, M.; Malanga, M.; Aykaç, A.; Jicsinszky, L.; Vargas-Berenguel, A.; Semiramoth, N.; Daoud-Mahammed, S.; Nicolas, V.; Martineau, C.; Taulelle, F.; Vigneron, J.; Etcheberry, A.; Serre, C.; Gref, R., A “green” strategy to construct non-covalent, stable and bioactive coatings on porous MOF nanoparticles. *Sci. Rep.* **2015**, *5*, (1), 7925.
3. Cutrone, G.; Li, X.; Casas-Solvas, J. M.; Menendez-Miranda, M.; Qiu, J.; Benkovics, G.; Constantin, D.; Malanga, M.; Moreira-Alvarez, B.; Costa-Fernandez, J. M.; García-Fuentes, L.; Gref, R.; Vargas-Berenguel, A., Design of engineered cyclodextrin derivatives for spontaneous coating of highly porous metal-organic framework nanoparticles in aqueous media. *Nanomaterials* **2019**, *9*, (8), 1103.
4. Aykac, A.; Noiray, M.; Malanga, M.; Agostoni, V.; Casas-Solvas, J. M.; Fenyvesi, E.; Gref, R.; Vargas-Berenguel, A., A non-covalent “click chemistry” strategy to efficiently coat highly porous MOF nanoparticles with a stable polymeric shell. *Biochim. Biophys. Acta* **2017**, *1861*, (6), 1606–1616.
5. Meng, X.; Gui, B.; Yuan, D.; Zeller, M.; Wang, C., Mechanized azobenzene-functionalized zirconium metal-organic framework for on-command cargo release. *Sci. Adv.* **2016**, *2*, e1600480.
6. Lajevardi, A.; Sadr, M. H.; Yarak, M. T.; Badieie, A.; Armaghana, M., A pH-responsive and magnetic $\text{Fe}_3\text{O}_4/\text{silica}@\text{MIL-100}(\text{Fe})/\beta\text{-CD}$ nanocomposite as a drug nanocarrier: loading and release study of cephalexin. *New J. Chem.* **2018**, *42*, 9690–9701.
7. Golmohamadpour, A.; Bahramian, B.; Shafiee, A.; Ma’mani, L., Slow released delivery of alendronate using β -cyclodextrine modified Fe–MOF encapsulated porous hydroxyapatite. *J. Inorg. Organomet. Polym. Mater.* **2018**, *28*, 1991–2000.
8. Lee, D. T.; Zhao, J.; Peterson, G. W.; Parsons, G. N., Catalytic “MOF-Cloth” formed via directed supramolecular assembly of UiO-66-NH_2 crystals on atomic layer deposition-coated textiles for rapid degradation of chemical warfare

agent simulants. *Chem. Mater.* **2017**, *29*, 4894–4903.

9. Mao, X.; Lu, Y.; Zhang, X.; Huang, Y., beta-Cyclodextrin functionalization of metal-organic framework MOF-235 with excellent chemiluminescence activity for sensitive glucose biosensing. *Talanta* **2018**, *188*, 161–167.
10. Liu, G.; Li, L.; Gao, Y.; Gao, M.; Huang, X.; Lv, J.; Xu, D., A beta-cyclodextrin-functionalized magnetic metal organic framework for efficient extraction and determination of prochloraz and triazole fungicides in vegetables samples. *Ecotoxicol. Environ. Saf.* **2019**, *183*, 109546.

Keywords

Cyclodextrins; Metal organic frameworks; Drug delivery and release system; Catalysis; Detection; Application



© 2020 by the author(s). Distribute under aCreative Commans CC BY license